



Thermomechanics of damageable materials under diffusion: modelling and analysis

Tomáš Roubíček and Giuseppe Tomassetti

Abstract. We propose a thermodynamically consistent general-purpose model describing diffusion of a solute or a fluid in a solid undergoing possible phase transformations and damage, beside possible visco-inelastic processes. Also heat generation/consumption/transfer is considered. Damage is modelled as rate-independent. The applications include metal-hydrogen systems with metal/hydride phase transformation, poroelastic rocks, structural and ferro/para-magnetic phase transformation, water and heat transport in concrete, and if diffusion is neglected, plasticity with damage and viscoelasticity, etc. For the ensuing system of partial differential equations and inclusions, we prove existence of solutions by a carefully devised semi-implicit approximation scheme of the fractional-step type.

Mathematics Subject Classification. 35K55 · 35Q74 · 74A15 · 74R20 · 74N10 · 74F10 · 76S99 · 80A17 · 80A20.

Keywords. Visco-elastic porous solids · Incomplete damage · Diffusion driven by chemical-potential gradient · Phase transformations · Poroelastic materials · Plasticity · Swelling · Creep · Quasilinear parabolic systems · Time discretization · A priori estimates · Convergence.

1. Introduction

This paper addresses damage processes in visco-elastic materials undergoing various diffusion or inelastic processes with the goal to develop a general, multi-purpose model with wide application range and covering, in particular, several particular models occurring in the literature in a unifying way.

We introduce two internal variables: a scalar variable d , which accounts for damage, and a (generally vector-valued) phase field χ , whose components may have different interpretations according to the specific application at hand. In particular, the components of χ may account for content of a solute or a fluid, plastic strain, porosity, viscous strain causing creep, etc. The primary fields in our model will be:

- displacement $\mathbf{u} : [0, T] \times \Omega \rightarrow \mathbb{R}^3$,
- phase field $\chi : [0, T] \times \Omega \rightarrow K \subset \mathbb{R}^N$,
- concentration $c : [0, T] \times \Omega \rightarrow \mathbb{R}^+$,
- damage variable $d : [0, T] \times \Omega \rightarrow [0, 1]$,
- temperature $\theta : [0, T] \times \Omega \rightarrow \mathbb{R}^+$,

where $\Omega \subset \mathbb{R}^3$ is a considered domain occupied by the solid body, $T > 0$ is a fixed time horizon. We work in the small-strain approximation and we assume that the linear strain has the following form:

$$\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + \mathbb{E}\chi, \quad (1.1)$$

This research has been supported by GA ČR through the projects 201/10/0357 “Modern mathematical and computational models for inelastic processes in solids”, 13-18652S “Computational modeling of damage and transport processes in quasi-brittle materials”, 14-15264S “Experimentally justified multiscale modelling of shape memory alloys”, by the CEN-TEM Project No. CZ.1.05/21.00/03.0088 (cofounded from ERDF within the OP RDI programme, MŠMT ČR) at New Technologies Research Centre (Univ. of West Bohemia, Plzeň), and by INdAM-GNFM through projects “Mathematical Modeling of Morphing Processes” and “Mathematical Modeling of Shape Changes in Soft Tissues”.

where $\boldsymbol{\varepsilon}(\mathbf{u}) = \frac{1}{2}(\nabla \mathbf{u})^\top + \frac{1}{2}\nabla \mathbf{u}$ is the total linear strain, \mathbf{E} is its elastic part, and $\mathbb{E}\chi$ is its anelastic part dependent linearly on the phase field χ . Here \mathbb{E} is a third-order tensor, which we think as the mapping of \mathbb{R}^N into $\mathbb{R}^{3 \times 3}$ defined by $(\mathbb{E}\chi)_{ij} = \mathbb{E}_{ijk}\chi_k$. Using the above decomposition we can cover the concept that the free energy as well as the dissipation energy are let to depend on the elastic strain \mathbf{E} rather than the total strain $\boldsymbol{\varepsilon}(\mathbf{u})$. For a more general ansatz see Remarks 4.3 and 6.4 below.

The main difficulty is the combination of thermo-visco-(in)elastic-diffusive model with damage. As always, some simplifications are necessary mainly for analytical reasons. In particular, beside the mentioned small-strain concept, we admit only incomplete damage. Furthermore, we perform the analysis on a special ansatz, see (3.4) below. In particular, among other approximations, we neglect thermal expansion effects, direct coupling between concentration and strain (see Remark 6.10 below), direct coupling between concentration and damage, and coupling between damage and temperature. We also neglect cross-effects between dissipation in χ and d , cf. (3.1a), as well as the cross-effects in the transport processes, i.e. the Soret/Peltier effects. On the other hand, in case of a multi-component diffusant (when c would be vector valued) some cross effect could simply be modelled by a nondiagonal \mathbf{M} in (3.1b). Let us emphasize that complete damage would bring serious mathematical difficulties; in the isothermal case it has been addressed in [25] using a formulation by a time-dependent domain.

Typical application of damage in engineering models assumes that this destruction process is activated, irreversible, and much faster than the time scale of the other internal processes or than the external loading. This is reflected by the dissipation potential for d being nonsmooth at zero rate, not everywhere finite, and *homogeneous of degree 1*, cf. (3.3) below and [14, 36, 54, 55], and also [15]. We remark that the dissipation potential for the phase field χ has *superlinear growth at infinity* with respect to $\dot{\chi}$. Thus, degree 1 homogeneity of the dissipation potential for d provides a distinction between the character and the subsequent treatment of damage d in contrast to the phase field χ . Without such distinction, we could treat the pair (d, χ) as a *single* vector-valued internal variable (of course, we may still assume that \mathbb{E} does not depend on d), and merge (2.1b) with (2.1d), or (3.7b) with (3.7d), etc., leading to a model similar to those considered, for instance in [42, 43]. In the literature, there exist many models that combine diffusion and elasticity under damage; some of them are only isothermal and involve a regularization of damage by rate-dependent terms, as in [7], and/or involve a gradient term for the concentration of diffusant leading to a diffusion equation of Cahn-Hilliard type, see for instance [7] and [25].

The main analytical result here is the proof of existence of weak solutions of the initial-boundary-value problem for the thermodynamical system. To this goal, a rather constructive method is used which yields a conceptual algorithm that may serve for designing an efficient numerical strategy after a suitable spatial discretization (not performed here, however).

It should be emphasized that there are several important differences from [52]: the elastic strain (instead of the total strain) is systematically used also for dissipative processes and the internal variables are split into two sets, both subjected to a substantially different treatment and allow for qualification of the free energy ψ well fitted to damage. On top of it, the mathematical treatment of the heat-transfer equation is simplified like in by holding the formulation in terms of the couple temperature-enthalpy (instead of mere temperature).

The paper is organized as follows: In Sect. 2 we formulate the general model and briefly outline the underlying physics, referring mainly to the previous work [52]. Then, in Sect. 3 we present a menagerie of various specific examples illustrating a wide range of applications. Eventually, Sect. 4 summarizes the main existence result, whose proof is performed in Sect. 5.

Through the whole article, we use the convention that small italics stands for scalar, small and capital bold stand, respectively, for elements of \mathbb{R}^3 and elements of $\mathbb{R}^{3 \times 3}$. We shall occasionally use Greek letters to denote elements of \mathbb{R}^N , where N is the number of internal variables incorporated in the phase field χ . Consistent with this rule is our usage of the letter σ to denote the conjugate variable of χ , instead of stress. For the reader's convenience we summarize in the following Table 1 the symbols mostly used in the rest of this paper.

TABLE 1. *Main notation used in this paper*

\mathbf{u} displacement	$\boldsymbol{\varepsilon}(\mathbf{u}) = \frac{1}{2}(\nabla\mathbf{u} + \nabla\mathbf{u}^\top)$ small-strain tensor
χ phase field	η entropy
c concentration of diffusant	μ chemical potential
d damage variable	\mathbf{h} flux of diffusant
θ temperature	h bulk supply of diffusant (eventually set to 0)
$w = e_{\text{TH}}(\chi, \theta)$ enthalpy	h_s surface supply of diffusant
\mathbf{S} stress	\mathbf{q} heat flux
\mathbf{f} bulk force	q bulk heat supply (eventually set to 0)
\mathbf{f}_s surface force	$\mathbf{M} = \mathbf{M}(\mathbf{E}, \chi, c, d, \theta)$ mobility tensor
σ internal microforce associated to χ	$\mathbf{K} = \mathbf{K}(\mathbf{E}, \chi, c, d, \theta)$ heat-conductivity tensor
$\boldsymbol{\Sigma}$ microstress	\mathbb{D} tensor of viscous moduli in the Kelvin–Voigt model
\mathbf{f}, g bulk microforces (eventually set to 0)	$\alpha = \alpha(\chi)$ fracture-toughness
ψ free energy	γ water content (in examples)
e internal energy	ϕ porosity (in an example)

2. The general model: balance laws and dissipation inequality

The model derivation follows quite closely that of [52]. In order to derive a system of partial differential equations governing the evolution of the primary fields, we adopt the point of view of [21]. The balance equations are considered as:

$$\rho \ddot{\mathbf{u}} - \operatorname{div} \mathbf{S} = \mathbf{f}, \quad (\text{balance of linear momentum}) \quad (2.1a)$$

$$\sigma - \operatorname{div} \boldsymbol{\Sigma} = \mathbf{f}, \quad (\text{microscopic balance for phase field}) \quad (2.1b)$$

$$\dot{c} + \operatorname{div} \mathbf{h} = h, \quad (\text{solute balance}) \quad (2.1c)$$

$$s - \operatorname{div} \mathbf{s} = g. \quad (\text{microscopic balance for damage}) \quad (2.1d)$$

The first equation is the standard balance of linear momentum, with ρ the referential mass density and \mathbf{f} the non-inertial body force. The second and the fourth equations involve systems of microscopic forces (σ, s) and microscopic stresses ($\boldsymbol{\Sigma}, \mathbf{s}$) that perform work, respectively, on $(\dot{\chi}, \dot{d})$ and $(\nabla\dot{\chi}, \nabla\dot{d})$. Consistent with this interpretation is the expression of the internal power expenditure that appears on the right-hand side of the energy equation:

$$\dot{e} + \operatorname{div} \mathbf{q} = q + \mathbf{S} : \boldsymbol{\varepsilon}(\dot{\mathbf{u}}) + \sigma \cdot \dot{\chi} + \boldsymbol{\Sigma} : \nabla\dot{\chi} + s \dot{d} + \mathbf{s} \cdot \nabla\dot{d} + \mu \dot{c} - \mathbf{h} \cdot \nabla\mu, \quad (\text{energy balance}) \quad (2.1e)$$

where also the energetic contribution from the diffusion of a chemical species is accounted for by the last two terms. The choice of constitutive prescriptions, which we shall make is guided by the dissipation inequality:

$$\dot{\psi} + \eta \dot{\theta} - \mu \dot{c} \leq \mathbf{S} : \boldsymbol{\varepsilon}(\dot{\mathbf{u}}) + \sigma \cdot \dot{\chi} + \boldsymbol{\Sigma} : \nabla\dot{\chi} + s \dot{d} + \mathbf{s} \cdot \nabla\dot{d} - \mathbf{h} \cdot \nabla\mu - \frac{1}{\theta} \mathbf{q} \cdot \nabla\theta,$$

where $\psi = e - \eta\theta$ is the free energy. The dissipation inequality can be rewritten by exploiting the decomposition (1.1):

$$\dot{\psi} + s \dot{\theta} - \mu \dot{c} \leq \mathbf{S} : \dot{\mathbf{E}} + (\sigma + \mathbf{S} : \mathbb{E}) \cdot \dot{\chi} + \boldsymbol{\Sigma} : \nabla\dot{\chi} + s \dot{d} + \mathbf{s} \cdot \nabla\dot{d} - \mathbf{h} \cdot \nabla\mu - \frac{1}{\theta} \mathbf{q} \cdot \nabla\theta. \quad (2.2)$$

By using standard arguments, one can show that the free energy is ruled by a constitutive equation of the following type:

$$\psi = \varphi(\mathbf{E}, \chi, c, d, \theta, \nabla\chi, \nabla d). \quad (2.3)$$

Moreover, if entropy η does depend on the same list of variables, then necessarily

$$\eta = -\partial_\theta \varphi(\mathbf{E}, \chi, c, d, \theta, \nabla\chi, \nabla d). \quad (2.4)$$

The dissipation inequality can be rendered in a more compact form by defining:

$$\mathbf{S}_d = \mathbf{S} - \partial_{\mathbf{E}}\varphi, \tag{2.5a}$$

$$\sigma_d = \sigma + \mathbf{S} : \mathbb{E} - \partial_{\chi}\varphi, \tag{2.5b}$$

$$\Sigma_d = \Sigma - \partial_{\nabla\chi}\varphi, \tag{2.5c}$$

$$s_d = s - \partial_d\varphi, \tag{2.5d}$$

$$\mathbf{s}_d = \mathbf{s} - \partial_{\nabla d}\varphi, \tag{2.5e}$$

$$\mu_d = \mu - \partial_c\varphi. \tag{2.5f}$$

Here the Roman subscript *d* stands for “dissipative”, not to be confused with the *Italic d*, which indicates the damage variable. Moreover, in (2.5b), $\mathbf{S} : \mathbb{E}$ means the vector $\sum_{i,j=1}^3 \mathbf{S}_{ij}\mathbb{E}_{ijk}$. With that splitting, one indeed obtains the *reduced dissipation inequality*

$$0 \leq \mathbf{S}_d : \dot{\mathbf{E}} + \sigma_d \cdot \dot{\chi} + \Sigma_d : \nabla\dot{\chi} + s_d\dot{d} + \mathbf{s}_d \cdot \nabla\dot{d} + \dot{c}\mu_d - \mathbf{h} \cdot \nabla\mu - \frac{1}{\theta}\mathbf{q} \cdot \nabla\theta. \tag{2.6}$$

Remark 2.1. (*Rheology of the model*) From (2.5a), we can see that the total mechanical stress is $\mathbf{S} = \partial_{\mathbf{E}}\varphi + \mathbf{S}_d$, in what follows considered as $\mathbf{S} = \partial_{\mathbf{E}}\varphi + \mathbb{D}\dot{\mathbf{E}}$, cf. (3.1a). This is the classical Kelvin–Voigt rheological model. Through the internal parameters contained possibly in χ , we can easily combine it to get some more complicated solid-type rheological models as Jeffreys’ material or a so-called 4-parameter solid etc.

Remark 2.2. (*An alternative understanding*) In the expression of the free energy we could alternatively use as state variables the total strain $\boldsymbol{\varepsilon}(\mathbf{u})$ in place of the elastic strain. In particular, the mechanical energy in (3.4) could be written as $\varphi_{\text{ME}}(\boldsymbol{\varepsilon}(\mathbf{u}) - \mathbb{E}\chi, d)$, which would highlight the different roles played by χ and *d*; note that, in this case, the term $\mathbf{S} : \mathbb{E}$ in (2.5b) would be incorporated in $\partial_{\chi}\varphi$, and thus (2.5b) would be replaced by $\sigma_d = \sigma - \partial_{\chi}\varphi$. Note that then $\partial_{\boldsymbol{\varepsilon}}\varphi$, which is standardly understood as the elastic part of the stress tensor, is indeed equal to $\partial_{\mathbf{E}}\varphi$ we used in (2.5a).

3. Specialization and examples

The system of partial differential equations governing the evolution of the primary fields is obtained by combining the balance equations (2.1) with appropriate constitutive prescriptions for the dissipative parts of the auxiliary fields, consistent with the reduced dissipation inequality (2.6). We make the following choice:

$$\mathbf{S}_d = \mathbb{D}\dot{\mathbf{E}}, \quad \sigma_d \in \partial_{\dot{\chi}}\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}), \quad s_d \in \partial_{\dot{d}}\xi(\chi, \dot{d}), \tag{3.1a}$$

$$\mathbf{q} = -\mathbf{K}(\mathbf{E}, \chi, d, c, \theta)\nabla\theta, \quad \mathbf{h} = -\mathbf{M}(\mathbf{E}, \chi, d, c, \theta)\nabla\mu, \tag{3.1b}$$

$$\Sigma_d = 0, \quad \mathbf{s}_d = 0, \quad \mu_d = 0. \tag{3.1c}$$

We also set to null bulk sources in (2.1), except for the force balance (2.1a), that is:

$$\mathbf{f} = 0, \quad h = 0, \quad g = 0, \quad q = 0. \tag{3.2}$$

Here ζ and ξ are (possibly non-smooth) dissipation potentials, both $\zeta(\mathbf{E}, \chi, d, \cdot)$ and $\xi(\chi, \cdot)$ being convex and possibly nonsmooth at 0. More specifically, $\xi(\chi, \cdot)$ is assumed convex positively homogeneous of degree 1, so it is always nonsmooth at 0. Assuming irreversible (i.e. unidirectional) damage, ξ will be in the form

$$\xi(\chi, \dot{d}) = \begin{cases} \alpha(\chi)|\dot{d}| & \text{if } \dot{d} \leq 0 \\ \infty & \text{otherwise} \end{cases} \tag{3.3}$$

with $\alpha : \mathbb{R}^N \rightarrow \mathbb{R}^+$ denoting a phenomenological fracture-toughness coefficient, meaning the specific energy in J/m^3 required (and dissipated) during damage evolution. As we shall see later, the degree 1 homogeneity of the dissipation potential ξ in \dot{d} has the consequence that \dot{d} will be a measure in general. On the other hand, neither \mathbf{E} nor d are continuous. Thus, α in (3.3) cannot be made to depend on \mathbf{E} and d neither on θ but, on the other hand, its dependence on χ is legitimate because we will have a regularity of χ at disposal, cf. (5.34d) below.

The involvement of non-trivial dissipative terms σ_d and s_d is essential. In fact, the non-smooth and unbounded dissipation potential for d allows us to incorporate the phenomenology of irreversibility of damage and its character to be an activated process. Moreover, we benefit from the dissipative term for χ to control the terms containing $\dot{\chi}$ on the right-hand side of the heat equation, which would anyway be present because of an adiabatic coupling (cf. (3.7e) below). Moreover, the specification of a non-trivial viscous stress in the first of (3.1a) which leads to Kelvin–Voigt-type visco-elastic rheological models as mentioned in Remark 2.1 is needed to handle inertia, otherwise it can be neglected, cf. Remark 6.11 below. Clearly, we may also include non-trivial viscous-like contributions Σ_d and \mathbf{s}_d in the stress-like terms under divergence in the balance equations (2.1b, d). Including these contributions would not significantly extend the range of applications of our treatment and would make all notation heavier (moreover they would make our analysis more trivial to some extent, as far as the equation governing χ). Similar considerations hold for a dissipative contribution to chemical potential.

In order to facilitate the mathematical analysis of (2.1) with (2.5) and (3.1), see Remark 6.8 below, we restrict the generality of the free energy (2.3). In particular, we make the partly decoupled ansatz for the free energy (2.3), distinguishing mechanical, chemical, and thermal parts in the sense:

$$\psi = \underbrace{\varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \varphi_{\text{CH}}(\chi, c) + \varphi_{\text{TH}}(\chi, \theta)}_{=: \varphi_{\text{TOT}}(\mathbf{E}, \chi, c, d, \theta)} + \frac{1}{2} \kappa_1 |\nabla \chi|^2 + \frac{1}{2} \kappa_2 |\nabla d|^2 + \delta_K(\chi) + \delta_{[0,1]}(d). \tag{3.4}$$

Here K is a convex set where values of χ are assumed to lie, while d is valued at $[0, 1]$, and δ stands for the indicator function, i.e. $\delta_K(\cdot)$ is equal to 0 on K and $+\infty$ otherwise and similarly for $\delta_{[0,1]}(\cdot)$. The consequence of the decoupling (3.4) is that the *internal energy*, defined by Gibbs' relation $e = \psi - \theta \eta$ and occurring already in (2.1e), can be written as:

$$e = e_{\text{TH}}(\chi, \theta) + \underbrace{\varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \varphi_{\text{CH}}(\chi, c)}_{=: \varphi_{\text{ME/CH}}(\mathbf{E}, \chi, c, d)} + \frac{1}{2} \kappa_1 |\nabla \chi|^2 + \frac{1}{2} \kappa_2 |\nabla d|^2 + \delta_K(\chi) + \delta_{[0,1]}(d), \tag{3.5}$$

where the thermal part of the internal energy is

$$e_{\text{TH}}(\chi, \theta) = \varphi_{\text{TH}}(\chi, \theta) - \theta \partial_{\theta} \varphi_{\text{TH}}(\chi, \theta). \tag{3.6}$$

Altogether, from (2.1) with (2.5), (3.1), and (3.4), we obtain the following system:

$$\rho \ddot{\mathbf{u}} - \text{div}(\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D} \dot{\mathbf{E}}) = \mathbf{f} \quad \text{with } \mathbf{E} = \varepsilon(\mathbf{u}) - \mathbb{E} \chi, \tag{3.7a}$$

$$\begin{aligned} \partial_{\chi} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) - \kappa_1 \Delta \chi + \partial_{\chi} \varphi_{\text{TOT}}(\mathbf{E}, \chi, c, d, \theta) \\ - \mathbb{E}^{\text{T}} : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D} \dot{\mathbf{E}}) + \sigma_{\text{r}} \ni 0 \end{aligned} \quad \text{with } \sigma_{\text{r}} \in \partial \delta_K(\chi), \tag{3.7b}$$

$$\dot{c} - \text{div}(\mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu) = 0 \quad \text{with } \mu = \partial_c \varphi_{\text{CH}}(\chi, c), \tag{3.7c}$$

$$\partial_d \xi(\chi, \dot{d}) - \kappa_2 \Delta d + \partial_d \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + s_{\text{r}} \ni 0 \quad \text{with } s_{\text{r}} \in \partial \delta_{[0,1]}(d), \tag{3.7d}$$

$$\begin{aligned} \dot{w} - \text{div}(\mathbf{K}(\mathbf{E}, \chi, c, d, \theta) \nabla \theta) = \partial_{\chi} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \cdot \dot{\chi} + \partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) \cdot \dot{\chi} \\ + \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} - \alpha(\chi) \dot{d} + \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu \cdot \nabla \mu \end{aligned} \quad \text{with } w = e_{\text{TH}}(\chi, \theta). \tag{3.7e}$$

We point out that, at variance with standard treatments of the heat equation, the left-hand side of (3.7e) does not contain the time derivative of temperature θ , at least explicitly. Instead, we have the time derivative of the so-called *enthalpy* w . In principle, we may replace temperature with enthalpy in the formulation, as done for instance in [51]. However, since temperature has a more straightforward physical relevance, we prefer to keep both w and θ in our formulation.

We also note that $\zeta(\mathbf{E}, \chi, c, d, \theta, \cdot)$ is possibly nonsmooth at 0, so that $\partial_{\dot{\chi}}\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi})$ may be multi-valued, but anyhow we assume in (4.1n) below that the term $\partial_{\dot{\chi}}\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \cdot \dot{\chi}$ appearing in the right-hand side of (3.7e) and also in (4.9f) below is well defined. This occurs, e.g., if $\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi})$ has a form $a(\mathbf{E}, \chi, c, d, \theta)|\dot{\chi}| + b(\mathbf{E}, \chi, c, d, \theta)|\dot{\chi}|^2$ with some $a, b \geq 0$. We complete (3.7) with the following boundary condition:

$$(\partial_{\mathbf{E}}\varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D}\dot{\mathbf{E}})\mathbf{n} = \mathbf{f}_s, \tag{3.8a}$$

$$\nabla\chi \cdot \mathbf{n} = 0, \tag{3.8b}$$

$$\mathbf{M}(\mathbf{E}, \chi, c, d, \theta)\nabla\mu \cdot \mathbf{n} = h_s, \tag{3.8c}$$

$$\nabla d \cdot \mathbf{n} = 0, \tag{3.8d}$$

$$\mathbf{K}(\mathbf{E}, \chi, c, d, \theta)\nabla\theta \cdot \mathbf{n} = q_s \tag{3.8e}$$

to be valid on the boundary Γ of Ω . Using the convention like $\mathbf{u}(\cdot, t) =: \mathbf{u}(t)$, we complete the system by the initial conditions:

$$\mathbf{u}(0) = \mathbf{u}_0, \quad \dot{\mathbf{u}}(0) = \mathbf{v}_0, \quad \chi(0) = \chi_0, \quad c(0) = c_0, \quad d(0) = d_0, \quad w(0) = w_0 := \varphi_{\text{TH}}(\chi_0, \theta_0). \tag{3.9}$$

The above-formulated model is very general and can be understood as truly multi-purpose. Let us present a couple of motivating examples now, while in the final section we shall present some examples more.

Example 3.1. (Metal/hydride phase transformation) Some metals or intermetallics allow for relatively easy diffusion of hydrogen and undergo a transformation into hydrides accompanied by markable volume changes (even up to 30%), cf. [31]. Several continuum models have been proposed, accompanied by their analytical study [5, 6, 10, 52]. Such big volume variation then often causes damage. In this case, we have $N = 1$ and the (scalar-valued) phase field χ stands for the volume fraction related to the metal/hydride transformation, while the variable c is the hydrogen concentration. The free energy can be considered as

$$\varphi_{\text{TOT}}(\mathbf{E}, \chi, c, d, \theta) = \underbrace{\frac{1}{2}\mathbb{C}(d)\mathbf{E}:\mathbf{E}}_{=: \varphi_{\text{ME}}} + \underbrace{\frac{k}{2}|a(\chi) - c|^2 + \phi_1(c)}_{=: \varphi_{\text{CH}}} + \underbrace{\phi_2(\chi, \theta)}_{=: \varphi_{\text{TH}}} \tag{3.10}$$

where $k > 0$ is a (typically large) coefficient and $a(\chi)$ a function that maps values of phase field into values of concentration, which reflects the fact that different phases typically manifest themselves at different concentrations. In this case, System (3.7) takes the form:

$$\rho\ddot{\mathbf{u}} - \text{div}(\mathbb{C}(d)\mathbf{E} + \mathbb{D}(\varepsilon(\dot{\mathbf{u}}) - \mathbb{E}\dot{\chi})) = \mathbf{f}, \quad \text{with } \mathbf{E} = \varepsilon(\mathbf{u}) - \mathbb{E}\chi, \tag{3.11a}$$

$$\begin{aligned} \partial_{\dot{\chi}}\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) - \kappa_1\Delta\chi + k(a(\chi)\partial_{\chi} - c)a'(\chi) + \partial_{\chi}\phi_2(\chi, \theta) \\ - \mathbb{E}^{\top}:(\mathbb{C}(d)\mathbf{E} + \mathbb{D}\dot{\mathbf{E}}) + \sigma_{\text{r}} \ni 0 \end{aligned} \quad \text{with } \sigma_{\text{r}} \in \partial\delta_K(\chi), \tag{3.11b}$$

$$\dot{c} - \text{div}(\mathbf{M}(\mathbf{E}, \chi, c, d, \theta)\nabla\mu) = 0 \quad \text{with } \mu = -k(a(\chi) - c) + \phi_1'(c), \tag{3.11c}$$

$$\partial_{\dot{d}}\xi(\chi, \dot{d}) - \kappa_2\Delta d + \frac{1}{2}\mathbb{C}'(d)\mathbf{E}:\mathbf{E} + s_{\text{r}} \ni 0 \quad \text{with } s_{\text{r}} \in \partial\delta_{[0,1]}(d), \tag{3.11d}$$

$$\begin{aligned} \dot{w} - \operatorname{div}(\mathbf{K}(\mathbf{E}, \chi, c, d, \theta)\nabla\theta) &= \partial_{\dot{\chi}}\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \cdot \dot{\chi} + k(a(\chi) - c)a'(\chi)\dot{\chi} \\ &+ \mathbb{D}\dot{\mathbf{E}}:\dot{\mathbf{E}} - \alpha(\chi)\dot{d} + \mathbf{M}(\mathbf{E}, \chi, c, d, \theta)\nabla\mu \cdot \nabla\mu \quad \text{with } w = \phi_2(\chi, \theta) - \theta\partial_{\theta}\phi_2(\chi, \theta). \end{aligned} \quad (3.11e)$$

As already remarked, (3.10) is consistent with our splitting ansatz (3.4). Without damage but considering still thermal expansion, this model has been treated in [52]. Thus, the present paper generalizes [52] towards this important damage phenomenon. In particular we may take $a(\chi) = \chi$. In this case, χ is somehow related to the concept of *nonlocal species concentration*, a concept introduced in [56] to handle the difficulties related to the numerical solution of the Cahn–Hilliard equation, and further elaborated in [12], where the extra field (here χ) is called *micromorphic concentration*. As $\partial_{cc}^2\varphi_{\text{CH}}(\chi, c) = k + \phi_1''(c)$, the uniform convexity in c requires just a semi-convexity of ϕ_1 if one admits k large. Moreover, the physically relevant non-negativity of c can then be ensured by taking for ϕ_2 a function that blows up as its argument tends to zero. An example may be the coarse-grain chemical free energy obtained from regular solution theory:

$$\phi_2(\chi, \theta) = \phi_3(\theta) + A\theta(\chi \log(\chi) + (1-\chi) \log(1-\chi)) + B\chi(1-\chi), \quad (3.12)$$

with A and B positive constants, cf. [26]. Of course, due to the large strains sometimes involved in the hydration phase transformation, developing the model in the small-strain setting might be debatable. For a model coupling diffusion and damage in the large-strain setting, we refer to [13].

Example 3.2. (Poroelastic rocks) Geophysical models of lithospheres in short time scale (less than 1 mil. yrs) count small strains. Typical phenomena to be captured are damage, plasticity (considered here rate-dependent), and water propagation through porous rocks, cf. e.g. [59]. The phase field is then composed from plastic strain π_{pl} and porosity ϕ , while c is the water concentration, cf. e.g. [22, 23, 33]. The free energy is considered as $\psi = \frac{1}{2}\lambda(\phi, d)(\operatorname{tr} \mathbf{E})^2 + G(\phi, d)|\mathbf{E}|^2 + \frac{1}{2}M(\phi, d)|\beta \operatorname{tr} \mathbf{E} - c + \phi|^2 + c_v\theta(\ln\theta - 1)$ with $\mathbf{E} = \boldsymbol{\varepsilon}(\mathbf{u}) - \pi_{\text{pl}}$ and with λ the first Lamé coefficient, G the shear modulus (also called the second Lamé coefficient and denoted by μ which here denotes, however, the chemical potential) M the Biot modulus, and β the Biot coefficient. The chemical potential μ and the Nernst–Planck equation (3.7c) play the role of a pressure and of the Darcy equation. This however does not directly fit with the splitting (3.4) because c and \mathbf{E} are directly coupled unless the Biot modulus or the Biot coefficient are zero. To make it consistent with (3.4), similarly as in Example 3.1 we again distinguish between the water concentration c and the water content γ ; in fact, [22, 23, 33] speak about water content, although consider the water flow governed by the Darcy equation like if it were a water concentration. Therefore, we consider the augmented phase field as $\chi = (\pi_{\text{pl}}, \phi, \gamma)$ and then the free energy as

$$\begin{aligned} \varphi_{\text{TOT}}(\mathbf{E}, \phi, \gamma, c, d, \theta) &= \underbrace{\frac{1}{2}\lambda(\phi, d)(\operatorname{tr} \mathbf{E})^2 + G(\phi, d)|\mathbf{E}|^2 + \frac{1}{2}M(\phi, d)|\beta \operatorname{tr} \mathbf{E} - \gamma + \phi|^2}_{=:\varphi_{\text{ME}}} \\ &+ \underbrace{\frac{1}{2}k|\gamma - c|^2}_{=:\varphi_{\text{CH}}} + \underbrace{c_v\theta(\ln\theta - 1)}_{=:\varphi_{\text{TH}}} \quad \text{with } \mathbf{E} = \boldsymbol{\varepsilon}(\mathbf{u}) - \pi_{\text{pl}}. \end{aligned} \quad (3.13)$$

Note that (1.1) still applies, provided that we define $\chi = (\pi_{\text{pl}}, \phi, \gamma)$ and $\mathbb{E}\chi := \pi_{\text{pl}}$. In order to arrive at a concrete system of partial differential equations/inclusions, we assume for simplicity that the dissipation pseudopotential associated to the evolution of $\chi = (\pi_{\text{pl}}, \phi, \gamma)$ be decoupled, in the sense that

$$\zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) = \zeta_{\text{pl}}(\pi_{\text{pl}}, \dot{\pi}_{\text{pl}}) + \zeta_{\phi}(\phi, \dot{\phi}) + \zeta_{\gamma}(\gamma, \dot{\gamma}), \quad (3.14)$$

and that the convex set K has the form $K = \mathbb{R}_{sym}^{3 \times 3} \times K_\phi \times K_\gamma$, with K_ϕ , and K_γ convex. Then, system (3.7) becomes:

$$\rho \ddot{\mathbf{u}} - \operatorname{div}(\lambda(\phi, d)(\operatorname{tr} \mathbf{E}) \mathbf{I} + 2G(\phi, d) \mathbf{E} + M(\phi, d)(\beta \operatorname{tr} \mathbf{E} - \gamma + \phi) \beta \mathbf{I} + \mathbb{D} \dot{\mathbf{E}}) = \mathbf{f}, \quad \text{with } \mathbf{E} = \boldsymbol{\varepsilon}(\mathbf{u}) - \pi_{pl}, \quad (3.15a)$$

$$\partial_{\dot{\pi}_{pl}} \zeta_{pl}(\pi_{pl}, \dot{\pi}_{pl}) - \kappa_1 \Delta \pi_{pl} - \lambda(\phi, d)(\operatorname{tr} \mathbf{E}) \mathbf{I} - 2G(\phi, d) \mathbf{E} - M(\phi, d)(\beta \operatorname{tr} \mathbf{E} - \gamma + \phi) \beta \mathbf{I} - \mathbb{D} \dot{\mathbf{E}} \ni 0, \quad (3.15b)$$

$$\begin{aligned} \partial_{\dot{\phi}} \zeta_\phi(\phi, \dot{\phi}) - \kappa_1 \Delta \phi + \frac{1}{2} \partial_\phi \lambda(\phi, d)(\operatorname{tr} \mathbf{E})^2 + \partial_\phi G(\phi, d) |\mathbf{E}|^2 + \frac{1}{2} \partial_\phi M(\phi, d) |\beta \operatorname{tr} \mathbf{E} - \gamma + \phi|^2 \\ + M(\phi, d)(\beta \operatorname{tr} \mathbf{E} - \gamma + \phi) + \sigma_{r, \phi} \ni 0 \end{aligned} \quad \text{with } \sigma_{r, \phi} \in \partial \delta_{K_\phi}(\phi), \quad (3.15c)$$

$$\partial_{\dot{\gamma}} \zeta_\gamma(\gamma, \dot{\gamma}) - \kappa_1 \Delta \gamma - M(\phi, d)(\beta \operatorname{tr} \mathbf{E} - \gamma + \phi) + k(\gamma - c) + \sigma_{r, \gamma} \ni 0 \quad \text{with } \sigma_{r, \gamma} \in \partial \delta_{K_\gamma}(\phi), \quad (3.15d)$$

$$\dot{c} - \operatorname{div}(\mathbf{M}(\mathbf{E}, \pi_{pl}, \phi, \gamma, c, d, \theta) \nabla \mu) = 0 \quad \text{with } \mu = -k(\gamma - c), \quad (3.15e)$$

$$\begin{aligned} \partial_{\dot{d}} \xi(\pi_{pl}, \dot{d}) - \kappa_2 \Delta d + \frac{1}{2} \partial_d \lambda(\phi, d)(\operatorname{tr} \mathbf{E})^2 + \partial_d G(\phi, d) |\mathbf{E}|^2 \\ + \frac{1}{2} \partial_d M(\phi, d) |\beta \operatorname{tr} \mathbf{E} - \gamma + \phi|^2 \ni 0 \end{aligned} \quad \text{with } s_r \in \partial \delta_{[0,1]}(d), \quad (3.15f)$$

$$\begin{aligned} c_v \dot{\theta} - \operatorname{div}(\mathbf{K}(\mathbf{E}, \pi_{pl}, \phi, \gamma, c, d, \theta) \nabla \theta) = \partial_{\dot{\pi}_{pl}} \zeta(\mathbf{E}, \pi_{pl}, \phi, \gamma, c, d, \theta, \dot{\pi}_{pl}) \cdot \dot{\pi}_{pl} \\ + \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} - \alpha(\pi_{pl}, \phi, \gamma) \dot{d} + \mathbf{M}(\mathbf{E}, \pi_{pl}, \phi, \gamma, c, d, \theta) \nabla \mu \cdot \nabla \mu. \end{aligned} \quad (3.15g)$$

Note that in this special case the thermal part of the free energy depends only on temperature. In particular, for the special form of φ_{TH} in (3.13) we have $w = c_v \theta$.

4. Data qualification, weak formulation, and the main result

Beside the standard notation for the Lebesgue L^p -spaces, we will use $W^{k,p}$ for Sobolev spaces whose k -th derivatives are in L^p -spaces, the abbreviation $H^k = W^{k,2}$. We consider a fixed time interval $I = [0, T]$, and we denote by $L^p(I; X)$ the standard Bochner space of Bochner-measurable mappings $I \rightarrow X$ with X a Banach space. Also, $W^{k,p}(I; X)$ denotes the Banach space of mappings from $L^p(I; X)$ whose k -th distributional derivative in time is also in $L^p(I; X)$. Also, $C(I; X)$ and $C_{\text{weak}}(I; X)$ will denote the Banach space of continuous and weakly continuous mappings $I \rightarrow X$, respectively. Moreover, we denote by $BV(I; X)$ the Banach space of the mappings $I \rightarrow X$ that have bounded variation on I , and by $B(I; X)$ the space of Bochner measurable, everywhere defined, and bounded mappings $I \rightarrow X$. By $\text{Meas}(I; X)$ we denote the space of X -valued measures on I . Finally, in what follows, C denotes a positive, possibly large constant, whereas ϵ denotes a positive small constant.

Let us collect our main assumptions on the data:

$$\Omega \subset \mathbb{R}^3 \text{ is a bounded Lipschitz domain,} \quad (4.1a)$$

$$\varphi_{ME} \in C^2(\mathbb{R}^N \times \mathbb{R} \times \mathbb{R}_{sym}^{3 \times 3}), \quad \varphi_{CH} \in C^2(\mathbb{R}^N \times \mathbb{R}), \quad \varphi_{TH} \in C^2(\mathbb{R}^N \times \mathbb{R}), \quad (4.1b)$$

$$\mathbf{M} \in C(\mathbb{R}_{sym}^{3 \times 3} \times \mathbb{R}^N \times \mathbb{R} \times \mathbb{R} \times \mathbb{R}), \quad \mathbf{K} \in C(\mathbb{R}_{sym}^{3 \times 3} \times \mathbb{R}^N \times \mathbb{R} \times \mathbb{R} \times \mathbb{R}). \quad (4.1c)$$

$$\varphi_{ME}(\mathbf{E}, \chi, d) \geq \epsilon |\mathbf{E}|^2 - C, \quad |\partial_{(\mathbf{E}, \chi)} \varphi_{ME}(\mathbf{E}, \chi, d)| \leq C(1 + |\mathbf{E}|), \quad (4.1d)$$

$$|\partial_\chi \varphi_{CH}(\chi, c)| \leq C(1 + |c|^3), \quad (4.1e)$$

$$0 < \epsilon \leq -\theta \partial_{\theta\theta}^2 \varphi_{\text{TH}}(\chi, \theta) \leq C \quad \text{and} \quad |\partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) - \theta \partial_{\chi\theta}^2 \varphi_{\text{TH}}(\chi, \theta)| \leq C, \tag{4.1f}$$

$$\varphi_{\text{CH}}(\chi, c) \geq \epsilon c^2 - C, \tag{4.1g}$$

$$\mathbf{E} \mapsto \varphi_{\text{ME}}(\mathbf{E}, \chi, d) \text{ is strongly convex uniformly with respect to } \chi \text{ and } d, \tag{4.1h}$$

$$(\mathbf{E}, \chi) \mapsto \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + M|\chi|^2 \text{ is convex for } M \text{ sufficiently large,} \tag{4.1i}$$

$$c \mapsto \varphi_{\text{CH}}(\chi, c), \text{ is strongly convex uniformly with respect to } \chi, \tag{4.1j}$$

$$\mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \text{ and } \mathbf{K}(\mathbf{E}, \chi, c, d, \theta) \text{ are uniformly positive definite and bounded,} \tag{4.1k}$$

$$\exists C > 0 : |\partial_c \varphi_{\text{CH}}(\chi, c)| \leq C(1 + \varphi_{\text{CH}}(\chi, c)), \tag{4.1l}$$

$$\zeta(\mathbf{E}, \chi, c, d, \theta, \cdot) : \mathbb{R}^N \rightarrow \mathbb{R}^+ \text{ is convex and } \exists \epsilon > 0 : \epsilon |\dot{\chi}|^2 \leq \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \leq \frac{1 + |\dot{\chi}|^2}{\epsilon}, \tag{4.1m}$$

$$\dot{\chi} \mapsto \partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \cdot \dot{\chi} : \mathbb{R}^N \rightarrow \mathbb{R}^+ \text{ is single-valued and strictly convex, while} \tag{4.1n}$$

ξ satisfies (3.3) with $\alpha : \mathbb{R}^N \rightarrow \mathbb{R}^+$ smooth and

$$\text{bounded together with its second gradient and } \inf \alpha(\mathbb{R}^N) > 0, \tag{4.1o}$$

$$|\partial_{\chi c}^2 \varphi_{\text{CH}}(\chi, c)| \leq C, \tag{4.1p}$$

$$|\partial_{\chi} \varphi_{\text{TH}}(\chi, \theta)| \leq C \sqrt{1 + \varphi_{\text{ME/CH}}(\mathbf{E}, \chi, c, d) + e_{\text{TH}}(\chi, \theta)}, \text{ and} \tag{4.1q}$$

$$|\partial_{\chi} e_{\text{TH}}(\chi, \theta)| \leq C \sqrt{1 + e_{\text{TH}}(\chi, \theta)}, \tag{4.1r}$$

$$\partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) = 0 \quad \text{for } \theta \leq 0. \tag{4.1s}$$

Then, we add the qualification of the outer mechanical, chemical, and thermal loading:

$$\mathbf{f} \in L^2(Q; \mathbb{R}^3), \quad \mathbf{f}_s \in L^2(\Sigma; \mathbb{R}^3), \quad q_s \in L^1(\Sigma), \quad h_s \in L^2(\Sigma) \text{ with } q_s \geq 0 \text{ and } h_s \geq 0 \text{ a.e. on } \Sigma, \tag{4.2}$$

where we used the abbreviation $Q = (0, T) \times \Omega$ and $\Sigma = (0, T) \times \Gamma$ for a fixed time horizon $T > 0$. Later, \bar{Q} will denote the closure of Q .

The uniform strong convexity means e.g. in (4.1h) that

$$\exists \epsilon > 0 \forall (\mathbf{E}, \tilde{\mathbf{E}}, \chi, d) \in \mathbb{R}_{\text{sym}}^{3 \times 3} \times \mathbb{R}_{\text{sym}}^{3 \times 3} \times K \times [0, 1] : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\tilde{\mathbf{E}}, \chi, d) - \partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d)) : (\tilde{\mathbf{E}} - \mathbf{E}) \geq \epsilon |\tilde{\mathbf{E}} - \mathbf{E}|^2. \tag{4.3}$$

Analogous meaning has also (4.1l). The statement (4.1k) is as usual understood in the sense that there exists $\epsilon > 0$ such that, for all $\mathbf{v} \in \mathbb{R}^3$ and $(\mathbf{E}, \chi, c, d, \theta) \in \mathbb{R}_{\text{sym}}^{3 \times 3} \times K \times [0, 1] \times \mathbb{R} \times \mathbb{R}^+$, it holds $\epsilon |\mathbf{v}|^2 \leq \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \mathbf{v} \cdot \mathbf{v} \leq |\mathbf{v}|^2 / \epsilon$ and $\epsilon |\mathbf{v}|^2 \leq \mathbf{K}(\mathbf{E}, \chi, c, d, \theta) \mathbf{v} \cdot \mathbf{v} \leq |\mathbf{v}|^2 / \epsilon$. In (4.1q)–(4.1r), we understand that $\varphi_{\text{ME/CH}} \geq 0$ and $e_{\text{TH}} \geq 0$, as we always can without loss of generality. The qualification (4.11c) represents a semi-stability of the initial damage profile; the adjective “semi” refers to that \mathbf{E}_0 and χ_0 are fixed on both the left- and the right-hand sides of (4.11c).

Let us briefly comment the main aspects of the above assumptions:

1. The second growth assumption in (4.1d) and assumption (4.1e) on $\partial_{\chi} \varphi_{\text{ME/CH}}$, together with assumption (4.1m) on ζ facilitates the L^2 estimate of $\Delta \chi$. This estimate is needed to make sense of the by-part-integration formula (5.71) which by its turn justifies the weak form (4.9b) of (3.7b), the inclusion governing χ .
2. In principle we could admit a general p -growth/coercivity with $p \leq 2$ in (4.1d). However, we cannot handle $p > 2$. The main reason is the integrability of terms in (5.73) and, if $\varrho > 0$, also the duality in (5.52). For simplicity, we confine ourselves to $p = 2$ only, without restricting substantially possible applications.
3. Assumptions (4.1k) are needed to have coercivity in the diffusion and the heat-conduction equation.

4. It follows from the third condition in (4.1b) and from the first condition in (4.1f) that the thermal part of the internal energy e_{TH} defined in (3.6) is continuously differentiable, and satisfies:

$$0 < \partial_{\theta} e_{\text{TH}}(\chi, \theta) \leq C. \tag{4.4}$$

Hence, the function $\theta \mapsto e_{\text{TH}}(\chi, \theta)$ is invertible for all χ and its inverse is continuously differentiable. Thus, there exists a function $\vartheta \in C^1(\mathbb{R}^N \times \mathbb{R}^+; \mathbb{R}^+)$ such that

$$e_{\text{TH}}(\chi, \vartheta(\chi, w)) = w, \tag{4.5}$$

$$0 < 1/C \leq \partial_w \vartheta(\chi, w) \leq 1/\epsilon \tag{4.6}$$

with ϵ and C referring to (4.4). Moreover, we observe that the second condition in (4.1f) entails that

$$|\partial_{\chi} \vartheta(\chi, w)| \leq C. \tag{4.7}$$

5. The semi-stability of the initial damage (4.11c) is needed for the energy conservation which, in turn, is vitally needed for the convergence in the heat equation, cf. Step 9 in the proof of Proposition 5.5.

We can now state the weak formulation of the initial-boundary-value problem (3.7)–(3.9). As for the damage part, we use the concept of the so-called energetic solution devised by Mielke and Theil [37], based on the energy (in)equality and the so-called stability, cf. (4.9d) below, and further employed in the thermodynamical concept in [45]. This formulation is essentially equivalent to the conventional weak formulation but excludes time derivatives of rate-independent variables, i.e. here the damage d .

Definition 4.1. Given initial conditions (4.11) and the bulk and boundary data (4.2), the seven-tuple $(\mathbf{u}, \chi, c, d, \theta, \mu, w)$ with

$$\mathbf{u} \in L^{\infty}(I; W^{1,p}(\Omega; \mathbb{R}^3)) \cap H^1(I; H^1(\Omega; \mathbb{R}^3)), \tag{4.8a}$$

$$\chi \in C_{\text{weak}}(I; H^1(\Omega; \mathbb{R}^N)) \cap H^1(I; L^2(\Omega; \mathbb{R}^N)) \quad \text{with} \quad \Delta \chi \in L^2(Q), \tag{4.8b}$$

$$c \in L^{\infty}(I; L^2(\Omega)), \tag{4.8c}$$

$$d \in B(I; H^1(\Omega)) \cap \text{BV}(I; L^1(\Omega)), \quad d \geq 0 \text{ a.e. on } Q, \tag{4.8d}$$

$$\theta \in L^r(I; W^{1,r}(\Omega)) \quad \text{for any } r \in [1, 5/4), \tag{4.8e}$$

$$\mu \in L^{\infty}(I; H^1(\Omega)), \tag{4.8f}$$

$$w \in L^{\infty}(I; L^1(\Omega)) \tag{4.8g}$$

is called a weak solution to the initial-boundary-value problem (3.7)–(3.9) if

$$\int_Q (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D} \dot{\mathbf{E}}) : \varepsilon(\mathbf{z}) - \rho \dot{\mathbf{u}} \cdot \dot{\mathbf{z}} \, dx \, dt = \int_Q \mathbf{f} \cdot \mathbf{z} \, dx \, dt + \int_{\Sigma} \mathbf{f}_s \cdot \mathbf{z} \, dS \, dt + \int_{\Omega} \mathbf{v}_0 \cdot \mathbf{z}(0) \, dx$$

$$\forall \mathbf{z} \in L^2(I; H^1(\Omega; \mathbb{R}^3)) \cap H^1(I; L^2(\Omega; \mathbb{R}^3)), \quad \mathbf{z}(T) = 0, \tag{4.9a}$$

$$\int_Q \zeta(\mathbf{E}, \chi, c, d, \theta, z) + (\partial_{\chi} \varphi_{\text{TOT}}(\mathbf{E}, \chi, c, d, \theta) - \mathbb{E}^{\top} : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D} \dot{\mathbf{E}}) + \sigma_{\text{r}}) \cdot (z - \dot{\chi}) + \kappa_1 \nabla \chi : \nabla z \, dx \, dt$$

$$+ \int_{\Omega} \frac{\kappa_1}{2} |\nabla \chi_0|^2 \, dx \geq \int_Q \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \, dx \, dt + \int_{\Omega} \frac{\kappa_1}{2} |\nabla \chi(T)|^2 \, dx \quad \forall z \in L^2(I; H^1(\Omega; \mathbb{R}^N)), \tag{4.9b}$$

$$\int_Q \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu \cdot \nabla z - c \dot{z} \, dx \, dt = \int_{\Sigma} h_s z \, dS \, dt + \int_{\Omega} c_0 z(0) \, dx \quad \forall z \in H^1(Q), \quad z(T) = 0, \tag{4.9c}$$

$$\int_{\Omega} \varphi_{\text{ME}}(\mathbf{E}(t), \chi(t), d(t)) + \frac{\kappa_2}{2} |\nabla d(t)|^2 dx \leq \int_{\Omega} \left(\varphi_{\text{ME}}(\mathbf{E}(t), \chi(t), \tilde{d}) + \frac{\kappa_2}{2} |\nabla \tilde{d}|^2 + \alpha(\chi(t))(\tilde{d} - d(t)) \right) dx \quad \text{for a.e. } t \in I \ \forall \tilde{d} \in H^1(\Omega), \ 0 \leq \tilde{d} \leq d(t) \text{ on } \Omega, \tag{4.9d}$$

$$\int_Q \mathbf{K}(\mathbf{E}, \chi, c, d, \theta) \nabla \theta \cdot \nabla z - w \dot{z} dx dt = \int_{\Omega} (w_0 + \alpha(\chi_0) d_0) z(0) dx + \int_{\Sigma} q_s z dS dt + \int_Q \left((\partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) + \partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) + \alpha'(\chi) d) \cdot \dot{\chi} + \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu \cdot \nabla \mu + \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} \right) z + \alpha(\chi) d \dot{z} dx dt \quad \forall z \in W^{1,\infty}(Q), \ z(T) = 0, \tag{4.9e}$$

$$\mathcal{E}_{\text{MC}}(T) + \int_{\Omega} \alpha(\chi(T)) d(T) dx + \int_Q \left(\mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} + (\partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) + \partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) + \alpha'(\chi) d) \cdot \dot{\chi} + \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu \cdot \nabla \mu \right) dx dt = \mathcal{E}_{\text{MC}}(0) + \int_{\Omega} \alpha(\chi_0) d_0 dx + \int_Q \mathbf{f} \cdot \dot{\mathbf{u}} dx dt + \int_{\Sigma} \mathbf{f}_s \cdot \dot{\mathbf{u}} + q_s + \mu h_s dS dt \tag{4.9f}$$

where $\mathbf{E} \in H^1(I; L^2(\Omega; \mathbb{R}_{\text{sym}}^{3 \times 3}))$, μ and w from (4.8f,g), and $\sigma_r \in L^2(Q; \mathbb{R}^N)$, satisfy

$$\mathbf{E} = \boldsymbol{\varepsilon}(\mathbf{u}) - \mathbb{E}\chi, \quad \mu = \partial_c \varphi_{\text{CH}}(\chi, c), \quad w = e_{\text{TH}}(\chi, \theta), \quad \sigma_r \in \partial \delta_K(\chi) \tag{4.9g}$$

a.e. in Q and where the energy occurring in (4.9f) at time $t = 0$ and $t = T$ is:

$$\mathcal{E}_{\text{MC}}(t) := \int_{\Omega} \varphi_{\text{ME/CH}}(\mathbf{E}(t), \chi(t), d(t), c(t)) + \frac{\rho}{2} |\dot{\mathbf{u}}(t)|^2 + \frac{\kappa_1}{2} |\nabla \chi(t)|^2 + \frac{\kappa_2}{2} |\nabla d(t)|^2 dx,$$

where $\varphi_{\text{ME/CH}}$ is defined in (3.5). Eventually, the remaining three initial conditions holds:

$$\mathbf{u}(0) = \mathbf{u}_0, \quad \chi(0) = \chi_0, \quad d(0) = d_0 \quad \text{a.e. in } \Omega. \tag{4.10}$$

We can now specify the qualifications of the initial conditions:

$$\mathbf{u}_0 \in H^1(\Omega; \mathbb{R}^3), \quad \mathbf{v}_0 \in L^2(\Omega; \mathbb{R}^3), \quad c_0 \in H^1(\Omega), \quad \chi_0 \in H^1(\Omega; \mathbb{R}^N), \quad d_0 \in H^1(\Omega), \quad w_0 \in L^1(\Omega), \tag{4.11a}$$

$$d_0 \in [0, 1], \quad \chi_0 \in K, \quad w_0 = e_{\text{TH}}(\chi_0, \theta_0) \text{ with } \theta_0 \geq 0 \text{ a.e. in } \Omega, \text{ and} \tag{4.11b}$$

$$\int_{\Omega} \varphi_{\text{ME}}(\mathbf{E}_0, \chi_0, d_0) + \frac{\kappa_2}{2} |\nabla d_0|^2 dx \leq \int_{\Omega} \varphi_{\text{ME}}(\mathbf{E}_0, \chi_0, \tilde{d}) + \frac{\kappa_2}{2} |\nabla \tilde{d}|^2 + \alpha(\chi(t))(\tilde{d} - d_0) dx \quad \forall \tilde{d} \in H^1(\Omega), \ 0 \leq \tilde{d} \leq d_0 \text{ a.e. on } \Omega, \tag{4.11c}$$

with $\mathbf{E}_0 = \boldsymbol{\varepsilon}(\mathbf{u}_0) - \mathbb{E}\chi_0$.

The above definition uses several tricky points, which seems in general quite inevitable for this sort of complicated problems, cf. also [42] for an even more tricky definition. Here, let us note that we made the by-part integration in time in (4.9a,c,e) to avoid abstract duality pairings due to only weak estimates on $\rho \ddot{\mathbf{u}}$, \dot{c} , and \dot{w} we will have at disposal, cf. (5.34a–c) below. The other three initial conditions $\dot{\mathbf{u}}(0) = \mathbf{v}_0$, $c(0) = c_0$, and $w(0) = w_0$ are thus involved already in (4.9a, c, e). The by-part integration used in (4.9b) is to avoid the term $\int_Q \nabla \chi \cdot \nabla \dot{\chi} dx dt$ where $\nabla \dot{\chi}$ would not have a good sense; for this we need the $L^2(Q)$

integrability of $\Delta\chi$ specified in (4.8b). Also note that we used the by-part integration in time for the heat term induced by damage, i.e.

$$\int_{\bar{Q}} \alpha(\chi)z\dot{d}(dxdt) = \int_{\Omega} \alpha(\chi(T))z(T)d(T) dx - \int_{\bar{Q}} (\alpha'(\chi)\dot{\chi}z + \alpha(\chi)\dot{z})d dxdt - \int_{\Omega} \alpha(\chi(0))z(0)d(0) dx \tag{4.12}$$

for z smooth with $z(T) = 0$ in (4.9e) or with $z = 1$ in (4.9f) to avoid usage of the measure \dot{d} in Definition 4.1, which anyway would be problematic, since the continuity of $\alpha(\chi)$ on \bar{Q} does not seem to be guaranteed.

More importantly, we balanced only the mechano-chemical energy \mathcal{E}_{MC} to avoid usage of $\theta(T)$ or of $w(T)$ which would not have a specified meaning as the temperature as well as the thermal part of the internal energy may be discontinuous in time instances where \dot{d} concentrates. The exponent 5/4 in (4.8e) is consistent with the Boccardo–Gallouët regularity estimates on parabolic equations with L^1 data [4], cf. e.g. also [46, sect. 12.1]. This relevant estimate shall be derived in Lemma 5.3 below.

Theorem 4.2. *Let the assumptions (4.1)–(4.2) be valid. Then there exists a weak solution to the initial-boundary-value problem (3.7)–(3.9) in the sense of Definition 4.1 such that also $q\dot{\mathbf{u}} \in L^2(I; H^1(\Omega; \mathbb{R}^3)^*)$, $\dot{c} \in L^2(I; H^1(\Omega)^*)$, $\dot{w} \in \text{Meas}(I; W^{1,r/(r-1)}(\Omega)^*)$, $\theta \geq 0$ a.e. in Q . Moreover, the total energy balance is satisfied “generically” in the sense that, for a.a. $t \in I$, it holds that*

$$\mathcal{E}_{\text{TOT}}(t) - \mathcal{E}_{\text{TOT}}(0) = \int_0^t \left(\int_{\Omega} \mathbf{f} \cdot \dot{\mathbf{u}} dx + \int_{\Gamma} \mathbf{f}_s \cdot \dot{\mathbf{u}} + q_s + \mu h_s dS \right) dt, \tag{4.13}$$

where, referring to $\varphi_{\text{ME/CH}}$ and e_{TH} from (3.5)–(3.6), the total energy is:

$$\mathcal{E}_{\text{TOT}}(t) = \int_{\Omega} \left(\varphi_{\text{ME/CH}}(\mathbf{E}(t), \chi(t), d(t), c(t)) + e_{\text{TH}}(\chi(t), \theta(t)) + \frac{\varrho}{2} |\dot{\mathbf{u}}(t)|^2 + \frac{1}{2} \kappa_1 |\nabla \chi(t)|^2 + \frac{1}{2} \kappa_2 |\nabla d(t)|^2 \right) dx.$$

We will prove this theorem in the next section by a constructive way which also suggest a conceptual numerical strategy which, after another discretization in space, would allow for an efficient computer implementation.

Remark 4.3. (*Difficulties with nonlinear ansatz*) One can attempt to generalize the linear term $\mathbb{E}\chi$ in (1.1) but a strong nonlinear dependence may affect the semi-convexity assumption (4.1i) below. To better clarify this last point, assume that we replace the decomposition (1.1) with $\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + \mathbf{E}_{\text{tr}}(\chi)$, where \mathbf{E}_{tr} is now a nonlinear function. Suppose also that the mechanical energy has the simple form $\varphi_{\text{ME}}(\mathbf{E}) = \frac{1}{2} \mathbb{C} \mathbf{E} : \mathbf{E}$. Then, the energy functional pertaining to \mathbf{u} and χ would be

$$(\mathbf{u}, \chi) \mapsto \int_{\Omega} \frac{1}{2} \mathbb{C}(\boldsymbol{\varepsilon}(\mathbf{u}) - \mathbf{E}_{\text{tr}}(\chi)) : (\boldsymbol{\varepsilon}(\mathbf{u}) - \mathbf{E}_{\text{tr}}(\chi)) dx \tag{4.14}$$

but a simple calculation shows that if the function \mathbf{E}_{tr} is nonlinear, then the integrand in (4.14) cannot be convex (and not even semiconvex) with respect to the variables $\boldsymbol{\varepsilon}(\mathbf{u})$ and χ . Anyhow, the simple, linear ansatz (1.1), to be interpreted as a first-order expansion consistent with the linearization implied by the small-strain setting, still enjoys a considerable range of applications, cf. in particular Examples 3.1–6.5 below and the references therein.

5. Time discretization and the proof of existence of weak solutions

Our proof of Theorem 4.2 is based on the following strategy:

- A semi-implicit discretization of the system (3.7) of a fractional-step type which decouples this system at each time level and is numerically stable under quite weak convexity requirements on φ_{TOT} , cf. also [46, Rem. 8.25] for a general discussion. Namely, we use four steps in such a way that one solves separately (3.7a-b), then (3.7c), then (3.7d), and eventually (3.7e).
- The above specified splitting allows for only the relatively weak (partial) semi-convexity assumption (4.1i). In particular, we thus do not require any (semi)-convexity of $\varphi_{\text{ME/CH}}$ or even of φ_{ME} itself which would exclude interesting applications like the examples in Sect. 3.
- A further key ingredient is an L^2 -estimate of the term $\partial_{\chi} \varphi_{\text{ME/CH}}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}) + \partial_{\chi} \varphi_{\text{TH}}(\underline{\chi}_{\tau}, \underline{\theta}_{\tau}) - \mathbb{E}^{\top} : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}) + \mathbb{D} \dot{\bar{\mathbf{E}}}_{\tau}) + \bar{\sigma}_{\tau, \tau}$ in (5.13b), together with the qualification of the dissipation potential ζ for χ to have a bounded subdifferential so that one can obtain the additional estimate $\Delta \chi \in L^2(Q; \mathbb{R}^N)$. This facilitates the by-part integration formula (5.71) and, if Ω is smooth, also the H^2 -regularity of χ is needed to give a good sense to the dissipative-heat term $\alpha(\chi) \dot{d}$.

We use an equidistant partition of the time interval $I = [0, T]$ with a time step $\tau > 0$, assuming $T/\tau \in \mathbb{N}$, and denote by $\{\mathbf{u}_{\tau}^k\}_{k=0}^{T/\tau}$ an approximation of the desired values $\mathbf{u}(k\tau)$, and similarly d_{τ}^k is to approximate $d(k\tau)$, etc. Further, let us abbreviate by \mathfrak{d}_{τ}^k the backward difference operator, e.g. $\mathfrak{d}_{\tau}^k \mathbf{u} := \frac{\mathbf{u}_{\tau}^k - \mathbf{u}_{\tau}^{k-1}}{\tau}$, and similarly also $[\mathfrak{d}_{\tau}^k]^2 \mathbf{u} = \mathfrak{d}_{\tau}^k [\mathfrak{d}_{\tau}^k \mathbf{u}] = \frac{\mathbf{u}_{\tau}^k - 2\mathbf{u}_{\tau}^{k-1} + \mathbf{u}_{\tau}^{k-2}}{\tau^2}$, or $\mathfrak{d}_{\tau}^k d := \frac{d_{\tau}^k - d_{\tau}^{k-1}}{\tau}$, $\mathfrak{d}_{\tau}^k c := \frac{c_{\tau}^k - c_{\tau}^{k-1}}{\tau}$. When evaluating $[\mathfrak{d}_{\tau}^k]^2 \mathbf{u}$ for $k = 1$, we let $\mathbf{u}_{\tau}^{-1} = \mathbf{u}_{\tau}^0 - \tau \mathbf{v}_0$.

From a conceptual ‘‘algorithmic’’ viewpoint that may serve for a possible numerical implementation and for making the free-energy qualification as weak as possible, it is advantageous to make as fine splitting as possible. The finest splitting is essentially dictated by the considered de-coupled form of the dissipation energy. In particular, note that the Kelvin–Voigt viscosity acts on the elastic strain rate and thus involves both \mathbf{u} and $\mathbb{E}\chi$ so that the problems in Step 1 cannot be further decoupled, cf. also Remark 6.11 below for further discussion.

As a result, we consider the following 4-step algorithm:

Step 1: We seek weak solution \mathbf{u}_{τ}^k , and χ_{τ}^k to the following boundary-value problem (written in the classical formulation)

$$\rho [\mathfrak{d}_{\tau}^k]^2 \mathbf{u} - \text{div}(\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d_{\tau}^{k-1}) + \mathbb{D} \mathfrak{d}_{\tau}^k \mathbf{E}_{\tau}) = \mathbf{f}^k \tag{5.1a}$$

$$\begin{aligned} \partial_{\chi} \zeta(\mathbf{E}_{\tau}^{k-1}, \chi_{\tau}^{k-1}, d_{\tau}^{k-1}, c_{\tau}^{k-1}, \theta_{\tau}^{k-1}, \mathfrak{d}_{\tau}^k \chi) - \kappa_1 \Delta \chi_{\tau}^k + \partial_{\chi} \varphi_{\text{ME/CH}}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d_{\tau}^{k-1}, c_{\tau}^{k-1}) \\ + \partial_{\chi} \varphi_{\text{TH}}(\chi_{\tau}^{k-1}, \theta_{\tau}^{k-1}) - \mathbb{E}^{\top} : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d_{\tau}^{k-1}) + \mathbb{D} \mathfrak{d}_{\tau}^k \mathbf{E}_{\tau}) + \sigma_{\tau, \tau}^k \ni 0, \end{aligned} \tag{5.1b}$$

$$\text{with } \mathbf{E}_{\tau}^k = \varepsilon(\mathbf{u}_{\tau}^k) - \mathbb{E} \chi_{\tau}^k \text{ and some } \sigma_{\tau, \tau}^k \in \partial \delta_K(\chi_{\tau}^k) \text{ on } \Omega, \tag{5.1c}$$

and with boundary conditions

$$(\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d_{\tau}^{k-1}) + \mathbb{D} \mathfrak{d}_{\tau}^k \mathbf{E}_{\tau}) \mathbf{n} = \mathbf{f}_{s, \tau}^k \quad \text{and} \quad \nabla \chi_{\tau}^k \cdot \mathbf{n} = 0 \quad \text{on } \Gamma. \tag{5.1d}$$

Step 2: We seek a weak solution c_{τ}^k and μ_{τ}^k to the boundary-value problem:

$$\mathfrak{d}_{\tau}^k c - \text{div}(\mathbf{M}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d_{\tau}^{k-1}, c_{\tau}^{k-1}, \theta_{\tau}^{k-1}) \nabla \mu_{\tau}^k) = 0 \quad \text{with } \mu_{\tau}^k = \partial_c \varphi_{\text{CH}}(\chi_{\tau}^k, c_{\tau}^k) \quad \text{on } \Omega, \tag{5.2a}$$

with boundary condition

$$\nabla \mu_{\tau}^k \cdot \mathbf{n} = 0 \quad \text{on } \Gamma. \tag{5.2b}$$

Step 3: We seek $d_{\tau}^k \in H^1(\Omega)$ as a (global) minimizer of the functional

$$d \mapsto \int_{\Omega} \varphi_{\text{ME}}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d) - \alpha(\chi_{\tau}^k) d + \frac{\kappa_2}{2} |\nabla d|^2 dx \tag{5.3}$$

on the set $\{d \in H^1(\Omega); 0 \leq d \leq d_{\tau}^{k-1}\}$.

Step 4: Eventually, we seek a weak solution θ_τ^k and w_τ^k to the boundary-value problem:

$$\begin{aligned} & \frac{w_\tau^k - w_\tau^{k-1}}{\tau} - \operatorname{div}(\mathbf{K}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k, c_\tau^k, \theta_\tau^k) \nabla \theta_\tau^k) \\ &= (\partial_{\dot{\chi}} \zeta(\mathbf{E}_\tau^{k-1}, \chi_\tau^{k-1}, d_\tau^{k-1}, c_\tau^{k-1}, \theta_\tau^{k-1}, \mathfrak{d}_\tau^k \chi) + \partial_{\dot{\chi}} \varphi_{\text{TH}}(\chi_\tau^k, \theta_\tau^k)) \cdot \mathfrak{d}_\tau^k \chi \\ & \quad - \alpha(\chi_\tau^k) \mathfrak{d}_\tau^k d + \frac{\mathbb{D} \mathfrak{d}_\tau^k \mathbf{E} : \mathfrak{d}_\tau^k \mathbf{E}}{1 + \tau |\mathfrak{d}_\tau^k \mathbf{E}|^2} + \frac{\mathbf{M}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^{k-1}, \theta_\tau^{k-1}) \nabla \mu_\tau^k \cdot \nabla \mu_\tau^k}{1 + \tau |\nabla \mu_\tau^k|^2} \\ & \quad \text{with } w_\tau^k = e_{\text{TH}}(\chi_\tau^k, \theta_\tau^k) \end{aligned} \quad (5.4a)$$

with the boundary condition

$$\mathbf{K}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k, c_\tau^k, \theta_\tau^k) \nabla \theta_\tau^k = q_{s,\tau}^k \quad \text{on } \Gamma. \quad (5.4b)$$

Of course, this recursive scheme is to be started for $k = 1$ by putting

$$\mathbf{u}_\tau^0 = \mathbf{u}_0, \quad \mathbf{u}_\tau^{-1} = \mathbf{u}_0 - \tau \mathbf{v}_0, \quad \chi_\tau^0 = \chi_0, \quad c_\tau^0 = c_0, \quad d_\tau^0 = d_0, \quad w_\tau^0 = w_0 \quad (5.5)$$

with w_0 from (3.9). An important feature of this scheme is that it decouples to four boundary-value problems, which (after a further spatial discretization) can facilitate a numerical treatment and which is advantageously used even to show existence of approximate solutions. We also remark that the term $\partial_{\dot{\chi}} \varphi_{\text{TH}}$ is treated as lower-order terms. Note also that d_τ^k obtained in Step 3 is a weak solution to the boundary-value problem:

$$\partial_d \xi(\chi_\tau^k, \mathfrak{d}_\tau^k d) + \partial_d \varphi_{\text{ME}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k) + s_{r,\tau}^k \ni \kappa_2 \Delta d_\tau^k \quad \text{on } \Omega \quad \text{with } \nabla d_\tau^k \cdot \mathbf{n} = 0 \quad \text{on } \Gamma, \quad (5.6)$$

with some $s_{d,\tau}^k \in \text{and } s_{r,\tau}^k \in \partial \delta_{[0,\infty]}(d_\tau^k)$ on Ω . We, however, rely on the fact that d_τ^k is a special weak solution which is also the minimizer of the underlying potential (5.3). This needs not be the same if $\varphi_{\text{ME}}(\mathbf{E}, \cdot)$ is not convex, i.e. if damage may undergo weakening effects.

We observe on passing that the right-hand side of (5.4a) approximates, at least formally, the dissipative terms in the continuous heat equation (3.7e) as $\tau \rightarrow 0$. As we shall see in the proof of Lemma 5.1 below, this expedient ensures that we can use the standard L^2 theory for elliptic equations at the approximation level.

Lemma 5.1. (Existence of the discrete solution) *Let (4.1)–(4.2) hold. Then, for any $k = 1, \dots, T/\tau$, (5.1)–(5.4) has a solution $\mathbf{u}_\tau^k \in H^1(\Omega; \mathbb{R}^3)$, $\chi_\tau^k \in H^1(\Omega; \mathbb{R}^N)$, $d_\tau^k \in H^1(\Omega)$, $\sigma_{r,\tau}^k \in L^2(\Omega; \mathbb{R}^N)$, $c_\tau^k \in H^1(\Omega)$, $\mu_\tau^k \in H^1(\Omega)$, $\theta_\tau^k \in H^1(\Omega)$ such that $\theta_\tau^k \geq 0$.*

Proof. Step 1: Let us consider the space $V = H^1(\Omega; \mathbb{R}^3) \times H^1(\Omega)$. The boundary-value problem (5.1) is of the form $A(\mathbf{u}, \chi) \ni 0$, with A a set-valued mapping from V to its dual V^* such that $A = \partial \Phi$, where

$$\begin{aligned} \Phi(\mathbf{u}, \chi) &= \int_{\Omega} \left(\varphi_{\text{ME/CH}}(\boldsymbol{\varepsilon}(\mathbf{u}) - \mathbb{E}\chi, \chi, d_\tau^{k-1}, c_\tau^{k-1}) + \frac{1}{2} \kappa_1 |\nabla \chi|^2 + \delta_K(\chi) \right. \\ & \quad \left. + \frac{\tau^2}{2} \varrho \left| \frac{\mathbf{u} - 2\mathbf{u}_\tau^{k-1} + \mathbf{u}_\tau^{k-2}}{\tau^2} \right|^2 + \frac{\tau}{2} \mathbb{D} \left(\boldsymbol{\varepsilon} \left(\frac{\mathbf{u} - \mathbf{u}_\tau^{k-1}}{\tau} \right) - \mathbb{E}\chi \right) : \left(\boldsymbol{\varepsilon} \left(\frac{\mathbf{u} - \mathbf{u}_\tau^{k-1}}{\tau} \right) - \mathbb{E}\chi \right) \right. \\ & \quad \left. + \tau \zeta \left(\mathbf{E}_\tau^{k-1}, \chi_\tau^{k-1}, d_\tau^{k-1}, c_\tau^{k-1}, \theta_\tau^{k-1}, \frac{\chi - \chi_\tau^{k-1}}{\tau} \right) \right. \\ & \quad \left. + \partial_{\dot{\chi}} \varphi_{\text{TH}}(\chi_\tau^{k-1}, \theta_\tau^{k-1}) \cdot \chi + \mathbf{f}_\tau^k \cdot \mathbf{u} \right) dx + \int_{\Gamma} \mathbf{f}_{s,\tau}^k \cdot \mathbf{u} \, dS. \end{aligned} \quad (5.7)$$

Here the formulation covers also the quasistatic case, which is obtained by formally setting $\varrho = 0$. By (4.1i) and (4.1m), the potential Φ is weakly lower-semicontinuous although not necessarily convex here; in fact, later it will be convex if $\tau > 0$ is small enough, cf. Lemma 5.3 below. Due to the terms δ_K and ζ ,

Φ is nonsmooth. Moreover, by (4.1g) it is also coercive. Hence, by using the direct method, cf. e.g. [46, Theorem 5.3], we can see that (5.1) has at least a solution. Next we observe that the solution satisfies an inclusion:

$$\partial_\chi(\Phi_1 + \Phi_2)(\chi) + D\Phi_3(\chi) \ni 0, \tag{5.8}$$

where the left-hand side is a subset of $H^1(\Omega; \mathbb{R}^N)^*$, with $\Phi_1(\chi) = \tau \int_\Omega \zeta(\mathbf{E}_\tau^{k-1}, \chi_\tau^{k-1}, d_\tau^{k-1}, \theta_\tau^{k-1}, \frac{\chi - \chi_\tau^{k-1}}{\tau}) dx$, $\Phi_2(\chi) = \int_\Omega \delta_K(\chi) dx$ and with Φ_3 the remaining part of the potential Φ , which is Gateaux differentiable (we denote its Gateaux differential by $D\Phi_3$). Next, we observe that Φ_1 is convex, and by (4.1m) its domain is the whole space $H^1(\Omega; \mathbb{R}^N)$, and it is bounded from above in a bounded set of $H^1(\Omega; \mathbb{R}^N)$. Thus, by [58, Thm. 4.8], Φ_1 is locally Lipschitz continuous. Next, since $\text{dom}(\Phi_2) \neq \emptyset$, there exists $\chi_0 \in \text{dom}\Phi_1 \cap \text{dom}\Phi_2$ such that Φ_1 is in particular continuous at χ_0 . As both Φ_1 and Φ_2 are convex and lower semicontinuous, we conclude [58, Thm. 4.7] that:

$$\partial\Phi_1(\chi) + \partial\Phi_2(\chi) = \partial_\chi(\Phi_1 + \Phi_2)(\chi). \tag{5.9}$$

Now, we can take a measurable selection $\sigma_{d,\tau}^k \in \tau \partial_\chi \zeta(\mathbf{E}_\tau^{k-1}, \chi_\tau^{k-1}, d_\tau^{k-1}, \theta_\tau^{k-1}, \frac{\chi - \chi_\tau^{k-1}}{\tau})$ and by (4.1m), $\sigma_{d,\tau}^k \in L^2(\Omega; \mathbb{R}^N)$. Then by comparison, we obtain $\sigma_{r,\tau}^k \in L^2(\Omega; \mathbb{R}^N)$, cf. also the arguments leading to (5.34e) below; we recall that $\sigma_{r,\tau}^k$ is the selection of $\partial\delta_K(\chi_\tau^k)$ in (5.1c).

Step 2: We can treat (5.2) by a variational approach. We consider the function $\varphi_{\text{CH}}^*(\chi_\tau^k, \cdot)$ defined as the Legendre transform of $\varphi_{\text{CH}}(\chi_\tau^k, \cdot)$, and we notice that (5.2b) can be written as

$$c_\tau^k = \partial_\mu \varphi_{\text{CH}}^*(\chi_\tau^k, \mu_\tau^k). \tag{5.10}$$

Then (5.2) is equivalent the following variational problem on $H^1(\Omega)$:

$$\text{minimize } \mu \mapsto \int_\Omega \frac{\varphi_{\text{CH}}^*(\chi_\tau^k, \mu) - c_\tau^{k-1} \mu}{\tau} + \mathbf{M}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^{k-1}, \theta_\tau^{k-1}) \nabla \mu \cdot \nabla \mu dx, \tag{5.11}$$

which can be solved through the direct method. With this aim in mind, we notice that, since the domain of $\varphi(\chi_\tau^k, d_\tau^{k-1}, \cdot)$ is \mathbb{R} , its Legendre transform is coercive; actually, this is a classical result from convex analysis.

Step 3: The solution of (5.3) can be obtained simply by weak lower semicontinuity and coercivity arguments. Note that we do not require convexity of $\varphi_{\text{ME}}(\mathbf{E}, d, \cdot)$ so that the solution of (5.3) does not need to be unique.

Step 4: In this final step we solve the time-discrete heat equation (5.4a) with boundary conditions (5.4b). To this effect, we note that $\nabla \mu_\tau^k \in L^2(\Omega; \mathbb{R}^3)$. In particular, we have simply both $\mathbb{D}\mathfrak{d}_\tau^k \mathbf{E} : \mathfrak{d}_\tau^k \mathbf{E} / (1 + \tau |\mathfrak{d}_\tau^k \mathbf{E}|^2) \in L^\infty(\Omega)$ and $\mathbf{M}(\mathbf{E}_{e,\tau}^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^{k-1}, \theta_\tau^{k-1}) \nabla \mu_\tau^k \cdot \nabla \mu_\tau^k / (1 + \tau |\nabla \mu_\tau^k|^2) \in L^\infty(\Omega)$, and thus the right-hand side of (5.4a) is in $L^2(\Omega)$. Therefore, eventually, we are to solve (5.4), which represents a semilinear heat-transfer equation with the right-hand side in $H^1(\Omega)^*$. The only nonlinearity with respect to θ_τ^k is in the terms $\mathbf{K}(\boldsymbol{\varepsilon}(\mathbf{u}_\tau^k), \chi_\tau^k, d_\tau^k, c_\tau^k, \theta_\tau^k)$ and $\partial_\chi \varphi_{\text{TH}}(\chi_\tau^k, \theta_\tau^k)$. The later is needed to guarantee $\theta_\tau^k \geq 0$. Anyhow, since this nonlinearity is of lower order, we can pass through it by compactness and strong convergence. Thus, it suffices for us to check coercivity of the underlying operator. Having this aim, we test (5.4) by θ_τ^k . The terms on the right-hand side of (5.4a) containing θ_τ^k are estimated standardly by using Hölder's and Young's inequalities, and using the qualification (4.1q).

Having coercivity, we see that there exists at least one solution. Moreover, this solution satisfies $\theta_\tau^k \geq 0$, which can be seen by testing (5.4) by the negative part $(\theta_\tau^k)^-$ of θ_τ^k and using that $\partial_\chi \varphi_{\text{TH}}(\chi, \theta) = 0$ for $\theta \leq 0$, as assumed in (4.1s); actually, besides other standard arguments including the non-negativity of the initial temperature in (4.11b), one also uses that $(\theta_\tau^k)^- = f(w_\tau^k)$ with $f(\cdot) = (\varphi_{\text{TH}}(\chi_\tau^k, \cdot)^{-1})^-$ nonpositive nondecreasing, so that its primitive function \hat{f} is nonincreasing and convex, thus, in particular, we have

the inequality $(w_\tau^k - w_\tau^{k-1})(\theta_\tau^k)^- = (w_\tau^k - w_\tau^{k-1})f(w_\tau^k) \geq \widehat{f}(w_\tau^k) - \widehat{f}(w_\tau^{k-1})$ which directly follows from the definition of convex subdifferential. \square

Remark 5.2. The delayed terms \mathbf{E}_τ^{k-1} and d_τ^{k-1} in (5.1b) and c_τ^{k-1} in (5.2a) allow us to treat (5.1) and (5.2) as variational problems. This does not create troubles in the limit passage, see also Step 5 in the proof of Proposition 5.5 below.

We are now going to rewrite the approximate system (5.1)–(5.4) and the semi-stability information we can get from (5.3) in a more “condensed” form closer to the desired continuous system (3.7). To this aim, we extend to the whole time interval I the variables defined at the discrete times $k\tau$ through suitable interpolations. For example, the piecewise affine interpolant of \mathbf{u}_τ is defined by

$$\mathbf{u}_\tau(t) := \frac{t - (k-1)\tau}{\tau} \mathbf{u}_\tau^k + \frac{k\tau - t}{\tau} \mathbf{u}_\tau^{k-1} \quad \text{for } t \in [(k-1)\tau, k\tau] \quad (5.12a)$$

with $k = 0, \dots, T/\tau$. Besides, we introduce also the forward (left-continuous) and the backward (right-continuous) piecewise constant interpolants $\bar{\mathbf{u}}_\tau$ and $\underline{\mathbf{u}}_\tau$ defined by, respectively,

$$\bar{\mathbf{u}}_\tau(t) := \mathbf{u}_\tau^k, \quad \text{for } t \in ((k-1)\tau, k\tau], \quad k = 1, \dots, T/\tau, \quad (5.12b)$$

and

$$\underline{\mathbf{u}}_\tau(t) := \mathbf{u}_\tau^{k-1}, \quad \text{for } t \in [(k-1)\tau, k\tau), \quad k = 1, \dots, T/\tau. \quad (5.12c)$$

Similarly, we define also $d_\tau, \bar{d}_\tau, \underline{d}_\tau, \bar{w}_\tau, w_\tau, \bar{g}_\tau, \bar{\mathbf{f}}_{b,\tau}$, etc. We will also need the piecewise affine interpolant of the (piecewise constant) velocity $\dot{\mathbf{u}}_\tau$, which we denote by $[\dot{\mathbf{u}}_\tau]^i$, i.e.

$$[\dot{\mathbf{u}}_\tau]^i(t) := \frac{t - (k-1)\tau}{\tau} \frac{\mathbf{u}_\tau^k - \mathbf{u}_\tau^{k-1}}{\tau} + \frac{k\tau - t}{\tau} \frac{\mathbf{u}_\tau^{k-1} - \mathbf{u}_\tau^{k-2}}{\tau} \quad \text{for } t \in ((k-1)\tau, k\tau]. \quad (5.12d)$$

Note that $\ddot{\mathbf{u}}_\tau^i := \frac{\partial}{\partial t} [\dot{\mathbf{u}}_\tau]^i$ is piecewise constant with the values $(\mathbf{u}_\tau^k - 2\mathbf{u}_\tau^{k-1} + \mathbf{u}_\tau^{k-2})/\tau^2$ on the particular subintervals $((k-1)\tau, k\tau)$. In a similar fashion, we interpolate the other variables, using the same notation we use for \mathbf{u} .

In terms of interpolants, we can write the approximate system (5.1)–(5.4) as:

$$\varrho \ddot{\mathbf{u}}_\tau^i - \operatorname{div}(\partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) + \mathbb{D} \dot{\mathbf{E}}_\tau) = \bar{\mathbf{f}}_\tau \quad \text{with } \bar{\mathbf{E}}_\tau = \boldsymbol{\varepsilon}(\bar{\mathbf{u}}_\tau) - \mathbb{E} \bar{\chi}_\tau, \quad (5.13a)$$

$$\begin{aligned} \partial_{\bar{\chi}} \zeta(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau, \dot{\chi}_\tau) - \kappa_1 \Delta \bar{\chi}_\tau + \partial_{\chi} \varphi_{\text{ME/CH}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau) \\ + \partial_{\chi} \varphi_{\text{TH}}(\underline{\chi}_\tau, \underline{\theta}_\tau) - \mathbb{E}^\top : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) + \mathbb{D} \dot{\mathbf{E}}_\tau) + \bar{\sigma}_{\text{I},\tau} \ni 0 \quad \text{with } \bar{\sigma}_{\text{I},\tau} \in \partial \delta_K(\bar{\chi}_\tau), \end{aligned} \quad (5.13b)$$

$$\dot{c}_\tau - \operatorname{div}(\mathbf{M}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau) \nabla \bar{\mu}_\tau) = 0 \quad \text{with } \bar{\mu}_\tau = \partial_c \varphi_{\text{CH}}(\bar{\chi}_\tau, \bar{c}_\tau), \quad (5.13c)$$

$$\begin{aligned} \int_{\Omega} \varphi_{\text{ME/CH}}(\bar{\mathbf{E}}_\tau(t), \bar{\chi}_\tau(t), \bar{d}_\tau(t), \bar{c}_\tau(t)) + \frac{\kappa_2}{2} |\nabla \bar{d}_\tau(t)|^2 \, dx \leq \int_{\Omega} (\varphi_{\text{ME/CH}}(\bar{\mathbf{E}}_\tau(t), \bar{\chi}_\tau(t), \tilde{d}, \bar{c}_\tau(t)) \\ + \frac{\kappa_2}{2} |\nabla \tilde{d}|^2 + \alpha(\bar{\chi}_\tau(t))(\tilde{d} - \bar{d}_\tau(t))) \, dx \quad \forall \tilde{d} \in H^1(\Omega), \quad 0 \leq \tilde{d} \leq \bar{d}_\tau(t) \text{ on } \Omega, \quad \text{for a.a. } t \in I, \end{aligned} \quad (5.13d)$$

$$\dot{w}_\tau - \operatorname{div}(\mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \nabla \bar{\theta}_\tau) = \bar{r}_\tau \quad \text{with } \bar{w}_\tau = e_{\text{TH}}(\bar{\chi}_\tau, \bar{\theta}_\tau) \quad \text{and}$$

$$\text{with } \bar{r}_\tau = (\bar{s}_{\text{d},\tau} + \partial_{\chi} \varphi_{\text{TH}}(\bar{\chi}_\tau, \bar{\theta}_\tau)) \cdot \dot{\chi}_\tau - \alpha(\bar{\chi}_\tau) \dot{d}_\tau + \frac{\mathbb{D} \dot{\mathbf{E}}_\tau : \dot{\mathbf{E}}_\tau}{1 + \tau |\dot{\mathbf{E}}_\tau|^2} + \frac{\mathbf{M}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau) \nabla \bar{\mu}_\tau \cdot \nabla \bar{\mu}_\tau}{1 + \tau |\nabla \bar{\mu}_\tau|^2}, \quad (5.13e)$$

$$\text{where } \bar{s}_{\text{d},\tau} \in \partial_{\bar{\chi}} \zeta(\mathbf{E}_\tau^{k-1}, \chi_\tau^{k-1}, d_\tau^{k-1}, c_\tau^{k-1}, \theta_\tau^{k-1}, \mathfrak{d}_\tau^k \chi), \quad (5.13f)$$

$$\begin{aligned}
 & \int_{\Omega} \varphi_{\text{ME/CH}}(\mathbf{E}_{\tau}^k, \chi_{\tau}^k, d_{\tau}^k, c_{\tau}^k) + \frac{\rho}{2} |\dot{\mathbf{u}}_{\tau}^k|^2 + \frac{\kappa_1}{2} |\nabla \chi_{\tau}^k|^2 + \frac{\kappa_2}{2} |\nabla d_{\tau}^k|^2 \, dx \\
 & + \int_0^{k\tau} \int_{\Omega} \left(\mathbb{D} \dot{\mathbf{E}}_{\tau} : \dot{\mathbf{E}}_{\tau} + ((\partial_{\chi} \zeta(\mathbf{E}_{\tau}, \underline{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}, \dot{\chi}_{\tau}) - \sqrt{\tau} \dot{\chi}_{\tau}) + \partial_{\chi} \varphi_{\text{TH}}(\underline{\chi}_{\tau}, \underline{\theta}_{\tau})) \cdot \dot{\chi}_{\tau} - \alpha(\bar{\chi}_{\tau}) \dot{d}_{\tau} \right. \\
 & \left. + \mathbf{M}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}) \nabla \bar{\mu}_{\tau} \cdot \nabla \bar{\mu}_{\tau} \right) \, dx \, dt \leq \int_0^{k\tau} \int_{\Gamma} \bar{\mathbf{f}}_{s,\tau} \cdot \dot{\mathbf{u}}_{\tau} + q_{s,\tau} + \bar{\mu}_{\tau} \bar{h}_{s,\tau} \, dS + \mathcal{E}_{\text{MC}}(0), \tag{5.13g}
 \end{aligned}$$

holding for any $k = 0, \dots, T/\tau$, together with the corresponding boundary conditions

$$(\partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}) + \mathbb{D} \dot{\mathbf{E}}_{\tau}) \mathbf{n} = \bar{\mathbf{f}}_{s,\tau}, \tag{5.14a}$$

$$\nabla \chi_{\tau} \cdot \mathbf{n} = 0, \tag{5.14b}$$

$$\mathbf{M}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}) \nabla \bar{\mu}_{\tau} \cdot \mathbf{n} = \bar{h}_{s,\tau}, \tag{5.14c}$$

$$(\mathbf{K}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \bar{d}_{\tau}, \bar{c}_{\tau}, \bar{\theta}_{\tau}) \nabla \bar{\theta}_{\tau}) \cdot \mathbf{n} = \bar{q}_{s,\tau}. \tag{5.14d}$$

Note that the arguments of the function $\varphi_{\text{ME/CH}}$ at the two sides of the inequality (5.13d) are not the same.

The discrete semi-stability (5.13d) has been obtained from minimizing (5.3) by comparing a solution d_{τ}^k against \tilde{d} and using the triangle inequality for $\xi(\chi_{\tau}^k, \cdot)$; here the positive degree 1 homogeneity of $\xi(\chi, \cdot)$ is used. Note that we just choose one global minimizer d_{τ}^k of (5.3) from possibly many, if $\varphi_{\text{ME}}(\mathbf{E}, \chi, \cdot)$ is not convex. The energy inequality (5.13g) which we will prove in Lemma 5.3 below is an analogue of the mechanical/chemical energy (4.9f) over the time interval $[0, k\tau]$ and without making the by-part integration like (4.12). Note also the term $\sqrt{\tau} |\dot{\chi}_{\tau}|^2$ in (5.13g) which facilitates handling of non-convex energies φ_{ME} as admitted by the semi-convexity assumption (4.1i) but which disappears in the limit for $\tau \rightarrow 0$, cf. [46, Rem. 8.24] for this trick.

Lemma 5.3. (First estimates) *Let again the assumptions of Lemma 5.1 hold. Then the mechano-chemical energy inequality (5.13g) holds and the following estimates hold uniformly with respect to the time step provided $\tau \leq \min(1/M^2, T, 4\epsilon^2)$ with M from (4.1i) (or simply $\tau \leq T$ if $M = 0$):*

$$\|\mathbf{u}_{\tau}\|_{W^{1,\infty}(I;L^2(\Omega;\mathbb{R}^3)) \cap H^1(I;H^1(\Omega;\mathbb{R}^3))} \leq C, \tag{5.15a}$$

$$\|\mathbf{E}_{\tau}\|_{L^{\infty}(I;L^2(\Omega;\mathbb{R}^3))} \tag{5.15b}$$

$$\|\chi_{\tau}\|_{L^{\infty}(I;H^1(\Omega;\mathbb{R}^N)) \cap H^1(I;L^2(\Omega;\mathbb{R}^N)) \cap L^{\infty}(Q;\mathbb{R}^N)} \leq C, \tag{5.15c}$$

$$\|c_{\tau}\|_{L^2(I;H^1(\Omega))} \leq C, \tag{5.15d}$$

$$\|\mu_{\tau}\|_{L^2(I;H^1(\Omega))} \leq C, \tag{5.15e}$$

$$\|d_{\tau}\|_{L^{\infty}(I;H^1(\Omega)) \cap \text{BV}(I;L^1(\Omega)) \cap L^{\infty}(Q)} \leq C, \tag{5.15f}$$

$$\|w_{\tau}\|_{L^{\infty}(I;L^1(\Omega))} \leq C. \tag{5.15g}$$

Moreover, for every $1 \leq r < \frac{5}{4}$ there exists $C_r > 0$, independent of τ , such that

$$\|\nabla w_{\tau}\|_{L^r(Q;\mathbb{R}^3)} \leq C_r, \tag{5.15h}$$

$$\|\nabla \theta_{\tau}\|_{L^r(Q;\mathbb{R}^3)} \leq C_r, \tag{5.15i}$$

$$\|w_{\tau}\|_{L^{r/(2-r)}(Q)} \leq C_r, \tag{5.15j}$$

$$\|\theta_{\tau}\|_{L^{r/(2-r)}(Q)} \leq C_r. \tag{5.15k}$$

Proof. The strategy is to test the particular equations in (5.1)–(5.4), respectively, by $\mathfrak{d}_\tau^k \mathbf{u}$, $\mathfrak{d}_\tau^k \chi$, μ_τ^k , $\mathfrak{d}_\tau^k d$, and $\frac{1}{2}$. For (5.1a,b), we note that a standard argument using convexity of $(\mathbf{E}, \chi) \mapsto \varphi_{\text{ME/CH}}(\mathbf{E}, \chi, c, d) + \delta_K(\chi)$ composed with the linear mapping $(\mathbf{u}, \chi) \mapsto \mathbf{E}$, and of $\dot{\chi} \mapsto \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi})$ yields:

$$\begin{aligned}
& \int_{\Omega} \varrho |\mathfrak{d}_\tau^k|^2 \mathbf{u} \cdot \mathfrak{d}_\tau^k \mathbf{u} + (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}) + \mathbb{D} \mathfrak{d}_\tau^k \mathbf{E}_\tau^k) : \varepsilon(\mathfrak{d}_\tau^k \mathbf{u}) \\
& + (\partial_{\dot{\chi}} \zeta(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k, c_\tau^k, \theta_\tau^k, \mathfrak{d}_\tau^k \chi) + \partial_\chi \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^{k-1}) \\
& - \mathbb{E}^\top : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}) + \mathbb{D} \mathfrak{d}_\tau^k \mathbf{E}_\tau^k) + \sigma_{\mathbf{r}, \tau}^k \cdot \mathfrak{d}_\tau^k \chi + \kappa_1 \nabla \chi_\tau^k : \nabla \mathfrak{d}_\tau^k \chi \, dx \\
& \geq \int_{\Omega} \mathbb{D} \mathfrak{d}_\tau^k \mathbf{E}_\tau : (\varepsilon(\mathfrak{d}_\tau^k \mathbf{u}) - \mathbb{E} \mathfrak{d}_\tau^k \chi) + s_{\mathbf{d}, \tau}^k + \partial_\chi \varphi_{\text{TH}}(\chi_\tau^{k-1}, \theta_\tau^{k-1}) \mathfrak{d}_\tau^k \chi \\
& + \frac{\varrho}{2} |\mathfrak{d}_\tau^k \mathbf{u}|^2 + \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^{k-1}) + \frac{\kappa_1}{2} |\nabla \chi_\tau^k|^2 + \delta_K(\chi_\tau^k) \\
& - \frac{\varrho}{2} |\mathfrak{d}_\tau^{k-1} \mathbf{u}|^2 - \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^{k-1}, \chi_\tau^{k-1}, d_\tau^{k-1}, c_\tau^{k-1}) - \frac{\kappa_1}{2} |\nabla \chi_\tau^{k-1}|^2 - \delta_K(\chi_\tau^{k-1}) \, dx. \tag{5.16}
\end{aligned}$$

Note that $\partial_{\mathbf{E}} \varphi_{\text{ME}} = \partial_{\mathbf{E}} \varphi_{\text{ME/CH}}$, since the chemical part of the free energy does not depend on strain. Further, we execute the test of (5.2) relying on the convexity of $c \mapsto \varphi_{\text{CH}}(\chi, c)$

$$\begin{aligned}
\int_{\Gamma} h_{\mathbf{s}, \tau}^k \mu_\tau^k \, dS &= \int_{\Omega} \mu_\tau^k \mathfrak{d}_\tau^k c + \mathbf{M}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^k, \theta_\tau^{k-1}) \nabla \mu_\tau^k \cdot \nabla \mu_\tau^k \, dx \\
&\geq \int_{\Omega} \varphi_{\text{CH}}(\chi_\tau^k, c_\tau^k) - \varphi_{\text{CH}}(\chi_\tau^k, c_\tau^{k-1}) + \mathbf{M}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^k, \theta_\tau^{k-1}) \nabla \mu_\tau^k \cdot \nabla \mu_\tau^k \, dx. \tag{5.17}
\end{aligned}$$

Moreover, we test (5.3) with d_τ^{k-1} to obtain

$$\int_{\Omega} \varphi_{\text{ME}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k) + \frac{\kappa_2}{2} |\nabla d_\tau^k|^2 \, dx \leq \int_{\Omega} \varphi_{\text{ME}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}) + \frac{\kappa_2}{2} |\nabla d_\tau^{k-1}|^2 - \alpha(\chi_\tau^k) (d_\tau^k - d_\tau^{k-1}) \, dx. \tag{5.18}$$

Relying on the semiconvexity (4.1i) of the mechano-chemical part $\varphi_{\text{ME/CH}}$ of the free energy (see the argument in [46, Rem. 8.24]) and adding (5.16), (5.17), and (5.18), and recalling that $\varphi_{\text{ME/CH}} = \varphi_{\text{ME}} + \varphi_{\text{CH}}$, we benefit with the telescopic cancellation of the terms $\pm \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^k)$ and $\pm \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^{k-1}, c_\tau^{k-1})$, and we obtain the following mechano-chemical energy balance:

$$\begin{aligned}
& \int_{\Omega} \frac{\varrho}{2} |\mathfrak{d}_\tau^k \mathbf{u}|^2 + \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k, c_\tau^k) + \frac{\kappa_2}{2} |\nabla d_\tau^k|^2 + \frac{\kappa_1}{2} |\nabla \chi_\tau^k|^2 + \delta_K(\chi_\tau^k) + \delta_{[0,1]}(d_\tau^k) \, dx \\
& + \tau \sum_{j=1}^k \int_{\Omega} \mathbb{D} \mathfrak{d}_\tau^j \mathbf{E} : \mathfrak{d}_\tau^j \mathbf{E} + (\partial_{\dot{\chi}} \zeta(\mathbf{E}_\tau^{j-1}, \chi_\tau^{j-1}, d_\tau^{j-1}, c_\tau^{j-1}, \theta_\tau^{j-1}, \mathfrak{d}_\tau^j \chi) - \sqrt{\tau} \mathfrak{d}_\tau^j \chi) \cdot \mathfrak{d}_\tau^j \chi \\
& - \alpha(\chi_\tau^j) \cdot \mathfrak{d}_\tau^j d + \mathbf{M}(\mathbf{E}_\tau^{j-1}, \chi_\tau^{j-1}, d_\tau^{j-1}, c_\tau^{j-1}, \theta_\tau^{j-1}) \nabla \mu_\tau^j \cdot \nabla \mu_\tau^j \, dx \, dt \\
& \leq \int_{\Omega} \left(\frac{\varrho}{2} |\mathbf{v}_0|^2 + \varphi_{\text{ME/CH}}(\mathbf{E}_0, \chi_0, d_0, c_0) + \frac{\kappa_2}{2} |\nabla d_0|^2 + \frac{\kappa_1}{2} |\nabla \chi_0|^2 \right) dx \\
& + \tau \sum_{j=1}^k \left(\int_{\Omega} \mathbf{f}_\tau^j \cdot \mathfrak{d}_\tau^j \mathbf{u} \mathfrak{d}_\tau^j \chi \, dx + \int_{\Gamma} \mathbf{f}_{\mathbf{s}, \tau}^j \cdot \mathfrak{d}_\tau^j \mathbf{u} + h_{\mathbf{s}, \tau}^j \cdot \mu_\tau^j \, dS \right).
\end{aligned}$$

We also used that $\delta_K(\chi_0) + \delta_{[0,1]}(d_0) = 0$. This proves (5.13g).

Finally, we test the heat equation (5.4) by $1/2$, and we add the resulting equation to (5.16)–(5.18). This is not a physical test (which would be by 1 instead of $1/2$) and thus, in this summation, the adiabatic terms do not cancel out. This scenario simplifies the implicit discretization to let it decoupled by using θ_τ^{k-1} in φ_{TH} in (5.1b) instead of θ_τ^k and also it allows us to estimate w with the other variables simultaneously, but it forces more restrictive assumption on the growth of heat capacity than physically necessary, i.e. the adiabatic terms (i.e. here only $\partial_\chi \varphi_{\text{TH}}(\chi, \theta) \cdot \dot{\chi}$) are in a smaller Lebesgue space than the physically natural $L^1(Q)$ -space, cf. also [46, Exercise 12.9]. Upon summing over k , we arrive at the following estimate:

$$\begin{aligned} & \int_\Omega \frac{1}{2} w_\tau^k + \frac{\varrho}{2} |\mathfrak{d}_\tau^k \mathbf{u}|^2 + \varphi_{\text{ME/CH}}(\mathbf{E}_\tau^k, \chi_\tau^k, d_\tau^k, c_\tau^k) + \frac{\kappa_2}{2} |\nabla d_\tau^k|^2 + \frac{\kappa_1}{2} |\nabla \chi_\tau^k|^2 + \delta_K(\chi_\tau^k) + \delta_{[0,1]}(d_\tau^k) \, dx \\ & + \tau \sum_{j=1}^k \int_\Omega \mathbb{D} \mathfrak{d}_\tau^j \mathbf{E} : \mathfrak{d}_\tau^j \mathbf{E} + \partial_\chi \zeta(\mathbf{E}_\tau^{j-1}, \chi_\tau^{j-1}, d_\tau^{j-1}, c_\tau^{j-1}, \theta_\tau^{j-1}, \mathfrak{d}_\tau^j \chi) \cdot \mathfrak{d}_\tau^j \chi \\ & - \alpha(\chi_\tau^j) \cdot \mathfrak{d}_\tau^j d + \frac{1}{2} \mathbf{M}(\mathbf{E}_\tau^j, \chi_\tau^j, d_\tau^{j-1}, c_\tau^{j-1}, \theta_\tau^{j-1}) \nabla \mu_\tau^j \cdot \nabla \mu_\tau^j \, dx dt \\ & \leq \int_\Omega \left(\frac{1}{2} e_{\text{TH}}(\chi_0, \theta_0) + \frac{\varrho}{2} |\mathbf{v}_0|^2 + \varphi_{\text{CH}}(\chi_0, c_0) + \varphi_{\text{ME}}(\mathbf{E}_0, d_0, c_0) + \frac{\kappa_2}{2} |\nabla d_0|^2 + \frac{\kappa_1}{2} |\nabla \chi_0|^2 \right) dx \\ & + \tau \sum_{j=1}^k \left(\int_\Omega \mathbf{f}_\tau^j \cdot \mathfrak{d}_\tau^j \mathbf{u} + \left(\frac{1}{2} \partial_\chi \varphi_{\text{TH}}(\chi_\tau^j, \theta_\tau^j) - \partial_\chi \varphi_{\text{TH}}(\chi_\tau^{j-1}, \theta_\tau^{j-1}) \right) \mathfrak{d}_\tau^j \chi \, dx \right. \\ & \left. + \int_\Gamma \mathbf{f}_{s,\tau}^j \cdot \mathfrak{d}_\tau^j \mathbf{u} + h_{s,\tau}^j \cdot \mu_\tau^j + \frac{1}{2} q_{s,\tau}^j \, dS \right). \end{aligned}$$

Using (4.1q) and Holder’s and Young’s inequalities, followed by the discrete Gronwall lemma, we see that the left-hand side in the above inequality is bounded uniformly with respect to t for all $k = 1, \dots, T/\tau$. We therefore obtain the following bounds:

$$\|\dot{\mathbf{u}}_\tau\|_{L^\infty(I; L^2(\Omega; \mathbb{R}^3))} \leq C, \tag{5.19a}$$

$$\|\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau)\|_{L^\infty(I; L^1(\Omega))} \leq C, \tag{5.19b}$$

$$\|\varphi_{\text{CH}}(\bar{\chi}_\tau, \bar{c}_\tau)\|_{L^\infty(I; L^1(\Omega))} \leq C, \tag{5.19c}$$

$$\|\nabla \chi_\tau\|_{L^\infty(I; L^2(\Omega; \mathbb{R}^{N \times 3}))} \leq C, \tag{5.19d}$$

$$\|\nabla d_\tau\|_{L^\infty(I; L^2(\Omega; \mathbb{R}^3))} \leq C, \tag{5.19e}$$

$$\chi_\tau \in K \text{ a.e. in } Q, \tag{5.19f}$$

$$\|\dot{\mathbf{E}}_\tau\|_{L^2(Q; \mathbb{R}^{3 \times 3})} \leq C, \tag{5.19g}$$

$$\|\dot{\chi}_\tau\|_{L^2(Q; \mathbb{R}^N)} \leq C, \tag{5.19h}$$

$$\|\dot{d}_\tau\|_{L^1(Q)} \leq C, \tag{5.19i}$$

$$\|\nabla \mu_\tau\|_{L^2(Q; \mathbb{R}^3)} \leq C, \tag{5.19j}$$

along with (5.15g). From (5.19b), and (4.1d) we immediately obtain the a priori estimate (5.15b). Furthermore, from (5.19d,h) we get (5.15c). From (5.19e,i), combined with the initial condition for d contained in (4.11b), and from the monotonicity of d (see Step 3 of the discretization scheme at the beginning of this section), we obtain the bound (5.15f) on the damage variable. Moreover, since $\varepsilon(\dot{\mathbf{u}}_\tau) = \dot{\mathbf{E}}_\tau + \mathbb{E} \dot{\chi}_\tau \in L^2(Q; \mathbb{R}^{3 \times 3})$, estimates (5.19g,h) and Korn’s inequality entail

$$\|\nabla \dot{\mathbf{u}}_\tau\|_{L^2(Q; \mathbb{R}^{3 \times 3})} \leq C. \tag{5.20}$$

Estimate (5.15a) is now recovered from (5.16) and (5.20). Next, from (5.2b) taking a gradient of $\bar{\mu}_\tau = \partial_{c'}\varphi_{\text{CH}}(\bar{\chi}_\tau, \bar{c}_\tau)$, cf. (5.13c), and using the strong convexity assumption (4.1j), we obtain the following estimate on concentration gradient:

$$\nabla \bar{c}_\tau = [\partial_{cc}^2\varphi_{\text{CH}}(\bar{\chi}_\tau, \bar{c}_\tau)]^{-1}(\nabla \bar{\mu}_\tau - \partial_{c\chi}^2\varphi_{\text{CH}}(\bar{\chi}_\tau, \bar{c}_\tau)\nabla \bar{\chi}_\tau), \tag{5.21}$$

and hence, by (4.1b, j, p), (5.19d, j), and (5.15e), we obtain

$$\|\nabla c_\tau\|_{L^2(Q;\mathbb{R}^3)} \leq C. \tag{5.22}$$

Because of the coercivity assumption in (4.1g), the bounds (5.19c) and (5.22) imply (5.15d). Using the assumption (4.1l), we obtain the bound of μ_τ in $L^\infty(I; L^1(\Omega))$, and combining it with (5.19j) we obtain (5.15e).

It remains for us to prove (5.15h)–(5.15k). Let us fix $r \in [1, 5/4)$ and let us set

$$\phi(\omega) = \frac{1 + \omega - (1 + \omega)^{1-\eta}}{\eta(1 - \eta)} \quad \text{with} \quad \eta = \frac{5 - 4r}{3}. \tag{5.23}$$

We are going to exploit the following properties of ϕ :

$$\forall \omega \geq 0: \quad \phi(\omega) \geq 0, \quad \phi'(\omega) \leq C, \quad 0 < \epsilon \leq \phi''(\omega) < \frac{1}{1 + \omega}, \tag{5.24a}$$

$$\limsup_{\omega \rightarrow +\infty} \frac{1}{\phi''(\omega)\omega^{1+\eta}} \leq C. \tag{5.24b}$$

By the second inequality in (5.24a), the function $\phi'(\bar{w}_\tau)$ is in $L^\infty(Q)$ and hence it is a legal test for (5.13f), whose right-hand side \bar{r}_τ is in $L^1(Q)$. By performing this test, and by exploiting the convexity of ϕ we arrive at:

$$\int_{\Omega} \phi(\bar{w}_\tau(T)) \, dx + \int_Q \phi''(\bar{w}_\tau) \mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \nabla \bar{\theta}_\tau \cdot \nabla \bar{w}_\tau \, dx \, dt \leq C. \tag{5.25}$$

From the equation in the third line of (5.13f), recalling from (4.5) that $w \mapsto \vartheta(\chi, w)$ is the inverse of $\theta \mapsto e_{\text{TH}}(\chi, \theta)$, we obtain

$$\bar{\theta}_\tau = \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \tag{5.26}$$

a.e. in Q . Furthermore, since $\bar{w}_\tau(t) \in H^1(\Omega)$ and $\bar{\chi}_\tau(t) \in H^1(\Omega; \mathbb{R}^N)$, by the chain rule for Sobolev functions, Eq. (5.26) together with assumptions (4.6) and (4.7) implies that $\bar{\theta}_\tau(\cdot, t) \in H^1(\Omega)$ for all $t \in (0, T)$ with

$$\nabla \bar{\theta}_\tau = \partial_\chi \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{\chi}_\tau + \partial_w \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{w}_\tau \tag{5.27}$$

holding a.e. in Q .

Now, by (4.1k) and (4.6), we have

$$\phi''(\bar{w}_\tau) \mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \partial_w \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{w}_\tau \cdot \nabla \bar{w}_\tau \geq \epsilon_1 \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2, \tag{5.28}$$

with some $\epsilon_1 > 0$. Moreover, using, in the order, Holder’s and Young’s inequalities, the last inequality in (5.24a), the last line of (5.13f), and (4.5), we obtain, for δ sufficiently small,

$$\begin{aligned} & \phi''(\bar{w}_\tau) \mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \partial_\chi \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{\chi}_\tau \cdot \nabla \bar{w}_\tau \\ & \geq -\frac{1}{2\delta} \phi''(\bar{w}_\tau) |\mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \partial_\chi \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{\chi}_\tau|^2 - \frac{\delta}{2} \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2 \end{aligned}$$

$$\begin{aligned} &\geq -\frac{1}{2\delta} \left| \frac{\mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \partial_\chi \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{\chi}_\tau}{\sqrt{1 + \bar{w}_\tau}} \right|^2 - \frac{\delta}{2} \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2 \\ &= -\frac{1}{2\delta} \left| \frac{\mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \partial_\chi e_\vartheta(\bar{\chi}_\tau, \bar{\theta}_\tau) \nabla \bar{\chi}_\tau}{\partial_\theta e_{\text{TH}}(\bar{\chi}_\tau, \bar{\theta}_\tau) \sqrt{1 + e_{\text{TH}}(\bar{\chi}_\tau, \bar{\theta}_\tau)}} \right|^2 - \frac{\delta}{2} \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2. \end{aligned} \tag{5.29}$$

The above chain of inequalities, combined with Assumption (4.1r) and with the lower bound in (4.4) yields:

$$\phi''(\bar{w}_\tau) \mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \partial_\chi \vartheta(\bar{\chi}_\tau, \bar{w}_\tau) \nabla \bar{\chi}_\tau \cdot \nabla \bar{w}_\tau \geq -\frac{C}{\delta} |\nabla \bar{\chi}_\tau|^2 - \frac{\delta}{2} \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2. \tag{5.30}$$

By combining (5.27) with (5.29), and (5.28), we arrive at

$$\phi''(\bar{w}_\tau) \mathbf{K}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \bar{d}_\tau, \bar{c}_\tau, \bar{\theta}_\tau) \nabla \bar{\theta}_\tau \cdot \nabla \bar{w}_\tau \geq (1 - \delta) \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2 - \frac{C}{\delta} |\nabla \bar{\chi}_\tau|^2. \tag{5.31}$$

Since ϕ is bounded from below, see (5.24a), and since $\nabla \bar{d}_\tau$ and $\nabla \bar{\chi}_\tau$ are bounded in $L^2(Q)$, see (5.19d,e), it follows from (5.25) and (5.31) that

$$\int_Q \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2 \, dx \, dt \leq C. \tag{5.32}$$

Now, by Holder’s inequality and by (5.24b) we have the bound

$$\begin{aligned} \int_Q |\nabla \bar{w}_\tau|^r \, dx \, dt &\leq \left(\int_Q \phi''(\bar{w}_\tau) |\nabla \bar{w}_\tau|^2 \, dx \, dt \right)^{r/2} \left(\int_Q \left(\frac{1}{\phi''(\bar{w}_\tau)^{r/2}} \right)^{2/(2-r)} \, dx \, dt \right)^{1-r/2} \\ &\leq C \left(1 + \int_Q |\bar{w}_\tau|^{(2-r)r/(1+\eta)} \, dt \right)^{1-r/2}. \end{aligned} \tag{5.33}$$

Now, let us set $\lambda = \frac{2-r}{1+\eta}$. The choice (5.23) for η entails that $\frac{\lambda}{r} = 1 - \lambda + \frac{\lambda}{r^*}$, with $r^* = \frac{3r}{3-r}$ the exponent of the Sobolev embedding $L^{r^*}(\Omega) \subset W^{1,r}(\Omega)$. Thus, a standard interpolation argument based on Holder’s inequality entails $\|\bar{w}_\tau\|_{L^{r(1+\eta)/(2-r)}(\Omega)} = \|\bar{w}_\tau\|_{L^{r/\lambda}(\Omega)} \leq \|\bar{w}_\tau\|_{L^1(\Omega)}^{1-\lambda} \|\bar{w}_\tau\|_{L^{r^*}(\Omega)}^\lambda = \|\bar{w}_\tau\|_{L^1(\Omega)}^{r(1+\eta)/(2-r)} \|\bar{w}_\tau\|_{L^{r^*}(\Omega)}^{(2-r)/(1+\eta)}$. Hence, the Sobolev embedding and Poincaré’s inequality yield

$$\|\bar{w}_\tau\|_{L^{r(1+\eta)/(2-r)}(\Omega)} \leq C \|\bar{w}_\tau\|_{L^1(\Omega)}^{(r-1+\eta)/(1+\eta)} \left(\|\bar{w}_\tau\|_{L^1(\Omega)} + \|\nabla \bar{w}_\tau\|_{L^r(\Omega)} \right)^{(2-r)/(1+\eta)}.$$

Thus, on taking into account the bound $\|\bar{w}_\tau\|_{L^\infty(I;L^1(\Omega))} \leq C$, which has already been established, we obtain $\int_Q |\nabla \bar{w}_\tau|^r \, dx \, dt \leq C(1 + \int_Q |\nabla \bar{w}_\tau|^r \, dx \, dt)^{1-r/2}$, whence (5.15h) and thence (5.15j). Finally, thanks to the boundedness of $\partial_\chi \vartheta$, cf. (4.7), by combining (5.27) with (5.19d-e), we obtain (5.15i). In view of (4.6), from (5.15j) we obtain (5.15k). \square

Lemma 5.4. (Further estimates) *Under the assumption of Lemma 5.1, for some constant C and C_r independent of τ , it also holds:*

$$\|\varrho \ddot{\mathbf{u}}_\tau^i\|_{L^2(I;H^1(\Omega;\mathbb{R}^3)^*)} \leq C, \tag{5.34a}$$

$$\|\dot{w}_\tau\|_{L^1(I;W^{1,r/(r-1)}(\Omega)^*)} \leq C_r \quad \text{with } r \text{ from (4.8e)}, \tag{5.34b}$$

$$\|\dot{c}_\tau\|_{L^2(I;H^1(\Omega)^*)} \leq C, \tag{5.34c}$$

$$\|\Delta\chi_\tau\|_{L^2(Q;\mathbb{R}^N)} \leq C, \tag{5.34d}$$

$$\|\sigma_{r,\tau}\|_{L^2(Q;\mathbb{R}^N)} \leq C, \tag{5.34e}$$

where we recall that $\sigma_{r,\tau}$ is the piecewise affine interpolant of the selections $\sigma_{r,\tau}^k$ in (5.1c).

Proof. The “dual” estimates (5.34a–c) follow by comparison from the time-discrete equations (5.13a, c, e) with the corresponding boundary conditions (5.14a, c, e).

In order to prove the remaining estimate (5.34d, e), we consider a measurable selection $\bar{\sigma}_{d,\tau} \in \partial_d \zeta(\underline{\mathbf{E}}_\tau, \underline{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau, \dot{d}_\tau)$. We notice that, thanks to the growth assumption in (4.1m) and estimate (5.15c), we have $\bar{\sigma}_{d,\tau} \in L^2(Q; \mathbb{R}^N)$. Thus, the equation in (5.13b) can be written as

$$\begin{aligned} \kappa_1 \Delta \bar{\chi}_\tau + \bar{f}_\tau &\in \partial \delta_K(\bar{\chi}_\tau) \text{ with} \\ \bar{f}_\tau &= -\bar{\sigma}_{d,\tau} - \partial_{\chi} \varphi_{\text{CH}}(\bar{\chi}_\tau, \underline{c}_\tau) - \partial_{\chi} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) - \partial_{\chi} \varphi_{\text{TH}}(\underline{\chi}_\tau, \underline{d}_\tau, \underline{\theta}_\tau) \in L^2(Q; \mathbb{R}^N). \end{aligned} \tag{5.35}$$

The estimate (5.34d) can be obtained by testing (5.35) by $\Delta \bar{\chi}_\tau$ and using $\int_{\Omega} \partial \delta_K(\bar{\chi}_\tau) \Delta \bar{\chi}_\tau \, dx \leq 0$ when counting also the homogeneous boundary conditions.

At this stage, (5.13b) is understood in the weak sense, so that $\Delta \bar{\chi}_\tau$ (and hence also $\bar{\sigma}_{r,\tau}$) are elements of $H^1(\Omega; \mathbb{R}^N)^*$. A rigorous proof is to be made by the Yosida regularization of δ_K and a subsequent limit passage; we refer e.g. to [1] or also [48] for technical details. The bound (5.34e) then follows by comparison. \square

Proposition 5.5. (Convergence for $\tau \rightarrow 0$) *Let again the assumption of Lemma 5.1 hold and let Ω be smooth. Then there is a subsequence such that*

$$\mathbf{u}_\tau \rightarrow \mathbf{u} \quad \text{strongly in } H^1(I; H^1(\Omega; \mathbb{R}^3)), \tag{5.36a}$$

$$\chi_\tau \rightarrow \chi \quad \text{strongly in } H^1(I; L^2(\Omega; \mathbb{R}^N)) \cap C(\bar{Q}; \mathbb{R}^N), \tag{5.36b}$$

$$\bar{c}_\tau \rightarrow c \quad \& \quad \underline{c}_\tau \rightarrow c \quad \text{strongly in } L^2(Q), \tag{5.36c}$$

$$\bar{d}_\tau(t) \rightarrow \bar{d}(t) \quad \text{weakly in } H^1(\Omega) \quad \forall t \in I, \tag{5.36d}$$

$$\dot{d}_\tau \rightarrow \dot{d} \quad \text{weakly* in } \text{Meas}(\bar{Q}) \cong C(\bar{Q})^*, \tag{5.36e}$$

$$\bar{\theta}_\tau \rightarrow \theta, \quad \underline{\theta}_\tau \rightarrow \theta \quad \text{strongly in } L^s(Q) \text{ with any } 1 \leq s < 5/3, \tag{5.36f}$$

$$\bar{\mu}_\tau \rightarrow \mu \quad \text{strongly in } L^2(I; H^1(\Omega)), \tag{5.36g}$$

$$\bar{w}_\tau \rightarrow w \quad \& \quad \underline{w}_\tau \rightarrow w \quad \text{strongly in } L^s(Q) \text{ with any } 1 \leq s < 5/3, \tag{5.36h}$$

and any $(\mathbf{u}, \chi, c, d, \theta, \mu, w)$ obtained in this way is a weak solution to the initial-boundary-value problem (3.7)–(3.9) according Definition 4.1 which also preserves the total energy in the sense (4.13).

Proof. For clarity of exposition, we divide the proof to eleven particular steps.

Step 1: Selection of a converging subsequence. By Banach’s selection principle, we select a weakly* converging subsequence with respect to the norms from estimates (5.15) and (5.34), namely,

$$\mathbf{u}_\tau \rightarrow \mathbf{u} \quad \text{weakly* in } W^{1,\infty}(I; L^2(\Omega; \mathbb{R}^3)) \cap H^1(I; H^1(\Omega; \mathbb{R}^3)) \tag{5.37a}$$

$$\mathbf{E}_\tau \rightarrow \mathbf{E} \quad \text{weakly in } H^1(I; L^2(\Omega; \mathbb{R}^{3 \times 3})) \tag{5.37b}$$

$$\chi_\tau \rightarrow \chi \quad \text{weakly* in } L^\infty(I; H^1(\Omega; \mathbb{R}^N)) \cap H^1(I; L^2(\Omega; \mathbb{R}^N)) \cap L^\infty(Q; \mathbb{R}^N), \tag{5.37c}$$

$$c_\tau \rightarrow c \quad \text{weakly in } L^2(I; H^1(\Omega)), \tag{5.37d}$$

$$\dot{c}_\tau \rightarrow \dot{c} \quad \text{weakly in } L^2(I; H^1(\Omega)^*), \tag{5.37e}$$

$$\mu_\tau \rightharpoonup \mu \quad \text{weakly in } L^2(I; H^1(\Omega)), \tag{5.37f}$$

$$d_\tau \rightharpoonup d \quad \text{weakly}^* \text{ in } L^2(I; H^1(\Omega)) \cap L^\infty(Q), \tag{5.37g}$$

$$\bar{\sigma}_{r,\tau} \rightharpoonup \sigma_r \quad \text{weakly in } L^2(Q; \mathbb{R}^N), \tag{5.37h}$$

and also (5.36e). Here $\bar{\sigma}_{r,\tau}$ is the piecewise-constant interpolant of the selection $\sigma_{r,\tau}^k$ appearing in (5.1c). Moreover, by the BV-estimate (5.15f) and by Helly's selection principle, we can rely also on (5.36d) for a subsequence. We introduce the shorthand notation

$$\mathbf{v}_\tau = [\dot{\mathbf{u}}_\tau]^i \quad \text{and} \quad \bar{\mathbf{v}}_\tau = \dot{\mathbf{u}}_\tau. \tag{5.38}$$

We also define $t_\tau := t - \tau[t/\tau]$. Then, we have $\bar{\mathbf{v}}_\tau - \mathbf{v}_\tau = (\tau - t_\tau)\dot{\mathbf{v}}_\tau$. Moreover,

$$\begin{aligned} \int_0^T \int_\Omega |\bar{\mathbf{v}}_\tau - \mathbf{v}_\tau|^2 dx dt &= \int_0^T \int_\Omega (\tau - t_\tau)(\bar{\mathbf{v}}_\tau - \mathbf{v}_\tau) \cdot \dot{\mathbf{v}}_\tau dx dt \\ &\leq \tau \|\mathbf{v}_\tau - \bar{\mathbf{v}}_\tau\|_{L^2(I; H^1(\Omega; \mathbb{R}^3))} \|\dot{\mathbf{v}}_\tau\|_{L^2(I; H^1(\Omega; \mathbb{R}^3)^*)} \rightarrow 0. \end{aligned} \tag{5.39}$$

By (5.37a), $\bar{\mathbf{v}}_\tau \rightharpoonup \dot{\mathbf{u}}$ weakly in $L^2(I; H^1(\Omega; \mathbb{R}^3))$. Thus, (5.39) implies that also $\mathbf{v}_\tau \rightharpoonup \dot{\mathbf{u}}$ weakly* in $L^2(I; H^1(\Omega; \mathbb{R}^3))$. On taking into account that $\ddot{\mathbf{u}}_\tau^i = \dot{\mathbf{v}}_\tau$ and using a standard argument to identify time derivatives (see for instance [46, Theorem 8.9]), we arrive at

$$\ddot{\mathbf{u}}_\tau^i \rightharpoonup \ddot{\mathbf{u}} \quad \text{weakly in } L^2(I; H^1(\Omega; \mathbb{R}^3)^*). \tag{5.40}$$

By Rellich's theorem we have the continuous and the compact embeddings $H^1(I; L^2(\Omega)) \cap L^\infty(I; H^1(\Omega)) \subset H^1(Q) \Subset L^2(Q)$ so that (5.37c,f) imply

$$\chi_\tau \rightarrow \chi \quad \text{strongly in } L^2(Q; \mathbb{R}^N). \tag{5.41a}$$

Again, arguing as (5.39), we have that $\|\bar{\chi}_\tau - \chi_\tau\|_{L^2(Q; \mathbb{R}^N)} \rightarrow 0$ and similarly also for $\underline{\chi}_\tau$, cf. [46, Remark 8.10], hence

$$\bar{\chi}_\tau \rightarrow \chi \text{ and } \underline{\chi}_\tau \rightarrow \chi \quad \text{strongly in } L^2(Q; \mathbb{R}^N). \tag{5.41b}$$

Using the Aubin-Lions theorem with estimates (5.15d) and (5.34c), we obtain, for a subsequence,

$$c_\tau \rightarrow c \quad \text{strongly in } L^2(I; L^q(\Omega)) \quad \forall 1 \leq q < 6. \tag{5.42}$$

Moreover, we have $\int_0^T \int_\Omega |c_\tau - \underline{c}_\tau|^2 dx dt \leq \tau \|\dot{c}_\tau\|_{L^2(I; H^1(\Omega)^*)} \|c_\tau - \underline{c}_\tau\|_{L^2(I; H^1(\Omega))} \rightarrow 0$ and similarly also for \bar{c}_τ . Hence,

$$\bar{c}_\tau \rightarrow c \text{ and } \underline{c}_\tau \rightarrow c \quad \text{strongly in } L^2(Q). \tag{5.43}$$

Similarly, by using the generalized Aubin-Lions theorem relying on the boundedness of $\{\dot{\mathbf{d}}_\tau\}_{\tau>0}$ in $\text{Meas}(I; L^1(\Omega))$, see [46, Corollary 7.9], we also have at disposal

$$\underline{\mathbf{d}}_\tau \rightarrow \mathbf{d} \quad \text{strongly in } L^2(Q). \tag{5.44}$$

Now, let $1 \leq r < 5/4$ and $1 \leq q < r^* = \frac{3r}{3-r}$. Then $L^q(\Omega)$ is compactly embedded in $W^{1,r}(\Omega)$. By (5.15h) and (5.15j), we have that $\|w_\tau\|_{L^r(I; W^{1,r}(\Omega))} \leq C$. Thus, by (5.34b), thanks to the Aubin-Lions Lemma, there exists a subsequence such that $\|w_\tau - w\|_{L^r(I; L^q(\Omega))} \rightarrow 0$. Now, for any such q and r , let $\lambda(r, q) = (1 + \frac{1}{r} - \frac{1}{q})^{-1}$. Then, we have $\frac{\lambda(r, q)}{r} = 1 - \lambda(r, q) + \frac{\lambda(r, q)}{q}$. Therefore, by interpolating between $L^\infty(I; L^1(\Omega))$ and $L^r(I; L^q(\Omega))$ (see [46, Proposition 1.41]), we have the inequality $\|w_\tau - w\|_{L^{r/\lambda(r, q)}(Q)} \leq C \|w_\tau - w\|_{L^\infty(I; L^1(\Omega))}^{1-\lambda(r, q)} \|w_\tau - w\|_{L^r(I; L^q(\Omega))}^{\lambda(r, q)}$. Now, for $1 \leq r < 5/4$ fixed, we have $\inf_{1 \leq q < r^*} \lambda(r, q) = (1 + \frac{1}{r} - \frac{1}{r^*})^{-1} = (1 + \frac{1}{r} - \frac{3-r}{3r})^{-1} = \frac{3}{4}$. Thus, $\sup_{\substack{1 \leq r < 5/4 \\ 1 \leq q < r^*}} \frac{r}{\lambda(r, q)} = 5/3$. This gives

$$w_\tau \rightarrow w \text{ strongly in } L^s(Q) \quad \text{with any } 1 \leq s < 5/3. \tag{5.45}$$

Next, we observe that $\dot{\bar{w}}_\tau$ is bounded in the space of $W^{1,r/(r-1)}(\Omega)^*$ -valued Radon measures on I , since:

$$\begin{aligned} \|\dot{\bar{w}}_\tau\|_{\text{Meas}(I;W^{1,r/(r-1)}(\Omega)^*)} &= \sup_{\|\varphi\|_{C(I;W^{1,r/(r-1)}(\Omega)^*)}=1} \int_Q \bar{w}_\tau \dot{\varphi} \, dx \, dt \\ &= \sup_{\|\varphi\|_{C(I;W^{1,r/(r-1)}(\Omega)^*)}=1} \sum_{k=1}^{T/\tau} \int_\Omega w_\tau^k (\varphi(k\tau) - \varphi((k-1)\tau)) \, dx \\ &= \sup_{\|\varphi\|_{C(I;W^{1,r/(r-1)}(\Omega)^*)}=1} \int_\Omega w_\tau^{T/\tau} \varphi(T) \\ &\quad - \sum_{k=1}^{T/\tau-1} \int_\Omega (w_\tau^{k+1} - w_\tau^k) \varphi(k\tau) \, dx - w_\tau^1 \varphi(0) \, dx \\ &\leq \|\dot{w}_\tau\|_{L^1(I;W^{1,r/(r-1)}(\Omega)^*)} \leq C, \end{aligned} \tag{5.46}$$

where the last inequality follows from (5.34b). We can now use the generalized version of the Aubin-Lions Lemma in [46, Corollary 7.9] and interpolate with the estimate to conclude that there exists $\bar{w} \in L^s(Q)$ such that

$$\bar{w}_\tau \rightarrow \bar{w} \text{ strongly in } L^s(Q) \quad \text{with any } 1 \leq s < 5/3. \tag{5.47}$$

Thanks to (5.45) and (5.47), in order to prove the first convergence statement in (5.36h) it suffices for us to show that $\bar{w} = w$. To this effect, we argue as in [46, Remark 8.10]:

$$\begin{aligned} \|w_\tau - \bar{w}_\tau\|_{L^1(I;W^{1,r/(r-1)}(\Omega)^*)} &= \sum_{k=1}^{T/\tau} \int_{(k-1)\tau}^k \left\| \frac{t-k\tau}{\tau} (w_\tau^k - w_\tau^{k-1}) \right\|_{W^{1,r/(r-1)}(\Omega)^*} \, dt \\ &= \frac{\tau}{2} \sum_{k=1}^{T/\tau} \|w_\tau^k - w_\tau^{k-1}\|_{W^{1,r/(r-1)}(\Omega)^*} \\ &= \frac{\tau}{2} \sum_{k=1}^{T/\tau} \int_{(k-1)\tau}^k \|\dot{w}_\tau\|_{W^{1,r/(r-1)}(\Omega)^*} \, dt = \frac{\tau}{2} \int_0^T \|\dot{w}_\tau\|_{W^{1,r/(r-1)}(\Omega)^*} \, dt \rightarrow 0, \end{aligned}$$

where we have used the bound (5.34b). The second convergence statement in (5.36h) is arrived at using a similar argument.

In order to obtain the convergences in (5.36f), we invert (5.13f) with respect to $\bar{\theta}_\tau$ to obtain (cf. (4.5)):

$$\bar{\theta}_\tau = \vartheta(\bar{\chi}_\tau, \bar{w}_\tau), \quad \text{and} \quad \underline{\theta}_\tau = \vartheta(\underline{\chi}_\tau, \underline{w}_\tau). \tag{5.48}$$

Then, (5.36f) follows from the already-established convergences (5.36h) and (5.41b) by the continuity of the Nemytskii mapping associated to ϑ .

Step 2: Strong convergence of \bar{E}_τ . In this step we prove:

$$\bar{E}_\tau \rightarrow E \text{ strongly in } L^2(Q; \mathbb{R}^{3 \times 3}). \tag{5.49}$$

Note that we already have the weak convergence. Thus, by (4.3),

$$\epsilon \|\bar{E}_\tau - E\|_{L^2(Q; \mathbb{R}^{3 \times 3})}^2 \leq \int_Q (\partial_E \varphi_{\text{ME}}(\bar{E}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) - \partial_E \varphi_{\text{ME}}(E, \bar{\chi}_\tau, \underline{d}_\tau)) : (\bar{E}_\tau - E) \, dx \, dt$$

$$\begin{aligned}
 &= \int_Q \partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) : (\boldsymbol{\varepsilon}(\bar{\mathbf{u}}_\tau) - \boldsymbol{\varepsilon}(\mathbf{u})) - \partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) : \mathbb{E}(\bar{\chi}_\tau - \chi) \, dx \, dt \\
 &\quad - \int_Q \partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \bar{\chi}_\tau, \underline{d}_\tau) : (\bar{\mathbf{E}}_\tau - \mathbf{E}) \, dx \, dt.
 \end{aligned} \tag{5.50}$$

We are going to show that the right-hand side of (5.50) converges to 0 as $\tau \rightarrow 0$.

By (5.41b) and (5.44) and the continuity of the Nemytskiĭ mapping induced by $\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \cdot, \cdot)$ and by (5.37b), we have $\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \bar{\chi}_\tau, \underline{d}_\tau) : (\mathbf{E}_\tau - \mathbf{E}) \rightarrow 0$ weakly in $L^1(Q)$. Also, by the boundedness of $\{\partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau)\}_{\tau>0}$ in $L^2(Q; \mathbb{R}^{3 \times 3})$ and again by (5.41b), we have $\partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) : \mathbb{E}(\bar{\chi}_\tau - \chi) \rightarrow 0$ strongly in $L^1(Q)$. Hence, relying on the discrete equation (5.13a), we can continue in estimation (5.50) as follows:

$$\begin{aligned}
 \epsilon \limsup_{\tau \rightarrow 0} \|\bar{\mathbf{E}}_\tau - \mathbf{E}\|_{L^2(Q; \mathbb{R}^{3 \times 3})}^2 &\leq \limsup_{\tau \rightarrow 0} \int_Q \partial_{\mathbf{E}} \varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) : (\boldsymbol{\varepsilon}(\bar{\mathbf{u}}_\tau) - \boldsymbol{\varepsilon}(\mathbf{u})) \, dx \, dt. \\
 &= \limsup_{\tau \rightarrow 0} \int_Q (\bar{\mathbf{f}}_\tau - \varrho \ddot{\mathbf{u}}_\tau^i) \cdot (\bar{\mathbf{u}}_\tau - \mathbf{u}) \, dx \, dt - \int_Q \mathbb{D} \dot{\mathbf{E}}_\tau : (\bar{\mathbf{E}}_\tau - \mathbf{E}) \, dx \, dt \\
 &\leq \lim_{\tau \rightarrow 0} \left(\int_\Omega \varrho \dot{\mathbf{u}}_\tau(0) \cdot \bar{\mathbf{u}}_\tau(\tau) - \varrho \dot{\mathbf{u}}_\tau(T) \cdot \bar{\mathbf{u}}_\tau(T) \, dx + \iint_{\tau \Omega} \varrho \dot{\mathbf{u}}_\tau(\cdot - \tau) \cdot \dot{\mathbf{u}}_\tau \, dx \, dt \right. \\
 &\quad \left. + \int_Q \varrho \ddot{\mathbf{u}}_\tau^i \cdot \mathbf{u} \, dx \, dt \right) \\
 &\quad + \lim_{\tau \rightarrow 0} \int_Q \bar{\mathbf{f}}_\tau \cdot (\bar{\mathbf{u}}_\tau - \mathbf{u}) \, dx \, dt - \liminf_{\tau \rightarrow 0} \int_Q \mathbb{D} \dot{\mathbf{E}}_\tau : (\mathbf{E}_\tau - \mathbf{E}) \, dx \, dt \\
 &= \int_\Omega \varrho \dot{\mathbf{u}}(0) \cdot \mathbf{u}(0) - \varrho \dot{\mathbf{u}}(T) \cdot \mathbf{u}(T) \, dx + \int_Q \varrho |\dot{\mathbf{u}}|^2 + \varrho \ddot{\mathbf{u}} \cdot \mathbf{u} \, dx \, dt \\
 &\quad - \liminf_{\tau \rightarrow 0} \int_Q \mathbb{D} \dot{\mathbf{E}}_\tau : \mathbf{E}_\tau \, dx \, dt + \lim_{\tau \rightarrow 0} \int_Q \mathbb{D} \dot{\mathbf{E}}_\tau : \mathbf{E} \, dx \, dt \\
 &= \liminf_{\tau \rightarrow 0} \frac{1}{2} \int_\Omega (\mathbb{D} \mathbf{E}_\tau(T) : \mathbf{E}_\tau(T) - \mathbb{D} \mathbf{E}_0 : \mathbf{E}_0) \, dx \\
 &\quad - \frac{1}{2} \int_\Omega (\mathbb{D} \mathbf{E}(T) : \mathbf{E}(T) - \mathbb{D} \mathbf{E}_0 : \mathbf{E}_0) \, dx \leq 0.
 \end{aligned} \tag{5.51}$$

Here we also used the discrete by-part summation, cf. e.g. [46, Remark 11.38] and that, since $\bar{\mathbf{E}}_\tau - \mathbf{E}_\tau = (\tau k - t) \dot{\mathbf{E}}_\tau$ for $t \in ((k - 1)\tau, k\tau)$ and since \mathbb{D} is positive, we have $\int_Q \mathbb{D} \dot{\mathbf{E}}_\tau : (\bar{\mathbf{E}}_\tau - \mathbf{E}_\tau) \, dx \, dt \geq 0$. Also we used the weak convergence $\mathbf{E}_\tau(T) \rightharpoonup \mathbf{E}(T)$ in $L^2(\Omega; \mathbb{R}^{3 \times 3})$, which is readily verified through $\int_\Omega \mathbf{E}_\tau(T) : \tilde{\mathbf{E}} \, dx = \int_0^T \int_\Omega \dot{\mathbf{E}}_\tau : \tilde{\mathbf{E}} \, dx \, dt + \int_\Omega \mathbf{E}_\tau(0) : \tilde{\mathbf{E}} \, dx \rightarrow \int_0^T \int_\Omega \dot{\mathbf{E}} : \tilde{\mathbf{E}} \, dx \, dt + \int_\Omega \mathbf{E}(0) : \tilde{\mathbf{E}} \, dx = \int_\Omega \mathbf{E}(T) : \tilde{\mathbf{E}} \, dx$ holding for $\tilde{\mathbf{E}} \in L^2(\Omega; \mathbb{R}^{3 \times 3})$ arbitrary. Moreover, we also used that $\{\varrho \ddot{\mathbf{u}}_\tau^i\}_{\tau>0}$ converges weakly* in a space which is in duality to the space where $\dot{\mathbf{u}}$ lives, and in particular also that $\varrho \ddot{\mathbf{u}}$ is in duality with $\dot{\mathbf{u}}$:

$$\dot{\mathbf{u}} \in L^2(I; H^1(\Omega; \mathbb{R}^3)) \quad \text{and} \quad \varrho \ddot{\mathbf{u}} \in L^2(I; H^1(\Omega; \mathbb{R}^3)^*). \tag{5.52}$$

Step 3: Convergence in the semilinear mechanical part. Because of the smoothness of φ_{ME} and of the strong convergence of $\bar{\mathbf{E}}_\tau$, $\bar{\chi}_\tau$, and \underline{d}_τ already established and stated, respectively, in (5.49), (5.41b), and (5.44), we have

$$\partial_{\mathbf{E}}\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) \rightarrow \partial_{\mathbf{E}}\varphi_{\text{ME}}(\mathbf{E}, \chi, d) \quad \text{in } L^2(Q; \mathbb{R}^{3 \times 3}). \quad (5.53)$$

by continuity of the Nemytskiĭ mapping induced by φ_{ME} . The limit passage in (5.13a) is then done.

Step 4: Limit passage in the phase-field equation. We rewrite (5.13d) as two variational inequalities:

$$\begin{aligned} & \int_Q (\bar{\sigma}_{\text{r},\tau} + \partial_{\chi}\varphi_{\text{ME/CH}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau) + \partial_{\chi}\varphi_{\text{TH}}(\underline{\chi}_\tau, \underline{\theta}_\tau) - \mathbb{E}^\top : (\partial_{\mathbf{E}}\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) + \mathbb{D}\dot{\mathbf{E}}_\tau)) \cdot (v - \dot{\chi}_\tau) \\ & \quad + \kappa_1 \nabla \bar{\chi}_\tau : (\nabla v - \nabla \dot{\chi}_\tau) + \zeta(\mathbf{E}_\tau, \underline{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau, v) \, dx dt \\ & \geq \int_Q -\zeta(\mathbf{E}_\tau, \underline{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau, \dot{\chi}_\tau) \, dx dt \quad \forall v \in L^2(I; H^1(\Omega; \mathbb{R}^N)), \end{aligned} \quad (5.54a)$$

$$\int_Q \bar{\sigma}_{\text{r},\tau} \cdot (v - \bar{\chi}_\tau) \, dx dt \geq 0 \quad \forall v \in L^2(Q; \mathbb{R}^N), \quad v \in K \text{ a.e. in } Q. \quad (5.54b)$$

The limit passage in (5.54b) is easy because $\bar{\sigma}_{\text{r},\tau} \rightarrow \sigma_{\text{r}}$ weakly in $L^2(Q; \mathbb{R}^N)$ and $\bar{\chi}_\tau \rightarrow \chi$ strongly in $L^2(Q; \mathbb{R}^N)$ has already been proved in Step 2; thus $\sigma_{\text{r}} \in N_K(\chi)$ is shown. Now we can make a limit passage in (5.54a). Here on the left-hand side we have collected all terms that need to be handled through a continuity or a weak upper semicontinuity, while the right-hand side is to be treated by weak lower semicontinuity. We benefit from the already proven strong convergence of \underline{d}_τ , \underline{c}_τ , and $\bar{\mathbf{E}}_\tau$. The limit passage in $\partial_{\chi}\varphi_{\text{ME/CH}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau) \cdot \dot{\chi}_\tau$ and $\partial_{\chi}\varphi_{\text{TH}}(\underline{\chi}_\tau, \underline{\theta}_\tau) \cdot \dot{\chi}_\tau$ is simply by continuity. Furthermore, we have

$$\begin{aligned} \limsup_{\tau \rightarrow 0} \int_Q -\kappa_1 \nabla \bar{\chi}_\tau \cdot \nabla \dot{\chi}_\tau \, dx dt & \leq \int_\Omega \frac{\kappa_1}{2} |\nabla \chi_0|^2 \, dx - \liminf_{\tau \rightarrow 0} \int_\Omega \frac{\kappa_1}{2} |\nabla \chi(T)|^2 \, dx \\ & \leq \int_\Omega \frac{\kappa_1}{2} |\nabla \chi_0|^2 - \frac{\kappa_1}{2} |\nabla \chi(T)|^2 \, dx. \end{aligned} \quad (5.55)$$

The only difficult term is $\mathbb{E}^\top : \mathbb{D}\dot{\mathbf{E}}_\tau \dot{\chi}_\tau$ because so far we only know the weak convergence of both $\dot{\mathbf{E}}_\tau$ and $\dot{\chi}_\tau$. This requires a quite tricky chain of arguments:

$$\begin{aligned} & \limsup_{\tau \rightarrow 0} \int_Q \mathbb{E}^\top : (\partial_{\mathbf{E}}\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) + \mathbb{D}\dot{\mathbf{E}}_\tau) \dot{\chi}_\tau \, dx dt \\ & = \limsup_{\tau \rightarrow 0} \int_Q (\partial_{\mathbf{E}}\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) + \mathbb{D}\dot{\mathbf{E}}_\tau) : (\varepsilon(\dot{\mathbf{u}}_\tau) - \dot{\mathbf{E}}_\tau) \, dx dt \\ & = - \liminf_{\tau \rightarrow 0} \int_Q (\varrho \ddot{\mathbf{u}}_\tau^i - \bar{\mathbf{f}}_\tau) \cdot \dot{\mathbf{u}}_\tau + (\partial_{\mathbf{E}}\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) + \mathbb{D}\dot{\mathbf{E}}_\tau) : \dot{\mathbf{E}}_\tau \, dx dt + \lim_{\tau \rightarrow 0} \int_\Sigma \bar{\mathbf{f}}_{\text{s},\tau} \cdot \dot{\mathbf{u}}_\tau \, dS dt \\ & \leq - \liminf_{\tau \rightarrow 0} \left(\frac{1}{2} \int_\Omega \varrho |\dot{\mathbf{u}}_\tau(T)|^2 \, dx + \int_Q \mathbb{D}\dot{\mathbf{E}}_\tau : \dot{\mathbf{E}}_\tau \, dx dt \right) \\ & \quad + \frac{1}{2} \int_\Omega \varrho |\dot{\mathbf{u}}(0)|^2 \, dx + \lim_{\tau \rightarrow 0} \left(\int_Q \bar{\mathbf{f}}_\tau \cdot \dot{\mathbf{u}}_\tau - \partial_{\mathbf{E}}\varphi_{\text{ME}}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau) : \dot{\mathbf{E}}_\tau \, dx dt + \int_\Sigma \bar{\mathbf{f}}_{\text{s},\tau} \cdot \dot{\mathbf{u}}_\tau \, dS dt \right) \end{aligned}$$

$$\begin{aligned}
 &\leq -\frac{1}{2} \int_{\Omega} \varrho |\dot{\mathbf{u}}(T)|^2 dx - \int_Q \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} dx dt \\
 &\quad + \frac{1}{2} \int_{\Omega} \varrho |\dot{\mathbf{u}}(0)|^2 dx + \int_Q \mathbf{f} \cdot \dot{\mathbf{u}} - \partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) : \dot{\mathbf{E}} dx dt + \int_{\Sigma} \mathbf{f}_s \cdot \dot{\mathbf{u}} dS dt \\
 &= - \int_0^T \langle \varrho \ddot{\mathbf{u}}, \dot{\mathbf{u}} \rangle dt + \int_Q \mathbf{f} \cdot \dot{\mathbf{u}} - (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D} \dot{\mathbf{E}}) : \dot{\mathbf{E}} dx dt + \int_{\Sigma} \mathbf{f}_s \cdot \dot{\mathbf{u}} dS dt \\
 &= \int_Q \mathbb{E}^\top : (\partial_{\mathbf{E}} \varphi_{\text{ME}}(\mathbf{E}, \chi, d) + \mathbb{D} \dot{\mathbf{E}}) \dot{\chi} dx dt. \tag{5.56}
 \end{aligned}$$

Here, the first equality has used just $\mathbb{E} \dot{\chi}_\tau = \varepsilon(\dot{\mathbf{u}}_\tau) - \dot{\mathbf{E}}_\tau$, the second one has used the force balance (5.13a) with the boundary conditions (5.14a) tested by $\dot{\mathbf{u}}_\tau$, then we have used the discrete by-part integration (or, in fact, summation) $\frac{1}{2} |\dot{\mathbf{u}}_\tau(T)|^2 - \frac{1}{2} |\dot{\mathbf{u}}_\tau(0)|^2 \leq \int_0^T \ddot{\mathbf{u}}_\tau \cdot \dot{\mathbf{u}}_\tau dt$ on Ω , then semicontinuity arguments, then the by-part integration formula

$$\int_0^T \langle \varrho \ddot{\mathbf{u}}, \dot{\mathbf{u}} \rangle dt = \int_{\Omega} \frac{\varrho}{2} |\dot{\mathbf{u}}(T)|^2 - \frac{\varrho}{2} |\dot{\mathbf{u}}(0)|^2 dx. \tag{5.57}$$

relying on the fact that, by (5.52), $\varrho \ddot{\mathbf{u}}$ and $\dot{\mathbf{u}}$ are in duality, then the limit force equilibrium we have already proved in Step 3, and at the end still $\mathbb{E} \dot{\chi} = \varepsilon(\dot{\mathbf{u}}) - \dot{\mathbf{E}}$. The limit in $\int_Q \bar{\sigma}_{r,\tau} \cdot \dot{\chi}_\tau dx dt$ is simple because, for any $\bar{\sigma}_{r,\tau} \in N_K(\dot{\chi}_\tau)$, this integral equals to $\int_{\Omega} \delta_K(\chi_\tau(T)) - \delta_K(\chi_0) dx = 0$. Eventually, the limit passage the right-hand side of (5.54a) is by convexity of $\zeta(\mathbf{E}, \chi, d, c, \theta, \cdot)$ and the weak lower semi-continuity

$$\liminf_{\tau \rightarrow 0} \int_Q \zeta(\underline{\mathbf{E}}_\tau, \underline{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau, \underline{\theta}_\tau, \dot{\chi}_\tau) dx dt \geq \int_Q \zeta(\mathbf{E}, \chi, d, c, \theta, \dot{\chi}) dx dt. \tag{5.58}$$

Here we have also used that $\underline{\mathbf{E}}_\tau \rightarrow \mathbf{E}$, which follows from (5.49) and from

$$\|\bar{\mathbf{E}}_\tau - \underline{\mathbf{E}}_\tau\|_{L^2(Q; \mathbb{R}^{3 \times 3})} \leq \tau \|\dot{\mathbf{E}}_\tau\|_{L^2(Q; \mathbb{R}^{3 \times 3})} \rightarrow 0. \tag{5.59}$$

Step 5: Limit passage in the diffusion equation. By the strong convergence of $\bar{\mathbf{E}}_\tau$, $\bar{\chi}_\tau$, \underline{d}_τ , and \underline{c}_τ established in (5.49), (5.41b), (5.43), and (5.36f), and by assumption of boundedness (4.1k) of \mathbf{M} and by the Nemytskii-mapping continuity argument, we have that

$$\mathbf{M}(\bar{\mathbf{E}}_\tau, \bar{\chi}_\tau, \underline{d}_\tau, \underline{c}_\tau) \rightarrow \mathbf{M}(\mathbf{E}, \chi, c, d) \quad \text{strongly in } L^p(Q; \mathbb{R}_{\text{sym}}^{3 \times 3}) \quad \forall 1 \leq p < +\infty. \tag{5.60}$$

Now, owing to (5.37e), (5.37f), and (5.60), we can pass to the limit in the first of (5.13c). In order to pass to the limit in the second of (5.13c), we observe that by the aforementioned a.e. convergence of $\bar{\chi}_\tau$, \underline{d}_τ , and \underline{c}_τ in Q and by the continuity of $\partial_c \varphi_{\text{CH}}$, we have

$$\bar{\mu}_\tau = \partial_c \varphi_{\text{CH}}(\bar{\chi}_\tau, \bar{c}_\tau) \rightarrow \partial_c \varphi_{\text{CH}}(\chi, c) \quad \text{a.e. in } Q, \tag{5.61}$$

for some subsequence. By comparing (5.61) with (5.37f) we conclude that

$$\mu = \partial_c \varphi_{\text{CH}}(\chi, c). \tag{5.62}$$

Step 6: Limit passage in the semi-stability (5.13d) towards (4.9d). The mutual recovery sequence in the sense of [35] for (5.13d) uses the sophisticated construction of M. Thomas [54, 55]. For all $t \in I$, we have

$$\bar{d}_\tau(t) \rightarrow d(t) \quad \text{weakly in } H^1(\Omega). \tag{5.63}$$

Consider a competitor \tilde{d} of $d(t)$ in (4.9d). It suffices to consider the case

$$\tilde{d}(x) \leq d(x, t) \quad \text{for a.e. } x \in \Omega, \tag{5.64}$$

since otherwise the right-hand side the inequality (4.9d) is $+\infty$.

We define the sequence

$$\tilde{d}_\tau(x, t) = \min \{(\tilde{d}(x) - \varepsilon_\tau)^+, \bar{d}_\tau(x, t)\} \quad \text{with} \quad \varepsilon_\tau = \|\bar{d}_\tau(t) - d(t)\|_{L^q(\Omega)}^{1/2}. \tag{5.65}$$

with $1 \leq q < 6$. It is immediate to check that $\tilde{d}_\tau \in H^1(\Omega)$ and $\tilde{d}_\tau(t) < \bar{d}_\tau(t)$. Moreover, for $A_\tau(t) = \{x \in \Omega : \tilde{d}(x) - \varepsilon_\tau \leq \bar{d}_\tau(x, t)\}$, we have:

$$\nabla \tilde{d}_\tau(x, t) = \begin{cases} \nabla \tilde{d}(x) & \forall x \in A_\tau(t), \\ \nabla \bar{d}_\tau(x, t) & \forall x \in \Omega \setminus A_\tau(t). \end{cases} \tag{5.66}$$

Consequently

$$\liminf_{\tau \rightarrow 0} \int_{\Omega} |\nabla \bar{d}_\tau(x, t)|^2 - |\nabla \tilde{d}_\tau(x, t)|^2 \, dx = \liminf_{\tau \rightarrow 0} \int_{A_\tau} |\nabla \bar{d}_\tau(x, t)|^2 - |\nabla \tilde{d}(x)|^2 \, dx. \tag{5.67}$$

Because of (5.64), we have $|\bar{d}_\tau(x, t) - d(x)| \leq \varepsilon_\tau \Rightarrow x \in A_\tau(t)$. Thus, $\Omega \setminus A_\tau(t) \subset \{x \in \Omega : |\bar{d}_\tau(x, t) - \tilde{d}(x)| \geq \varepsilon_\tau\}$. Using Markov's inequality and the weak convergence of $\bar{d}_\tau(t)$ to $d(t)$ in $H^1(\Omega)$, we obtain

$$|\Omega \setminus A_\tau(t)| \leq \frac{1}{\varepsilon_\tau^q} \int_{\Omega} |\bar{d}_\tau(x, t) - d(x, t)|^q \, dx = \|\bar{d}_\tau(t) - d(t)\|_{L^q(\Omega)}^{q/2} \rightarrow 0 \tag{5.68}$$

where $q \in [1, 6)$ is the same exponent as (5.65) and $|\Omega \setminus A_\tau(t)|$ denotes the Lebesgue measure of the set $\Omega \setminus A_\tau(t)$. Given a set C , let δ_C be its indicator function. It is shown in [55] that

$$\delta_{A_\tau(t)} \nabla \bar{d}_\tau(t) \rightarrow \nabla d(t) \quad \text{weakly in } L^2(\Omega; \mathbb{R}^3). \tag{5.69}$$

On the other hand we have, trivially, that $\delta_{A_\tau(t)} \nabla \tilde{d}$ converges strongly to $\nabla \tilde{d}$. Thus, from (5.67) we find, by lower semicontinuity,

$$\begin{aligned} \liminf_{\tau \rightarrow 0} \int_{\Omega} |\nabla \bar{d}_\tau(x, t)|^2 - |\nabla \tilde{d}_\tau(x, t)|^2 \, dx &= \liminf_{\tau \rightarrow 0} \int_{\Omega} \delta_{A_\tau(t)}(x) |\nabla \bar{d}_\tau(x, t)|^2 \, dx - \lim_{\tau \rightarrow 0} \int_{A_\tau(t)} |\nabla \tilde{d}(x)|^2 \, dx \\ &\geq \int_{\Omega} |\nabla d(x, t)|^2 \, dx - \int_A |\nabla \tilde{d}(x)|^2 \, dx. \end{aligned} \tag{5.70}$$

With this result, the limit passage in the semi-stability condition is easily achieved for a.e. $t \in I$, on taking into account that $\bar{\mathbf{E}}_\tau(t) \rightarrow \mathbf{E}(t)$ strongly in $L^2(\Omega; \mathbb{R}_{sym}^{3 \times 3})$; furthermore, $\bar{\chi}_\tau(t) \rightarrow \chi(t)$ strongly in $L^q(\Omega; \mathbb{R}^N)$, and $\bar{c}_\tau(t) \rightarrow c(t)$ strongly in $L^q(\Omega)$.

Step 7: Mechanical/chemical energy conservation (4.9f). This is standardly achieved by testing the mechano-chemical equations (3.7a–d), respectively, by $\dot{\mathbf{u}}$, $\dot{\chi}$, μ , and \dot{d} , and by using the chain rule to integrate with respect to t . Here, however, (3.7d) has to be specially treated because \dot{d} can be a measure.

Making the first test legal, we again need $\varrho \dot{\mathbf{u}}$ to be in duality with $\dot{\mathbf{u}}$, cf. (5.52), and make use of (5.57). For the second mentioned test, we need $\Delta \chi \in L^2(Q; \mathbb{R}^N)$ to have the integration-by-part formula at our disposal. The regularity of $\Delta \chi$ follows from estimate (5.34d) and weak convergence. The proof of the by-part integration formula is rather technical because $\chi : I \rightarrow H^1(\Omega; \mathbb{R}^N)$ is actually only a weakly continuous function but not necessarily strongly continuous. The desired formula is

$$\int_Q \Delta \chi \cdot \dot{\chi} \, dx dt = \frac{1}{2} \int_{\Omega} |\nabla \chi_0|^2 - |\nabla \chi(T)|^2 \, dx. \tag{5.71}$$

Its proof is a bit tricky and can be done either by a mollification in space [38, Formula (3.69)] or also [46, Formula (12.132b)], and or in time by a time-difference technique [20, Formula (2.15)]. Also we use that $\sigma_r \in L^2(Q; \mathbb{R}^N)$ is in duality with $\dot{\chi} \in L^2(Q; \mathbb{R}^N)$, so that the integral $\int_Q \sigma_r \cdot \dot{\chi} \, dxdt$ has a sense and simply equals to 0 because $\sigma_r \in \partial\delta_K(\chi)$ has been proved in Step 4 and because $\delta_K(\chi_0) = 0$ has been assumed, cf. (4.11b).

Also, $\dot{c} \in L^2(I; H^1(\Omega)^*)$ is in duality with $\mu \in L^2(I; H^1(\Omega))$ as well as $\dot{\chi} \in L^2(Q; \mathbb{R}^N)$ is in duality with $\partial_{\chi} \varphi_{CH}(\chi, c) \in L^2(Q; \mathbb{R}^N)$, cf. (5.34c) with (5.36g) and (4.1e) so that we obtain

$$\int_0^T \left(\langle \dot{c}, \mu \rangle + \int_{\Omega} \partial_{\chi} \varphi_{CH}(\chi, c) \cdot \dot{\chi} \, dx \right) g dt = \int_{\Omega} \varphi_{CH}(\chi(T), c(T)) - \varphi_{CH}(\chi_0, c_0) \, dx. \tag{5.72}$$

Eventually, we use the Riemann-sum approximation of Lebesgue integrals and semi-stability as devised in [11, 34], cf. also [45, Formulas (4.68)–(4.74)] for a combination with rate-dependent mechanical part. In fact, the Riemann sums can range only a.a. points from I and thus the semi-stability need not hold at every time but only at almost each times, cf. (4.9d). By this way we obtain

$$\begin{aligned} & \int_{\Omega} \varphi_{ME}(\mathbf{E}(T), \chi(T), d(T)) + \frac{\kappa_2}{2} |\nabla d(T)|^2 + \alpha(\chi(T))d(T) \, dx + \int_Q \alpha'(\chi) \dot{\chi} \, dxdt \\ &= \int_{\Omega} \varphi_{ME}(\mathbf{E}_0, \chi_0, d_0) + \frac{\kappa_2}{2} |\nabla d_0|^2 + \alpha(\chi_0)d_0 \, dx - \int_Q \partial_{\mathbf{E}} \varphi_{ME}(\mathbf{E}, \chi, d) \dot{\mathbf{E}} + \partial_{\chi} \varphi_{ME}(\mathbf{E}, \chi, d) \dot{\chi} \, dxdt. \end{aligned} \tag{5.73}$$

Again we used that $\dot{\mathbf{E}} \in L^2(Q; \mathbb{R}_{sym}^{3 \times 3})$ and $\dot{\chi} \in L^2(Q; \mathbb{R}^N)$ are in duality with $\partial_{\mathbf{E}} \varphi_{ME}(\mathbf{E}, \chi, d) \in L^2(Q; \mathbb{R}_{sym}^{3 \times 3})$ and $\partial_{\chi} \varphi_{ME}(\mathbf{E}, \chi, d) \dot{\chi}$, respectively. Here we also used the semi-stability of the initial condition d_0 assumed in (4.11c).

Eventually, by summing up all four obtained partial balances, we obtain (4.9f).

Step 8: Strong convergence of $\dot{\mathbf{E}}_{\tau}$, $\dot{\chi}_{\tau}$, and $\nabla \bar{\mu}_{\tau}$. Using the discrete mechano-chemical energy imbalance (5.13g) and eventually the energy equality (4.9f), we can write

$$\begin{aligned} & \int_Q \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} + \partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \cdot \dot{\chi} + \mathbf{M}(\mathbf{E}, d, c, \theta) \nabla \mu \cdot \nabla \mu \, dxdt \\ & \leq \liminf_{\tau \rightarrow 0} \int_Q \mathbb{D} \dot{\mathbf{E}}_{\tau} : \dot{\mathbf{E}}_{\tau} + \partial_{\dot{\chi}} \zeta(\underline{\mathbf{E}}_{\tau}, \underline{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}, \dot{\chi}_{\tau}) \cdot \dot{\chi}_{\tau} + \mathbf{M}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}) \nabla \bar{\mu}_{\tau} \cdot \nabla \bar{\mu}_{\tau} \\ & \leq \limsup_{\tau \rightarrow 0} \int_Q \mathbb{D} \dot{\mathbf{E}}_{\tau} : \dot{\mathbf{E}}_{\tau} + \partial_{\dot{\chi}} \zeta(\mathbf{E}_{\tau}, \underline{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}, \dot{\chi}_{\tau}) \cdot \dot{\chi}_{\tau} + \mathbf{M}(\bar{\mathbf{E}}_{\tau}, \bar{\chi}_{\tau}, \underline{d}_{\tau}, \underline{c}_{\tau}, \underline{\theta}_{\tau}) \nabla \bar{\mu}_{\tau} \cdot \nabla \bar{\mu}_{\tau} \, dxdt \\ & \leq \limsup_{\tau \rightarrow 0} \left(\mathcal{E}_{MC}(0) - \int_{\Omega} \frac{\varrho}{2} |\dot{\mathbf{u}}_{\tau}(T)|^2 + \varphi_{ME/CH}(\mathbf{E}_{\tau}(T), \chi_{\tau}(T), d_{\tau}(T), c_{\tau}(T)) \right. \\ & \quad \left. + \frac{\kappa_1}{2} |\nabla \chi_{\tau}(T)|^2 + \frac{\kappa_2}{2} |\nabla d_{\tau}(T)|^2 dx - \int_{\Sigma} \bar{\mathbf{f}}_{s,\tau} \cdot \dot{\mathbf{u}}_{\tau} \, dSdt + \int_Q \alpha(\bar{\chi}_{\tau}) \dot{d}_{\tau} - \bar{\mathbf{f}}_{\tau} \cdot \dot{\mathbf{u}}_{\tau} \, dxdt \right) \end{aligned}$$

$$\begin{aligned}
 &\leq \mathcal{E}_{\text{MC}}(0) - \mathcal{E}_{\text{MC}}(T) - \int_{\Sigma} \mathbf{f}_s \cdot \dot{\mathbf{u}} \, dS dt - \int_Q \alpha'(\chi) \dot{\chi} d + \mathbf{f} \cdot \dot{\mathbf{u}} \, dx \, dt - \int_{\Omega} \alpha(\chi(T)) d(T) - \alpha(\chi_0) d_0 \, dx \\
 &= \int_Q \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} + \partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) \cdot \dot{\chi} + \mathbf{M}(\mathbf{E}, d, c, \theta) \nabla \mu \cdot \nabla \mu \, dx dt.
 \end{aligned} \tag{5.74}$$

Note that in the last inequality we have made use of the discrete by-part integration (= summation) formula for the following calculations, being a discrete analogue of (4.12) with $z = 1$:

$$\begin{aligned}
 \lim_{\tau \rightarrow 0} \int_Q \alpha(\bar{\chi}_{\tau}) \dot{d}_{\tau} \, dx \, dt &= \lim_{\tau \rightarrow 0} \sum_{k=1}^{T/\tau} \int_{\Omega} \alpha(\chi_{\tau}^k) (d_{\tau}^k - d_{\tau}^{k-1}) \, dx \\
 &= \lim_{\tau \rightarrow 0} \left(\int_{\Omega} \alpha(\chi_{\tau}^{T/\tau}) d_{\tau}^{T/\tau} \, dx - \sum_{k=1}^{T/\tau} \int_{\Omega} (\alpha(\chi_{\tau}^k) - \alpha(\chi_{\tau}^{k-1})) d_{\tau}^{k-1} \, dx \right) - \int_{\Omega} \alpha(\chi_{\tau}^0) d_{\tau}^0 \, dx \\
 &= \lim_{\tau \rightarrow 0} \left(\int_{\Omega} \alpha(\chi_{\tau}(T)) d_{\tau}(T) \, dx - \int_Q (\alpha'(\chi_{\tau}) \dot{\chi}_{\tau} d_{\tau} + r_{\tau} d_{\tau}) \, dx \, dt \right) - \int_{\Omega} \alpha(\chi_0) d_0 \, dx \\
 &= \int_{\Omega} \alpha(\chi(T)) d(T) \, dx - \int_Q (\alpha'(\chi) \dot{\chi} d + 0) \, dx \, dt - \int_{\Omega} \alpha(\chi_0) d_0 \, dx,
 \end{aligned}$$

where we have set $d_{\tau}^{-1} = d_{\tau}^0 = d_0$ and where r_{τ} denotes the difference between $[\alpha(\chi_{\tau})]'$ meaning the time derivative of the piecewise linear interpolation $\alpha(\chi_{\tau}^k)$ and the piece-wise constant-in-time function with values $(\alpha(\chi_{\tau}^k) - \alpha(\chi_{\tau}^{k-1}))/\tau$ on the interval $((k-1)\tau, k\tau)$; here we used the differentiability assumption on α stated in (4.10) and the estimate $|r_{\tau}| \leq \tau^2 (\sup_{\mathbb{R}^N} \alpha'') |\dot{\chi}_{\tau}|^2$ so that

$$\left| \int_Q r_{\tau} d_{\tau} \, dx \, dt \right| \leq \tau^2 (\sup_{\mathbb{R}^N} \alpha'') \int_Q |\dot{\chi}_{\tau}|^2 d_{\tau} \, dx \, dt \leq \tau^2 (\sup_{\mathbb{R}^N} \alpha'') \|\dot{\chi}_{\tau}\|_{L^2(Q; \mathbb{R}^N)}^2 \|d_{\tau}\|_{L^{\infty}(Q)} = \mathcal{O}(\tau^2) \rightarrow 0$$

for $\tau \rightarrow 0$. In order to check that $\alpha'(\chi_{\tau}) \dot{\chi}_{\tau} d_{\tau}$ converges to $\alpha'(\chi) \dot{\chi} d$ weakly in $L^1(Q)$, we used (5.41b) together with (5.37c), and (5.44). The last equality in (5.74) has been proved in Step 7. Altogether, we can write “lim” and “=” everywhere in (5.74) and, together with the already proved weak convergence, we obtain the desired strong convergence of $\dot{\mathbf{E}}_{\tau}$ and $\dot{\chi}_{\tau}$ and $\nabla \bar{\mu}_{\tau}$ in $L^2(Q)$ -spaces. Here we rely on the well-known concept of compactness via convexity ([57, 58]) with some modifications. In particular, for technical details about the term $\mathbf{M} \nabla \mu \cdot \nabla \mu$ with the nonconstant coefficient $\mathbf{M} = \mathbf{M}(\mathbf{E}, d, c, \theta)$, we refer to [51, Formula (4.25)].

Step 9: Limit passage in the heat equation (5.13f). Having proved the strong convergence in Steps 3 and 9, the right-hand side of (5.13f) converges strongly in $L^1(Q)$ except the term $\alpha(\chi) \dot{d}$ but even this term converges weakly* in $\text{Meas}(\bar{Q})$, cf. Step 7, which is sufficient to the limit passage towards (3.7e), which is then easy.

Step 10: Total energy conservation (4.13) at almost each time. Considering $t_* \in [0, T]$ fixed, we use a smoothed characteristic function of the cylinder $\Omega \times [0, t_*]$, namely

$$z_{\epsilon}(x, t) = \begin{cases} 1 & \text{if } t \leq t_*, \\ 1 + (t_* - t)/\epsilon & \text{if } t_* \leq t \leq t_* + \epsilon, \\ 0 & \text{if } t \geq t_* + \epsilon, \end{cases} \tag{5.75}$$

as the test function for (4.9e). Using that $\dot{z} = 0$ for $t \in [0, t_*] \cup [t_* + \epsilon, T]$ and that $\nabla z = 0$, this test leads to

$$\begin{aligned} \frac{1}{\epsilon} \int_{t_*}^{t_*+\epsilon} \int_{\Omega} w \, dx \, dt &= \int_0^{t_*} \int_{\Omega} \left((\partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) + \partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) + \alpha'(\chi)d) \cdot \dot{\chi} + \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu \cdot \nabla \mu \right. \\ &\quad \left. + \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} \right) dx \, dt + \frac{1}{\epsilon} \int_{t_*}^{t_*+\epsilon} \int_{\Omega} \alpha(\chi)d \, dx \, dt + \int_{\Omega} (w_0 + \alpha(\chi_0)d_0) \, dx \\ &\quad + \int_{\Sigma} q_s \, dS \, dt + o_t(\epsilon) \end{aligned} \quad (5.76)$$

with $o_{t_*}(\epsilon)$ abbreviating the corresponding integrals over $[t_*, t_* + \epsilon]$. We have $\lim_{\epsilon \rightarrow 0} o_{t_*}(\epsilon) = 0$ for any t_* due to the absolute continuity of the Lebesgue integral. Considering however t_* as a right Lebesgue point of the functions $t \mapsto \int_{\Omega} w(x, t) \, dx$ and $t \mapsto \int_{\Omega} \alpha(\chi(x, t))d(x, t) \, dx$, in the limit for $\epsilon \rightarrow 0+$ we obtain

$$\begin{aligned} \int_{\Omega} w(t_*) \, dx \, dt &= \iint_{0}^{t_*} \left((\partial_{\dot{\chi}} \zeta(\mathbf{E}, \chi, c, d, \theta, \dot{\chi}) + \partial_{\chi} \varphi_{\text{TH}}(\chi, \theta) + \alpha'(\chi)d) \cdot \dot{\chi} + \mathbf{M}(\mathbf{E}, \chi, c, d, \theta) \nabla \mu \cdot \nabla \mu \right. \\ &\quad \left. + \mathbb{D} \dot{\mathbf{E}} : \dot{\mathbf{E}} \right) dx \, dt + \int_{\Omega} \alpha(\chi(t_*))d(t_*) \, dx + \int_{\Omega} (w_0 + \alpha(\chi_0)d_0) \, dx + \iint_{0}^{t_*} q_s \, dS \, dt. \end{aligned} \quad (5.77)$$

The set of such points t_* has full Lebesgue measure on I . Eventually, we get (4.13) by summing (5.77) with the mechanical/chemical energy balance (4.9f) written for t_* instead of T obtained already in Step 8 by an obvious modification of the arguments there. \square

6. Some additional examples and concluding remarks

The general model (3.7) admits much wider application than so far presented in Examples 3.1 and 3.2, which is what we want partly illustrate now.

Example 6.1. (Magnetic and hydride transformations in intermetallics) Some intermetallic compounds exposed to hydrogen (or deuterium) exhibit not only metal/hydride phase transformations as mentioned above but also a dramatic structural transformation analogous to the martensitic ferro-to-para magnetic transformation, both mutually coupled. This is the case of Uranium- or rare-earth-based alloys, cf. [24, 27]. Experiments show that hydrogenation implies a substantial increase of the magnetic ordering temperature and noticeable increase in specific heat, cf. e.g. [17, 28]. There does not seem to be any models for it in mathematical literature to exist, however. The structural cubic-to-cubic phase transformation in particular single-crystal grains is similar e.g. to cubic-to-tetragonal so-called martensitic transformation which may also exhibit magnetic phase transformation in intermetallic like NiMnGa. Here, densely packed cubic configuration is typically paramagnetic (because electron orbits of particular atoms over-cover each other), while sparsely packed cubic configuration is typically ferromagnetic) in analogy with cubic austenite and tetragonal martensite in NiMnGa. Counting this analogy, one can assemble a model from already existing particular models for the martensitic transformation of the Souza-Auricchio type as e.g. in [2, 29], for the ferro-to-para magnetic transformation as in [38] in combination (and ignoring gyromagnetic effects) as in [48], and for the metal/hydride transformation under diffusion as above in (3.10). When considering the magnetic variation slow and thus neglecting all induced electrical effects and when neglecting also the self-induced demagnetising field, one can consider the (vector-valued) phase field $\chi = (\lambda, m)$ composed by the volume fraction λ related to the metal/hydride transformation and m

the magnetization vector. Magnetization hysteresis effects due to magnetic-domain pinning effects can be accounted for through the nonsmooth potential ζ , cf. [39, 40, 49, 53]. Again, damage is an important phenomenon which can even pulverize such materials due to markable volume changes during the cubic-to-cubic structural transformation. Combining [48, 50, 52], the free energy can be considered as

$$\begin{aligned} \varphi_{\text{TOT}}(\mathbf{E}, \chi, c, d, \theta) &= \frac{1}{2} \mathbb{C}(d) \mathbf{E} : \mathbf{E} + \frac{k}{2} |a(\lambda) - c|^2 + \phi_1(c) + \phi_2(\theta) + \frac{a_0}{2} (\theta - \theta_c) |m|^2 + \frac{b_0}{4} |m|^4 + \alpha_1(\theta) \lambda \\ &= \underbrace{\frac{1}{2} \mathbb{C}(d) \mathbf{E} : \mathbf{E} + \frac{b_0}{4} |m|^4}_{=:\varphi_{\text{ME}}} + \underbrace{\frac{k}{2} |a(\lambda) - c|^2 + \phi_1(c)}_{=:\varphi_{\text{CH}}} \\ &\quad + \underbrace{\phi_2(\theta) + \frac{a_0}{2} (\theta - \theta_c) |m|^2 + \alpha_1(\theta) \lambda}_{=:\varphi_{\text{TH}}} \end{aligned} \quad (6.1)$$

and with $\theta_c > 0$ the Curie temperature above which the ferromagnetic phase does not exist, $a_0, b_0 > 0$, and α_1 the temperature-dependent latent-heat density of the medium. Now $\frac{\kappa_+}{2} |\nabla \chi|^2$ occurring in (3.4) involves also $\frac{\kappa_+}{2} |\nabla m|^2$ which is called an exchange energy in magnetism. Further considerations may go beyond the ansatz in Sect. 2 by involving global effects through a demagnetising field as in [38, Remark 11] or dynamical electro-magnetic effects including Joule heating through the Maxwell system, possibly in an eddy-current approximation as in [48].

Example 6.2. (Water and heat propagation in concrete) An important application in civil engineering is water/vapour and heat transport in concrete undergoing damage and creep. The creep strain is most influenced by the moisture and temperature distribution. The model would be quite similar to (3.13) although some microscopical mechanisms behind the free energy and some dissipation mechanisms are different. In particular, c would be again interpreted as water concentration and μ as pressure. Moreover, the decomposition (1.1) would be adapted to the form considered in models of concrete that take into account creep, shrinkage and thermal strains [3, 19], namely, $\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + \mathbf{E}_{\text{cr}} + \mathbf{E}_{\text{sh}} + \mathbf{E}_{\text{th}}$, where \mathbf{E}_{cr} would be the creep strain, \mathbf{E}_{sh} would be the shrinkage strain caused by change of moisture, and \mathbf{E}_{th} would be the thermal strain. Of course, since direct coupling with c and θ is not included in our analysis, we would resort to a penalization like in (3.10) for c and a similar one for θ , cf. Remark 6.4 below. Furthermore, in this case the constraint $\chi \in K$ would be dropped, that is, we would set $K = \mathbb{R}^N$. Moreover, the dissipation potential ζ would be smooth at $\dot{\pi}_{\text{pl}} = 0$ because, in contrast to plasticity, the creep is typically not an activated process. Also the ageing mechanisms play a role, influencing the activation threshold α of damage. There is a lot of phenomenological models in literature, although typically not based on rational thermomechanics to be directly fitted in the framework (3.7); cf. e.g. [30].

Remark 6.3. (Poro-elastic model revisited) In order to apply our existence Theorem to the poroelastic model of Example 3.2, we need to slightly depart from the assumptions typically made in the modelling literature. To begin with, the Biot modulus M is usually assumed to be affine (cf. [22, 33]), a feature that would make the functional $\phi \mapsto \psi$ non-convex (even equi-semiconvexity (4.1i) cannot be expected, which would make technical troubles in using time discretization). Yet, (4.1i) does not necessarily mean M or G or λ to be constant. More importantly, a small modification of the free energy complying with the growth/coercivity restriction (4.1d) is needed for facilitating the analysis. In fact, the energy functional (3.13) from the poro-elastic example does not comply with the second condition in (4.1d) unless λ, G , and M are independent of d . Also, (3.13) is incompatible with (4.1i) in general, although one could weaken this condition and then make a finer splitting in the time-discretization in Sect. 5 by considering (ϕ, γ) separately from $(\mathbf{E}, \pi_{\text{pl}})$ in (5.1); here it depends, however, on the dissipation which should allow this separation. Anyhow, due to (4.1d), the example (3.13) has to be slightly modified. One option is to pose:

$$\begin{aligned} \varphi_{\text{TOT}}(\mathbf{E}, \phi, \gamma, c, d, \theta) &= \frac{1}{2} \frac{\lambda(\phi, d)(\text{tr } \mathbf{E})^2}{\sqrt{1+\epsilon(\text{tr } \mathbf{E})^2}} + G(\phi, d) \frac{|\mathbf{E}|^2}{\sqrt{1+\epsilon|\mathbf{E}|^2}} + \frac{1}{2} M(\phi, d) \frac{|\beta \text{tr } \mathbf{E} - \gamma + \phi|^2}{\sqrt{1+\epsilon(\text{tr } \mathbf{E})^2}} \\ &\quad + \frac{1}{2} \lambda_0 (\text{tr } \mathbf{E})^2 + G_0 |\mathbf{E}|^2 + \frac{1}{2} k |\gamma - c|^2 + c_v \theta (\ln \theta - 1) \end{aligned} \tag{6.2}$$

with $\epsilon > 0$ a presumably small regularizing parameter and with $\lambda_0 \geq 0$ and $G_0 > 0$. Then (4.1d) is satisfied. However, the papers [22, 23, 33] as a matter of fact (although not explicitly) consider cross-effects in dissipation of damage and porosity; here these effects must be neglected as otherwise there would be a coupling of (5.1) and (5.2) and stronger separate semi-convexity qualification likely not compatible with (3.13). Moreover, damage was considered reversible in [22, 23, 33], which is important in particular for longer-time scale processes in rocks, and moreover a phenomenological flow rule for π_{pl} was not governed directly by the free energy.

Remark 6.4. (*A general treatment of swelling or thermal expansion*) Some models would rather need, instead of (1.1), a more general form

$$\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + \mathbb{E}\chi + s(c)\mathbb{E}_{\text{sw}} + r(\theta)\mathbb{E}_{\text{ex}} \tag{6.3}$$

with some \mathbb{E}_{sw} and \mathbb{E}_{ex} swelling and thermal-expansion tensors and some (possibly even nonlinear) mappings $s, r : \mathbb{R} \rightarrow \mathbb{R}$ modelling swelling or thermal expansion effects, respectively. Thermal expansion would influence also the entropy: in fact, (2.4) is no longer valid and, in the spirit of Remark 2.2, we should rather consider $\varphi_{\text{ME}}(\boldsymbol{\varepsilon}(\mathbf{u}) - \mathbb{E}\chi - r(\theta)\mathbb{E}_{\text{ex}}, \chi, d)$ which gives an additional contribution $r'(\theta)\mathbb{E}_{\text{ex}}^\top \partial_{\mathbf{E}} \varphi_{\text{ME}}(\boldsymbol{\varepsilon}(\mathbf{u}) - \mathbb{E}\chi - r(\theta)\mathbb{E}_{\text{ex}}, \chi, d)$ to the enthalpy and also a corresponding contribution to the heat capacity $-\theta \partial_{\theta\theta}^2 \psi$ (unless the dependence on φ_{ME} on strain in quadratic). Furthermore, the positivity of temperature in the proof of Lemma 5.1 would fail, unless appropriate restrictions are imposed on the function θ . Additional troubles have already been mentioned in Remark 4.3. To fit such more general situations to our ansatz, we can little modify the particular problem by introducing additional phase-field variables, say χ_1 and χ_2 , and augment appropriately the free-energy parts φ_{CH} or φ_{TH} . More specifically, φ_{CH} can be augmented by $\frac{1}{2}k|s^{-1}(\chi_1) - c|^2$ or φ_{TH} by $\frac{1}{2}k|r^{-1}(\chi_2) - \theta|^2 - \frac{1}{2}k\theta^2$; actually, the term $-\frac{1}{2}k\theta^2$ balances this contribution to avoid its influence on the heat capacity. In fact, we already used the former term in (3.10), (3.13), and (6.1), too. Considering a presumably large constant k makes χ_1 and χ_2 approximate, respectively, $s(c)$ and $r(\theta)$. Then, instead of (6.3), we then take

$$\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + \mathbb{E}\chi + \chi_1 \mathbb{E}_{\text{sw}} + \chi_2 \mathbb{E}_{\text{ex}}, \tag{6.4}$$

which complies with (1.1). Note that the positive definiteness $\partial_{cc}^2 \varphi_{\text{CH}}$ is kept and the heat capacity $-\theta \partial_{\theta\theta}^2 \varphi_{\text{TH}}(\chi, \theta)$ is not affected by this modification. The energy balance (2.1e) is then affected through non-thermal terms, which exhibits similar modelling effects but makes the analysis easier.

Example 6.5. (Damage by freezing water) Application of thermal expansion discussed in Remark 6.4 can be modelling a very common phenomenon that water propagating in porous medium expands during water-ice phase transformation and may cause damage. This happens e.g. in concrete or in poroelastic rocks discussed above. Other occurrence is in polymer membranes in fuel cells [60], etc. The thermal expansion is now (approximately) proportional to the overall amount of ice, i.e. $c\lambda$ where c is the water concentration and λ the volume fraction of ice versus liquid water. Naturally, $\lambda = \lambda(\theta)$. Like in Remark 6.4, we consider rather the linear splitting $\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + \beta \mathbb{E}_{\text{ex}}$ with β and γ new phase-field variables which are expectedly close to $\lambda(\theta)c$ and c , respectively. This can be achieved, e.g. by adding terms like $\frac{1}{2}k|\theta - \lambda^{-1}(\beta/\gamma)|^2 - \frac{1}{2}k\theta^2 + \frac{1}{2}k|\gamma - c|^2$ to $\varphi_{\text{TH}} + \varphi_{\text{CH}}$. As ice practically cannot move, the mobility of water $\mathbf{M} = \mathbf{M}(\theta)$ falls to very small values if θ is below freezing point θ_{F} . The heat capacity $c_v(\gamma, \theta) = -\theta \partial_{\theta\theta}^2 \varphi_{\text{TH}}(\gamma, \theta)$ also depends on the water content γ and, moreover, may contain a Dirac distribution supported at the freezing point, i.e. $c_v(\chi, \theta) = c_{v,0} + \gamma L \delta_{\theta_{\text{F}}}(\theta)$ with L the latent heat of the water/ice phase transition. This is called the Stefan problem, cf. e.g. [44, 58], and then the upper bound C in the first condition in (4.1f) and also in (4.6) is ∞ and the graph of $\vartheta(\chi, \cdot)$ from (4.5) has a horizontal segment of the length γL

at the height θ_F . Some arguments we use in our proof must be then slightly generalized as such $\vartheta(\chi, \cdot)$ with now $\chi = (\beta, \gamma)$ is not invertible and smooth; important, (5.28) and the corresponding $\nabla\theta$ -estimate holds for such generalization, too. In fact, λ should depend on the enthalpy w rather than on temperature θ , cf. also Definition 4.1, but anyhow a fine regularization of the Stefan problem seems to be needed to overcome the singular character of this problem.

Remark 6.6. (*Other applications*) Beside, there are a lot of applications without considering any diffusion or without any damage, i.e. c or d is void (not used). For example magnetostriction in magnetic shape-memory alloys as in [48] with no damage and no diffusion, or plasticity in metals with damage but no diffusion, and or a combination of inelastic processes with some more complex rheologies involving additional internal variables in χ as e.g. Jeffreys' model involving a creep strain, that is, it combines the Maxwell rheology (responsible for creep) with the Kelvin–Voigt one, etc., cf. also Remark 2.1.

Remark 6.7. (*Some restrictions*) Within our approach, we cannot unfortunately handle the dependence of the coefficients in the gradient terms, i.e. of κ_2 and κ_1 , on damage d or on χ , which would be natural in some application. This dependence would give rise the higher-order L^1 -type terms in (4.9b) and (4.9d) which would destroy the regularity (5.34d) without which also (5.71) could not be proved.

Remark 6.8. (*The partly decoupled ansatz* (3.4)) The analysis carried out so far excludes certain couplings that would make our ansatz more general. We here list some generalization that, although appealing from the modelling viewpoint, appear to be incompatible with our strategy of proof.

1. If θ and \mathbf{E} were generally be coupled in (2.3), in general a concept of *non-simple material*, whose constitutive equations involve higher spatial derivatives of the displacement field (as opposed to constitutive equations for *simple materials*, which involve only the first derivatives), would be needed to have a control on $\nabla\mathbf{E}$, cf. [47]. An exception would be if θ would appear linearly, i.e. a term like $\theta\varphi(\mathbf{E})$, which then would not contribute to the heat capacity, cf. e.g. [52].
2. If c and \mathbf{E} were generally be coupled in (2.3), then the chemical potential $\mu = \partial_c\varphi$ from (2.5f) with (3.1c) would depend on \mathbf{E} and again the estimate (5.21) of ∇c would need a control of $\nabla\mathbf{E}$, i.e. the concept of nonsimple materials. Some alternative option would be introduce a gradient of c into the free energy, i.e. capillarity concept, see also Remark 6.10.
3. If d and θ were be coupled in (2.3), then the adiabatic heat term $\partial_{c\theta}^2\varphi(\dots, \theta)\dot{d}$ would occur but \dot{d} is a measure and θ tends typically to jump exactly at the points where \dot{d} concentrates, and such term would not be analytically well defined.
4. If c and θ were generally be coupled in (2.3), the adiabatic heat term $\partial_{c\theta}^2\varphi\dot{c}$ would occur in the right-hand side of the heat-transfer equation, cf. (3.7e), but we will not have any estimate on \dot{c} except the “dual” estimate (5.34c), so this term would not be controlled as a measure.
5. If c and d were generally be coupled in (2.3), we would see a term $\partial_d\varphi_{\text{CH}}(\chi, d, c)\dot{d}$ in (5.72). However, the term $\partial_d\varphi_{\text{CH}}(\chi, d, c)$ would be not continuous, because of the aforementioned lack of continuity of c , and hence its combination with the measure \dot{d} would not be well defined.

These five requirements led us to make the partly decoupled ansatz (3.4).

Remark 6.9. (*Damageable viscosity*) One may want to include damageable viscosity in the model through a constitutive equation of the form $\mathbf{S}_d = \mathbb{D}(d)\dot{\mathbf{E}}$ for the viscous part of the stress. With this modification, when performing the integration by parts in (5.51), the additional term $-\int_Q \frac{\partial}{\partial t}\mathbb{D}(d_\tau)\mathbf{E}_\tau : \mathbf{E}_\tau dxdt$ would appear. Passage to the limit through lower semicontinuity would still be possible if the tensor $\frac{\partial}{\partial t}\mathbb{D}(d_\tau)$ is non-positive. This could rely on the unidirectional evolution of d adopted in this paper and monotone dependence of \mathbb{D} on damage, in the sense of the so-called Löwner ordering, namely $(\mathbb{D}(d_1) - \mathbb{D}(d_2))\mathbf{E} : \mathbf{E} \leq 0$ if $d_1 < d_2$.

Remark 6.10. (*Decoupling between concentration and strain*) Our assumption (3.4) rules out any direct coupling between strain and concentration. We need a decoupling between concentration and strain to avoid an explicit dependence of chemical potential on strain, which would lead to the appearance of the gradient of strain in the formulation. Indeed, in order to pass to the limit in the nonlinear equation:

$$\mu = \partial_c \varphi_{\text{CH}}(\chi, c) \tag{6.5}$$

which defines chemical potential, we exploit the strong convergence of c in a suitable L^p space, cf. (5.36d) above. In order to obtain such convergence, we rely on the standard Aubin-Lions compactness theorem, whose application requires estimates on \dot{c} and ∇c . The natural energetic estimate provides us with a control on $\nabla \mu$ [cf. (5.15e)], but not on ∇c . To control of the latter [cf. estimate (5.15d) above] we take the gradient of (6.5) at the approximation level, see (5.21) in the proof of Lemma 5.3. If we were allowed $\partial_{c\mathbf{E}}^2 \varphi \neq 0$, then $\nabla \mathbf{E}$ would have appeared in that estimate. To give a concrete example, let us consider a toy model with no phase field χ , no damage variable d , and no temperature θ . Let us assume that the following strain decomposition:

$$\boldsymbol{\varepsilon}(\mathbf{u}) = \mathbf{E} + c\mathbb{E} \tag{6.6}$$

holds, where \mathbb{E} is a constant second-order symmetric tensor. In this case, the dissipation inequality takes the form

$$\dot{\psi} - \mu \dot{c} \leq \mathbf{S} : \dot{\mathbf{E}} + \mathbf{S} : \mathbb{E} \dot{c} - \mathbf{h} \cdot \nabla \mu. \tag{6.7}$$

Then, the application of the Coleman-Noll argument yields, for chemical potential, a constitutive equation of the form

$$\mu = \partial_c \psi(\mathbf{E}, c) + \mathbf{S} : \mathbb{E}. \tag{6.8}$$

Suppose that we take $\psi = \frac{1}{2} \mathbb{C} \mathbf{E} : \mathbf{E}$. Then, if we rule out viscoelastic dissipation, the constitutive equation for the stress is $\mathbf{S} = \mathbb{C} \mathbf{E}$. From (6.8) we have

$$\partial_{cc}^2 \psi(\mathbf{E}, c) \nabla c = \nabla \mu - \mathbb{E}^\top : \mathbb{C} \nabla \mathbf{E} \tag{6.9}$$

Clearly, there is no hope to control the second term on the right-hand side of (6.9), unless we have some control on $\nabla \mathbf{E}$, which however cannot be expected. This issue may be circumvented by allowing a dependence of free energy on ∇c , for instance by adding a term proportional to $|\nabla c|^2$. As discussed, for instance, in [16], this term describes capillarity effects and would lead to a system of Cahn–Hilliard type [9], similar to those studied in [18]. Alternatively, one might think of reformulating the model in the framework of non-simple materials, by allowing for instance the free energy to depend on $\nabla \mathbf{E}$ and by introducing hyperstress. In this case, however, issues would arise from the choice of traction boundary conditions in non-smooth domains [41].

Remark 6.11. (*Quasistatic and inviscid model*) Some models in literature neglect inertia and viscosity by putting both $\varrho = 0$ and $\mathbb{D} = 0$, see e.g. [7, 25]. The semi-implicit scheme can then be split naturally into five fractional steps, each of them for each variable \mathbf{u} , χ , d , c , and θ separately by replacing χ_τ^k in (5.1a) by χ_τ^{k-1} . Instead of (4.1i), it would suffice to require $\varphi_{\text{ME}}(\cdot, \chi, d)$ and $\varphi_{\text{ME}}(\mathbf{E}, \cdot, d) + \frac{1}{2} M |\cdot|^2$ convex. In this case, however, we would have to remove the dependence of ζ on \mathbf{E} because we would lose estimate (5.59), which relies on viscosity. Also e.g. thermal expansion leading usually to adiabatic terms containing $\dot{\mathbf{E}}$ would have to be excluded, although some particular studies resulting to spatially constant temperature does exist, cf. [32].

Remark 6.12. (*Viscous damage and higher regularity of displacements*) We already pointed out that in the case of rate-dependent evolution of damage (i.e. if the dissipation pseudopotential ξ would be quadratic), the variable d may be incorporated into the vectorial variable χ , which would still obey an evolution equation having the structure of (3.7b). This variant has recently been investigated in [43] in the case of thermal coupling. It is worth pointing out that its mathematical analysis would, however, require $L^2(Q)$ regularity of the term $\partial_d \varphi_{\text{ME}}(\mathbf{E}, \chi, d)$. Such regularity would in general not be compatible with the quadratic growth of φ_{ME} with respect to \mathbf{E} . In order to better elucidate this point, let us take

$\varphi_{\text{ME}} = \frac{1}{2}\mathbb{C}(d)\mathbf{E}:\mathbf{E}$. In order to guarantee the above-mentioned regularity, we would need $L^4(Q)$ regularity of \mathbf{E} , which in general cannot be expected without additional assumptions. Yet, higher regularity of displacements may be proved through a sophisticated technique based on testing the standard-force balance by $-\text{div}(\boldsymbol{\varepsilon}(\dot{\mathbf{u}}))$, as in [8], and also in [43]. This estimate would, however, require the assumption that acceleration vanishes on the whole boundary, which in turn would restrict the applicability of the model to affine-in-time Dirichlet boundary conditions for \mathbf{u} .

Acknowledgements

The authors are very thankful to two anonymous referees for their exceptionally thorough reviews which led to substantial improvement of the manuscript at many spots.

References

1. Akagi, G.: Maximal monotonicity for the sum of two subdifferential operators in L^p -spaces. *Nonlinear Anal. Theory. Methods Appl.* **74**, 1664–1671 (2011)
2. Auricchio, F., Reali, A., Stefanelli, U.: A macroscopic 1D model for shape memory alloys including asymmetric behaviors and transformation-dependent elastic properties. *Comput. Methods Appl. Mech. Eng.* **198**, 1631–1637 (2009)
3. Bažant, Z.P., Cusatis, G., Cedolin, G.: Temperature effect on concrete creep modeled by microprestress-solidification theory. *J. Eng. Mech.* **130**, 691–699 (2004)
4. Boccardo, L., Gallouët, T.: Non-linear elliptic and parabolic equations involving measure data. *J. Funct. Anal.* **87**, 149–169 (1989)
5. Bonetti, E., Colli, P., Laurençot, P.: Global existence for a hydrogen storage model with full energy balance. *Nonlinear Anal. Theory Methods Appl.* **75**, 3558–3573 (2012)
6. Bonetti, E., Fremond, M., Lexcellant, C.: Hydrogen storage: modeling and analytical results. *Appl. Math. Optim.* **55**, 31–59 (2007)
7. Bonetti, E., Heinemann, C., Kraus, C., Segatti, A.: Modeling and analysis of a phase field system for damage and phase separation processes in solids. *WIAS Preprint No. 1841*, Berlin (2013)
8. Bonetti, E., Schimperna, G., Segatti, A.: On a doubly nonlinear model for the evolution of damaging in viscoelastic materials. *J. Differ. Equ.* **218**, 91–116 (2005)
9. Cahn, J.W., Hilliard, J.E.: Free energy of a nonuniform system. I. Interfacial free energy. *J. Chem. Phys.* **28**, 258–267 (1958)
10. Chiodaroli, E.: A dissipative model for hydrogen storage: existence and regularity results. *Math. Methods Appl. Sci.* **34**, 642–669 (2011)
11. Dal Maso, G., Francfort, G., Toader, R.: Quasistatic crack growth in nonlinear elasticity. *Arch. Ration. Mech. Anal.* **176**, 165–225 (2005)
12. Di Leo, C.V., Rejovitzky, E., Anand, L.: A Cahn–Hilliard-type phase-field theory for species diffusion coupled with large elastic deformations: application to phase-separating Li-ion electrode materials. *J. Mech. Phys. Solids* **70**, 1–29 (2014)
13. Duda, F.P., Barbosa, J.M., Guimarães, L.J., Souza, A.C.: Modeling of coupled deformation-diffusion-damage in elastic solids. *Int. J. Model. Simul. Pet. Ind.* **1**, 85–91 (2007)
14. Francfort, G., Marigo, J.-J.: Revisiting brittle fracture as an energy minimization problem. *J. Mech. Phys. Solids* **46**, 1319–1342 (1998)
15. Frémond, M.: *Non-smooth Thermomechanics*. Springer, Berlin (2002)
16. Fried, E., Gurtin, M.: Coherent solid-state phase transitions with atomic diffusion: a thermomechanical treatment. *J. Stat. Phys.* **95**, 1361–1427 (1999)
17. Fujita, A., Fujieda, S., Hasegawa, Y., Fukamichi, K.: Itinerant-electron metamagnetic transition and large magnetocaloric effects in $\text{La}(\text{Fe}_x\text{Si}_{1-x})_{13}$ compounds and their hydrides. *Phys. Rev. B* **67**, 104416 (2003)
18. Garcke, H.: On a Cahn–Hilliard model for phase separation with elastic misfit. *Ann. Inst. H. Poincaré* **22**, 165–185 (2005)
19. Gawin, D., Pesavento, F., Schrefler, B.: Modelling creep and shrinkage of concrete by means of effective stresses. *Mater. Struct.* **40**, 579–591 (2007)
20. Grün, G.: Degenerate parabolic equations of fourth order and a plasticity model with nonlocal hardening. *Zeits. Anal. U. Ihre Anwend.* **14**, 541–573 (1995)
21. Gurtin, M.E.: Generalized Ginzburg–Landau and Cahn–Hilliard equations based on a microforce balance. *Phys. D* **92**, 178–192 (1996)

22. Hamiel, Y., Lyakhovsky, V., Agnon, A.: Coupled evolution of damage and porosity in poroelastic media: theory and applications to deformation of porous rocks. *Geophys. J. Int.* **156**, 701–713 (2004)
23. Hamiel, Y., Lyakhovsky, V., Agnon, A.: Poroelastic damage rheology: dilation, compaction, and failure of rocks. *Geochem. Geophys. Geosyst.* **6**, Q01008 (2005)
24. Havela, L., Miliyanchuk, K., Kolomiets, A.: f-Element hydrides: structure and magnetism. *Int. J. Mater. Res.* **100**, 1182–1186 (2009)
25. Heinemann, C., Kraus, C.: A degenerating Cahn–Hilliard system coupled with complete damage processes. *Math. Bohem.* **139**, 315–331 (2014)
26. Jones, R.A.L.: *Soft Condense Matter*. Oxford University Press, Oxford (2002)
27. Kolomiets, A.V., Havela, L., Yartys, V.A., Andreev, A.V.: Hydrogenation and its effect on crystal structure and magnetism in *R*ENiAl intermetallic compounds. *J. Phys. Stud.* **3**, 55–59 (1999)
28. Kolwicz-Chodak, L., Tarnawski, Z., Figiel, H., Budziak, A., Dawid, T., Havela, L., Kolomiets, A., Kim-Ngan, N.-T.: Specific heat anomalies in $\text{RMn}_2(\text{H}, \text{D})_x$ hydrides. *J. Alloy Compd.* **404**, 51–54 (2005)
29. Krejčí, P., Stefanelli, U.: Existence and nonexistence for the full thermomechanical Souza–Auricchio model of shape memory wires. *Math. Mech. Solids* **16**, 349–365 (2011)
30. Kruis, J., Koudelka, T., Krejčí, T.: Multi-physics analyses of selected civil engineering concrete structures. *Commun. Comput. Phys.* **12**, 885–918 (2012)
31. Latroche, M.: Structural and thermodynamic properties of metallic hydrides used for energy storage. *J. Phys. Chem. Solids* **65**, 517–522 (2004)
32. Lazzaroni, G., Rossi, R., Thomas, M., Toader, R.: Rate-independent damage in thermo-viscoelastic materials with inertia. WIAS Preprint No. 2025, Berlin (2014)
33. Lyakhovsky, V., Hamiel, Y.: Damage evolution and fluid flow in poroelastic rock. *Izv. Phys. Solid Earth* **43**, 13–23 (2007)
34. Mainik, A., Mielke, A.: Existence results for energetic models for rate-independent systems. *Calc. Var. Partial Differ. Equ.* **22**, 73–99 (2005)
35. Mielke, A., Roubíček, T., Stefanelli, U.: Γ -limits and relaxations for rate-independent evolutionary problems. *Calc. Var. Partial Differ. Equ.* **31**, 387–416 (2008)
36. Mielke, A., Roubíček, T., Zeman, J.: Complete damage in elastic and viscoelastic media and its energetics. *Comput. Methods Appl. Mech. Eng.* **199**, 1242–1253 (2010)
37. Mielke, A., Theil, F.: On rate-independent hysteresis models. *Nonlinear Differ. Equ. Appl.* **11**, 151–189 (2004)
38. Podio Guidugli, P., Roubíček, T., Tomassetti, G.: A thermodynamically-consistent theory of the ferro/paramagnetic transition. *Arch. Ration. Mech. Anal.* **198**, 1057–1094 (2010)
39. Podio-Guidugli, P., Tomassetti, G.: On the evolution of domain walls in hard ferromagnets. *SIAM J. Appl. Math.* **64**, 1887–1906 (2004)
40. Podio-Guidugli, P., Tomassetti, G.: Magnetization switching with nonstandard dissipation. *IEEE Trans. Magn.* **42**, 3652–3656 (2006)
41. Podio-Guidugli, P., Vianello, M.: Hypertractions and hyperstresses convey the same mechanical information. *Contin. Mech. Thermodyn.* **22**, 163–176 (2010)
42. Rocca, E., Rossi, R.: “Entropic” solutions to a thermodynamically consistent PDE system for phase transitions and damage. *SIAM J. Math. Anal.* **47**, 2519–2586 (2015)
43. Rocca, E., Rossi, R.: A degenerating PDE system for phase transitions and damage. *Math. Models Methods Appl. Sci.* **24**, 1265–1341 (2014)
44. Roubíček, T.: The Stefan problem in heterogeneous media. *Ann. Inst. Henri Poincaré* **6**, 481–501 (1989)
45. Roubíček, T.: Thermodynamics of rate independent processes in viscous solids at small strains. *SIAM J. Math. Anal.* **42**, 256–297 (2010)
46. Roubíček, T.: *Nonlinear Partial Differential Equations with Applications*, 2nd edn. Birkhäuser, Basel (2013)
47. Roubíček, T.: Nonlinearly coupled thermo-visco-elasticity. *Nonlinear Differ. Equ. Appl.* **20**, 1243–1275 (2013)
48. Roubíček, T., Stefanelli, U.: Magnetic shape-memory alloys: thermomechanical modeling and analysis. *Contin. Mech. Thermodyn.* **26**, 783–810 (2014)
49. Roubíček, T., Tomassetti, G.: Ferromagnets with eddy currents and pinning effects: their thermodynamics and analysis. *Math. Models Methods Appl. Sci.* **21**, 29–55 (2011)
50. Roubíček, T., Tomassetti, G.: Phase transformations in electrically conductive ferromagnetic shape-memory alloys, their thermodynamics and analysis. *Arch. Ration. Mech. Anal.* **210**, 1–43 (2013)
51. Roubíček, T., Tomassetti, G.: Thermodynamics of shape-memory alloys under electric current. *Z. Angew. Math. Phys.* **61**, 1–20 (2010)
52. Roubíček, T., Tomassetti, G.: Thermomechanics of hydrogen storage in metallic hydrides: modeling and analysis. *Discrete Contin. Dyn. Syst. B* **14**, 2313–2333 (2014)
53. Roubíček, T., Tomassetti, G., Zanini, C.: The Gilbert equation with dry-friction-type damping. *J. Math. Anal. Appl.* **355**, 453–468 (2009)

54. Thomas, M.: Rate-independent damage processes in nonlinearly elastic materials. PhD thesis, Institut für Mathematik, Humboldt-Universität zu Berlin (2010)
55. Thomas, M., Mielke, A.: Damage of nonlinearly elastic materials at small strain—existence and regularity results. *Z. Angew. Math. Mech.* **90**, 88–112 (2010)
56. Ubachs, R., Schreurs, P., Geers, M.: A nonlocal diffuse interface model for microstructure evolution of tin–lead solder. *J. Mech. Phys. Solids* **52**, 1763–1792 (2004)
57. Visintin, A.: Strong convergence results related to strict convexity. *Commun. Partial Differ. Equ.* **9**, 439–466 (1984)
58. Visintin, A.: *Models of Phase Transitions*. Birkhäuser, Boston (1996)
59. Wang, H.: *Theory of Linear Poroelasticity with Applications to Geomechanics and Hydrogeology*. Princeton University Press, Princeton (2000)
60. Yan, Q., Toghiani, H., Lee, Y.-W., Liang, K., Causey, H.: Effect of sub-freezing temperatures on a PEM fuel cell performance, startup and fuel cell components. *J. Power Sources* **160**, 1242–1250 (2006)

Tomáš Roubíček
Mathematical Institute
Charles University
Sokolovská 83
186 75 Praha 8
Czech Republic

and

Institute of Thermomechanics of the Czech Academy of Sciences
Dolejšková 5
182 00 Praha 8
Czech Republic
e-mail: tomas.roubicek@mff.cuni.cz

Giuseppe Tomassetti
Dipartimento di Ingegneria Civile e Ingegneria Informatica
Università di Roma “Tor Vergata”
Via Politecnico
00133 Roma
Italy
e-mail: tomassetti@ing.uniroma2.it

(Received: October 30, 2014; revised: July 18, 2015)